

Acceptance Criteria for Moment Frames Based on Structural Testing (ACI 374.1-05) and Commentary

An ACI Standard

Reported by ACI Committee 374

Ronald Klemencic
Chair

John R. Hayes, Jr.
Secretary

Sergio M. Alcocer	Mary Beth D. Hueste	Andres Lepage	Arturo E. Schultz
Mark A. Aschheim	Mohammad Iqbal	Ali M. Memari	Shamim A. Sheikh
John F. Bonacci	Brian E. Kehoe	Vilas S. Mujumdar	Bozidar Stojadinovic
Sergio F. Brena	Dominic J. Kelly	Javeed A. Munshi	Andrew W. Taylor
Paul J. Brienen	Richard E. Klingner	Stavroula J. Pantazopoulou	Raj Valluvan
JoAnn P. Browning	Mervyn J. Kowalsky	Chris P. Pantelides	John W. Wallace
Duane E. Castaneda	Michael E. Kreger	Long T. Phan	Eric B. Williamson
Jeffrey J. Dragovich	Sashi K. Kunnath	Jose A. Pincheira	Sharon L. Wood
Juan Carlos Esquivel	James M. LaFave	Mario E. Rodriguez	Fernando V. Yanez
Luis E. Garcia	Dawn E. Lehman	Murat Saatcioglu	

Originally prepared by Innovation Task Group 1 and Collaborators

Norman L. Scott
Chair

Neil M. Hawkins
Secretary

Michael E. Kreger
James R. Libby

Leslie D. Martin
Robert F. Mast

Collaborators

Geraldine S. Cheok	Suzanne Nakaki	John F. Stanton
S. K. Ghosh	M. J. Nigel Priestley	Dean E. Stephan
H. S. Lew	David C. Seagren*	William C. Stone

*Deceased

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

This document defines the minimum experimental evidence deemed adequate to validate the use, in regions of high seismic risk or in structures assigned to satisfy high seismic performance or design categories, of weak beam/strong column moment frames not in conformance with Chapter 18 of ACI 318-14. This document consists of both a Standard and a Commentary that is not part of the ACI 318-14 Standard and Commentary. The document

ACI Committee 374 adopted ACI T1.1/T1.1R-01 as ACI 374.1-05 on October 12, 2005. ACI T1.1/T1.1R-01 superseded ACI ITG/T1.1-99 and became effective March 9, 2001.

Copyright © 2019, American Concrete Institute.
All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

has been written in such a form that its various parts can be adopted directly into Sections 2, 3, 18.1, and 18.2 of ACI 318-14 and the corresponding sections of the Commentary of ACI 318-14. Among the subjects covered are requirements for: procedures that shall be used to design test modules; configurations for those modules; test methods; test reports; and determination of satisfactory performance.

The Commentary describes some of the considerations of the Innovation Task Group (1) in developing this Standard. The section numbering for the Commentary is the same as that for the Standard, with numbers preceded by an "R" and the text in italics to distinguish them from the corresponding section numbers of the Standard.

The Commentary references documentary evidence, additional to the references of Chapter 18 of the ACI 318-14 Commentary, that supports this Standard. Consistent with the approach of ACI 318-14, no comparison is made between research results for test modules conforming to ACI 318-14 with those for modules that, although not conforming to ACI 318-14, do conform to this Standard. Such comparisons, both experimental and analytical, are available in the references of the Commentary.

Keywords: acceptance criteria; drift ratio; energy dissipation; lateral resistance; moment frame; post-tensioning; precast concrete; prestressed concrete; seismic design; test module; toughness.

CONTENTS

Introduction, p. 2

1.0—Notation, p. 2

2.0—Definitions, p. 3

3.0—Scope, p. 4

4.0—Design procedure, p. 5

5.0—Test modules, p. 5

6.0—Testing agency, p. 6

7.0—Test method, p. 6

8.0—Test report, p. 7

9.0—Acceptance criteria, p. 8

10.0—References, p. 9

INTRODUCTION

For seismic design, 18.2.1.7 in ACI 318-14 specifies 18.2.1.7 that "a reinforced concrete structural system not satisfying this chapter shall be permitted if it is demonstrated by experimental evidence and analysis that the proposed system will have strength and toughness equal to or exceeding those provided by a comparable reinforced concrete structure satisfying this chapter." This Standard defines the minimum experimental evidence that shall be provided in order to validate the use, in regions of high seismic risk or for structures assigned to satisfy high seismic performance or design categories, of a weak beam/strong column moment frame not conforming to the requirements of Chapter 18 of ACI 318-14.

Consistent with the ACI 318-14 requirement for analysis, this Standard specifies that, before the testing mandated by the Standard, a design procedure shall have been developed for prototype frames having the generic form for which acceptance is sought and that design procedure shall be used to

proportion the test modules. Further, the Standard assumes that the prototype frames have forms that are essentially regular, having no significant physical discontinuities in plan or in vertical configuration or in their lateral-force-resisting systems, and that the frames conform to some, but not all, of the requirements of ACI 318-14, Chapter 18. Such frames might, for example, involve use of precast elements, precast-prestressed elements, post-tensioned reinforcement, or combinations of those elements and reinforcement. Prescriptive requirements for moment frames constructed with such elements are not included in ACI 318-14. Such frames might also, for example, use alternate methods, other than those specified in Chapter 18, for force transfer through beam-column joints.

The provisions of this Standard are intended to supplement the provisions of Chapter 18 of ACI 318-14 and not to supplant them.

1.0—Notation

Only notation additional to that in ACI 318-14 is defined.

E_{max} = maximum lateral resistance of test module determined from test results (forces or moments)

E_n = nominal lateral resistance of test module determined using specified geometric properties of test members, specified yield strength of reinforcement, specified compressive strength of concrete, a strain compatibility analysis for flexural moment strength, and a strength reduction factor ϕ of 1.0

E_{pr} = probable lateral resistance of test module determined using actual geometric and material properties of test members, an analysis for probable flexural moment strength of beams based on strain compatibility and including strain-hardening effects in the reinforcement, and a strength reduction factor ϕ of 1.0

λ = column overstrength factor used for test module

θ = drift ratio

β = relative energy dissipation ratio

R1.0—Notation

Only symbols used in this Commentary that are additional to those in Section 2.1 of ACI 318-11 and ACI TI.1-01 are defined in the following:

A_h = area of hysteresis loop

E_1, E_2 = peak lateral resistance for positive, negative, loading for third cycle of loading sequence

f_l = factor on live load defined in R2.6

h = height of column of test module, in. or mm

K, K' = initial stiffness for positive, negative, loading for first cycle

θ_1, θ_2 = drift ratios at peak lateral resistance for positive, negative, loading for third cycle of loading sequence

θ'_1, θ'_2 = drift ratios for zero lateral load for unloading at stiffnesses K, K' from peak positive, negative, lateral resistance for third cycle of loading sequence (Fig. R2.4)

Δ = lateral displacement, in. or mm. See Fig. R2.1