

ACI 546.2R-10

Guide to Underwater Repair of Concrete

Reported by ACI Committee 546



American Concrete Institute®



First Printing
June 2010

American Concrete Institute®
Advancing concrete knowledge

Guide to Underwater Repair of Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI. Proper use of this document includes periodically checking for errata at www.concrete.org/committees/errata.asp for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
U.S.A.

Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN 978-0-87031-383-7

Guide to Underwater Repair of Concrete

Reported by ACI Committee 546

Paul E. Gaudette*
Chair

David W. Whitmore*
Secretary

James Peter Barlow	Fred R. Goodwin	John S. Lund	Joe Solomon
Paul D. Carter	Harald G. Greve	James E. McDonald*	Michael M. Sprinkel
Michael M. Chehab	Ron Heffron	Lawrence G. Mrazek	Ronald R. Stankie
Marwan A. Daye	Robert F. Joyce	Myles A. Murray	Alexander M. Vaysburd*
Peter H. Emmons	Lawrence F. Kahn	Jay H. Paul	Kurt Wagner
Michael J. Garlich*	Brian F. Keane	Richard C. Reed*	Patrick M. Watson
Timothy R. W. Gillespie	Benjamin Lavon	Johan L. Silfwerbrand	Mark V. Ziegler*
Yelena S. Golod	Kenneth M. Lozen		

*Subcommittee members who prepared this guide.

This document provides guidance on the selection and application of materials and methods for the repair and strengthening of concrete structures under water. An overview of materials and methods for underwater repair is presented as a guide for making a selection for a particular application. References are provided for additional information about selected materials and construction methods.

Keywords: anti-washout; cathodic protection; concrete removal; deterioration; diver; formwork; marine placement; pile-jackets; polymer(s); repair; surface preparation; tremie; underwater.

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

Chapter 1—General, p. 546.2R-2

- 1.1—Introduction
- 1.2—Scope
- 1.3—Underwater access technology

Chapter 2—Notation and definitions, p. 546.2R-4

- 2.1—Notation
- 2.2—Definitions

Chapter 3—Causes of deterioration, p. 546.2R-5

- 3.1—Deficient construction practices
- 3.2—Marine organisms
- 3.3—Chemical attack
- 3.4—Corrosion
- 3.5—Mechanical damage
- 3.6—Freezing and thawing damage
- 3.7—Salt scaling
- 3.8—Scour

ACI 546.2R-10 supersedes ACI 546.2R-98 and was adopted and published June 2010. Copyright © 2010, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

Chapter 4—Investigation and evaluation, p. 546.2R-8

- 4.1—Introduction
- 4.2—Visual inspection
- 4.3—Tactile inspection
- 4.4—Underwater nondestructive testing of concrete
- 4.5—Sampling and destructive testing
- 4.6—Evaluation

Chapter 5—Preparation for repair, p. 546.2R-12

- 5.1—General
- 5.2—Excavation and debris removal
- 5.3—Concrete removal
- 5.4—Surface preparation
- 5.5—Reinforcement preparation
- 5.6—Concrete anchors

Chapter 6—Formwork, p. 546.2R-14

- 6.1—General
- 6.2—Rigid forms
- 6.3—Semi-rigid forms
- 6.4—Flexible forms

Chapter 7—Materials and methods, p. 546.2R-19

- 7.1—General considerations
- 7.2—Anti-washout admixtures
- 7.3—Preplaced-aggregate concrete
- 7.4—Tremie concrete
- 7.5—Pumped concrete and grout
- 7.6—Free dump through water
- 7.7—Epoxy grouting
- 7.8—Epoxy injection
- 7.9—Gloved-hand placement
- 7.10—Geomembrane systems
- 7.11—Cathodic protection
- 7.12—Fiber-reinforced polymers

Chapter 8—Inspection of repairs, p. 546.2R-28

- 8.1—Introduction
- 8.2—Procedure
- 8.3—Documentation

Chapter 9—References, p. 546.2R-29

- 9.1—Referenced standards and reports
- 9.2—Cited references

CHAPTER 1—GENERAL

1.1—Introduction

The repair of concrete structures under water presents many complex problems. Although the applicable basic repair procedures and materials are similar to those required in typical concrete repair, the harsh environmental conditions and specific problems associated with working under water or in the splash zone area (Fig. 1.1) create many differences. The repair of concrete under water is usually difficult, requiring specialized products and systems, and the services of highly qualified and experienced design professionals and contractors.

Proper evaluation of existing structural condition is the essential first step in designing long-term repairs. To be most

effective, the evaluation procedure should begin with a review of historical information on the structure and its environment, including any changes made to the structure over time and the records of prior on-site inspections or repairs. Accurate repairs can be designed only after the extent of deterioration is documented and the failure mechanism is determined. In addition, proper repair techniques and installation procedures should be followed to produce an optimum repair system.

Underwater concrete deterioration is a serious economic problem (Fig. 1.2 and 1.3). Water containing oxygen and contaminants can aggressively attack concrete. Selecting appropriate repair materials and methods, and maintaining quality control not normally associated with repair above water are critical when working in a marine environment. As such, underwater repair of concrete is a specialized and highly technical part of concrete repair technology. Successful repairs can be achieved when these factors are carefully implemented. This guide provides an overview of the current status of underwater repair technology to assist the design professional, contractor, and owner in making repair decisions.

1.2—Scope

This guide covers the repair of concrete structures in the splash zone and underwater portions of structures located in lakes, rivers, oceans, and groundwater. Concrete deterioration, investigation and testing procedures, preparation, materials and methodology, and inspection procedures are described. Design considerations and references for underwater repair of concrete bridges, wharves, pipelines, piers, outfalls, bulkheads, and offshore structures are identified. Scour repair, however, is not included in this guide.

One option for repairing underwater structures is to construct a cofferdam around the structure and remove the water inside the cofferdam. Concrete repairs can then be installed in the dry, as discussed in ACI 546R.

1.3—Underwater access technology

Underwater work is generally classified into one of two broad categories for accessing the work site: diving or a remotely operated vehicle (ROV).

Diving is the traditional method of performing tasks under water. In this category, the diver is equipped with life-support systems that provide breathable air and protection from the elements. Manned diving systems include SCUBA (self-contained underwater breathing apparatus) and surface-supplied air. When employing SCUBA, the diver is supplied with breathing air (or gas) from a tank carried by the diver. In surface supply diving, the breathing medium is supplied to the diver through a hose connected to the air (or gas) supply above water.

Performance of duties at higher than one atmosphere ambient pressure causes a multitude of physiological changes within the human body. For example, body tissues absorb and shed gases at different rates than those normally experienced on the surface. Because of this, the time available to perform work under water decreases rapidly with increased water depth. For example, industry standards allow a diver using compressed air to work at 30 ft (10 m) for