

**Guide for Obtaining Cores  
and Interpreting  
Compressive Strength Results**

Reported by ACI Committee 214



**American Concrete Institute®**



First Printing  
June 2010

American Concrete Institute®  
*Advancing concrete knowledge*

## Guide for Obtaining Cores and Interpreting Compressive Strength Results

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI. Proper use of this document includes periodically checking for errata at [www.concrete.org/committees/errata.asp](http://www.concrete.org/committees/errata.asp) for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

**Order information:** ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**U.S.A.**

**Phone: 248-848-3700**  
**Fax: 248-848-3701**

**[www.concrete.org](http://www.concrete.org)**

ISBN 978-0-87031-254-0

# Guide for Obtaining Cores and Interpreting Compressive Strength Results

Reported by ACI Committee 214

Casimir Bognacki  
Chair

Jerry Parnes  
Secretary

David J. Akers  
Madasamy Arockiasamy  
William L. Barringer  
F. Michael Bartlett\*  
Jerrold L. Brown  
James E. Cook  
Ronald L. Dilly\*  
Donald E. Dixon  
Richard D. Gaynor

Alejandro Graf  
Thomas M. Greene  
Gilbert J. Haddad  
Kal R. Hindo  
Robert S. Jenkins  
Alfred L. Kaufman, Jr.\*  
William F. Kepler  
Michael L. Leming  
Colin L. Lobo

John J. Luciano  
Allyn C. Luke  
Stephen Marchese  
Richard E. Miller  
Venkataswamy Ramakrishnan  
D. V. Reddy  
David N. Richardson\*  
James M. Shilstone, Jr.

Bryce P. Simons  
Luke M. Snell  
Patrick J. E. Sullivan  
Eugene Takhtovich  
Michael A. Taylor  
Roger E. Vaughan  
Woodward L. Vogt\*  
Orville R. Werner II

\*Subcommittee members who prepared this document.

*Core testing is the most direct method to determine the compressive strength of concrete in a structure. Generally, cores may be obtained to assess whether concrete in a new structure complies with strength-based acceptance criteria or to evaluate the structural capacity of an existing structure based on the in-place concrete strength. In either case, the process of obtaining core specimens and interpreting strength test results is often confounded by various factors affecting in-place concrete strength or measured strength of test specimens. The scatter in strength test data, which is unavoidable given the inherent randomness of in-place concrete strengths and the uncertainty attributable to preparation and testing of the specimens, may further complicate compliance and evaluation decisions.*

*This guide summarizes practices for obtaining cores and interpreting core compressive strength test results. Factors that affect in-place concrete strength are reviewed so sampling locations that are consistent with objectives of the investigation can be selected. Strength correction factors are presented for converting the measured strength of non-standard core-test specimens to the strength of equivalent specimens with standard diameters, length-to-diameter ratios, and moisture conditioning. This guide provides direction for checking strength compliance of concrete in a structure under*

*construction and methods for determining equivalent specified strength to assess capacity of an existing structure. The materials, processes, quality control measures, and inspections described in this document should be tested, monitored, or performed as applicable only by individuals holding the appropriate ACI Certifications or equivalent.*

**Keywords:** compressive strength; core; hardened concrete; sampling; test.

## CONTENTS

### Chapter 1—Introduction, p. 214.4R-2

- 1.1—Introduction
- 1.2—Background
- 1.3—Scope

### Chapter 2—Notation and definitions, p. 214.4R-3

- 2.1—Notation
- 2.2—Definitions

### Chapter 3—Variation of in-place concrete strength in structures, p. 214.4R-3

- 3.1—Bleeding
- 3.2—Consolidation
- 3.3—Curing
- 3.4—Microcracking
- 3.5—Overall variability of in-place strengths

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 214.4R-10 supersedes ACI 214.4R-03 and was adopted and published June 2010. Copyright © 2010, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

## Chapter 4—Planning the testing program, p. 214.4R-5

- 4.1—Investigating concrete in a new structure using strength-based acceptance criteria
- 4.2—Evaluating existing structure capacity using in-place strengths

## Chapter 5—Obtaining test specimens, p. 214.4R-6

## Chapter 6—Core testing, p. 214.4R-6

## Chapter 7—Analyzing strength test data, p. 214.4R-7

- 7.1—ASTM C42/C42M precision statements
- 7.2—Review of core strength correction factors
- 7.3—Statistical analysis techniques

## Chapter 8—Investigation of low-strength test results in new construction using ACI 318, p. 214.4R-10

## Chapter 9—Determining an equivalent $f'_c$ value for evaluating structural capacity of an existing structure, p. 214.4R-10

- 9.1—Conversion of core strengths to equivalent in-place strengths
- 9.2—Uncertainty of estimated in-place strengths
- 9.3—Percentage of in-place strengths less than  $f'_c$
- 9.4—Methods to estimate the equivalent specified strength

## Chapter 10—References, p. 214.4R-13

- 10.1—Referenced standards and reports
- 10.2—Cited references

## Appendix—Example calculations, p. 214.4R-15

- A.1—Outlier identification in accordance with ASTM E178 criteria
- A.2—Student's  $t$  test for significance of difference between observed average values
- A.3—Equivalent specified strength by tolerance factor approach
- A.4—Equivalent specified strength by alternate approach

## CHAPTER 1—INTRODUCTION

### 1.1—Introduction

Core testing is the most direct method to determine the in-place compressive strength of concrete in a structure. Generally, cores are obtained to:

- Assess, if required, whether concrete in a new structure complies with strength-based acceptance criteria; or
- Determine in-place concrete strengths in an existing structure for evaluation of structural capacity.

In new construction, cylinder strength tests failing to meet strength-based acceptance criteria can be investigated using provisions given in ACI 318. These criteria specify the circumstances when core tests are permitted, the number of cores to be tested, the conditioning of the cores before testing, the limits on the time interval between coring and testing, and the basis for determining whether the concrete in the area represented by the core strengths is structurally adequate. This

guide presents procedures for obtaining and testing cores and interpreting results in accordance with ACI 318.

If strength records are unavailable, the in-place strength of concrete in an existing structure can be evaluated using cores. This in-place strength determination is simplified when in-place strength data are converted into an equivalent specified compressive strength  $f'_c$  value that can be directly substituted into conventional strength equations with customary strength reduction factors. This guide presents procedures for performing this conversion in a manner consistent with the assumptions used to derive strength reduction factors for structural design.

### 1.2—Background

Analysis of core test data can be difficult and can subsequently lead to uncertain interpretations and conclusions. Based on 10 hypothetical core test results, 23 practitioners responding to a survey in 2000 estimated the compressive strength of in-place concrete between 3000 and 5000 psi (21 and 35 MPa) (Hanson 2007). Strength interpretations should always be made by, or with the assistance of, an investigator experienced in concrete technology. Factors contributing to the scatter of core strength test results include:

- Systematic variation of in-place strength along a member or throughout the structure;
- Random variation of concrete strength, both within one batch and among batches;
- Low test results attributable to flawed test specimens or improper test procedures;
- Effects of the size, aspect ratio, and moisture condition of the test specimen on the measured strengths; and
- Additional uncertainty attributable to testing that is present even for tests performed in strict accordance with standardized testing procedures.

### 1.3—Scope

This guide summarizes current practices for obtaining cores and interpreting core compressive strength test results in light of past and current research findings. Many of these findings are based on older references as the research has reached a mature state. Parallel procedures are presented for cases where cores are obtained to assess whether concrete strength in a new structure complies with strength-based acceptance criteria, and to determine a value based on the actual in-place concrete strength equivalent to the specified compressive strength  $f'_c$ . The latter can be directly substituted into conventional strength equations with customary strength reduction factors for strength evaluation of an existing structure. It is inappropriate to use procedures for determining the equivalent specified concrete strength to assess whether concrete strength in a new structure complies with strength-based acceptance criteria.

The order of contents parallels the logical sequence of activities in a typical core-test investigation. Chapter 3 describes how bleeding, consolidation, curing, and micro-cracking affect in-place concrete strength in structures so the investigator can account for this strength variation when planning the testing program. Chapter 4 identifies preferred