

American Society of Civil Engineers

Compaction Grouting Consensus Guide

This document uses both the International System of Units (SI) and customary units.



Library of Congress Cataloging-in-Publication Data

American Society of Civil Engineers. Standards 53-10-Consensus Guide Committee.

Compaction grouting consensus guide : ASCE standard ASCE/G-I53-10 / American Society of Civil Engineers, Standards 53-10-Consensus Guide Committee.

p. cm.

ISBN 978-0-7844-1094-3

1. Grouting—Standards—United States. 2. Soil compaction—Standards—United States. 3. Soil stabilization—Standards—United States. I. Title.

TA755.A44 2010

624.1'51363—dc22

2010014960

Published by American Society of Civil Engineers
1801 Alexander Bell Drive
Reston, Virginia 20191
www.pubs.asce.org

This standard was developed by a consensus standards development process which has been accredited by the American National Standards Institute (ANSI). Accreditation by ANSI, a voluntary accreditation body representing public and private sector standards development organizations in the U.S. and abroad, signifies that the standards development process used by ASCE has met the ANSI requirements for openness, balance, consensus, and due process.

While ASCE's process is designed to promote standards that reflect a fair and reasoned consensus among all interested participants, while preserving the public health, safety, and welfare that is paramount to its mission, it has not made an independent assessment of and does not warrant the accuracy, completeness, suitability, or utility of any information, apparatus, product, or process discussed herein. ASCE does not intend, nor should anyone interpret, ASCE's standards to replace the sound judgment of a competent professional, having knowledge and experience in the appropriate field(s) of practice, nor to substitute for the standard of care required of such professionals in interpreting and applying the contents of this standard.

ASCE has no authority to enforce compliance with its standards and does not undertake to certify products for compliance or to render any professional services to any person or entity.

ASCE disclaims any and all liability for any personal injury, property damage, financial loss or other damages of any nature whatsoever, including without limitation any direct, indirect, special, exemplary, or consequential damages, resulting from any person's use of, or reliance on, this standard. Any individual who relies on this standard assumes full responsibility for such use.

ASCE and American Society of Civil Engineers—Registered in U.S. Patent and Trademark Office.

Photocopies and reprints. You can obtain instant permission to photocopy ASCE publications by using ASCE's online permission service (<http://pubs.asce.org/permissions/requests/>). Requests for 100 copies or more should be submitted to the Reprints Department, Publications Division, ASCE (address above); e-mail: permissions@asce.org. A reprint order form can be found at <http://pubs.asce.org/support/reprints/>.

Copyright © 2010 by the American Society of Civil Engineers.
All Rights Reserved.

ISBN 978-0-7844-1094-3

Manufactured in the United States of America.

STANDARDS

In 2003, the Board of Direction approved the revision to the ASCE Rules for Standards Committees to govern the writing and maintenance of standards developed by the Society. All such standards are developed by a consensus standards process managed by the Society's Codes and Standards Committee (CSC). The consensus process includes balloting by a balanced standards committee made up of Society members and nonmembers, balloting by the membership of the Society as a whole, and balloting by the public. All standards are updated or reaffirmed by the same process at intervals not exceeding five years.

The following standards have been issued:

- ANSI/ASCE 1-82 N-725 Guideline for Design and Analysis of Nuclear Safety Related Earth Structures
- ASCE/EWRI 2-06 Measurement of Oxygen Transfer in Clean Water
- ANSI/ASCE 3-91 Standard for the Structural Design of Composite Slabs
- ASCE 4-98 Seismic Analysis of Safety-Related Nuclear Structures
- Building Code Requirements for Masonry Structures (ACI 530-02/ASCE 5-02/TMS 402-02) and Specifications for Masonry Structures (ACI 530.1-02/ASCE 6-02/TMS 602-02)
- ASCE/SEI 7-05 Minimum Design Loads for Buildings and Other Structures
- SEI/ASCE 8-02 Standard Specification for the Design of Cold-Formed Stainless Steel Structural Members
- ANSI/ASCE 9-91 Standard Practice for the Construction and Inspection of Composite Slabs
- ASCE 10-97 Design of Latticed Steel Transmission Structures
- SEI/ASCE 11-99 Guideline for Structural Condition Assessment of Existing Buildings
- ASCE/EWRI 12-05 Guideline for the Design of Urban Subsurface Drainage
- ASCE/EWRI 13-05 Standard Guidelines for Installation of Urban Subsurface Drainage
- ASCE/EWRI 14-05 Standard Guidelines for Operation and Maintenance of Urban Subsurface Drainage
- ASCE 15-98 Standard Practice for Direct Design of Buried Precast Concrete Pipe Using Standard Installations (SIDD)
- ASCE 16-95 Standard for Load Resistance Factor Design (LRFD) of Engineered Wood Construction
- ASCE 17-96 Air-Supported Structures
- ASCE 18-96 Standard Guidelines for In-Process Oxygen Transfer Testing
- ASCE 19-96 Structural Applications of Steel Cables for Buildings
- ASCE 20-96 Standard Guidelines for the Design and Installation of Pile Foundations
- ANSI/ASCE/T&DI 21-05 Automated People Mover Standards—Part 1
- ANSI/ASCE/T&DI 21.2-08 Automated People Mover Standards—Part 2
- ANSI/ASCE/T&DI 21.3-08 Automated People Mover Standards—Part 3
- ANSI/ASCE/T&DI 21.4-08 Automated People Mover Standards—Part 4
- SEI/ASCE 23-97 Specification for Structural Steel Beams with Web Openings
- ASCE/SEI 24-05 Flood Resistant Design and Construction
- ASCE/SEI 25-06 Earthquake-Actuated Automatic Gas Shutoff Devices
- ASCE 26-97 Standard Practice for Design of Buried Precast Concrete Box Sections
- ASCE 27-00 Standard Practice for Direct Design of Precast Concrete Pipe for Jacking in Trenchless Construction
- ASCE 28-00 Standard Practice for Direct Design of Precast Concrete Box Sections for Jacking in Trenchless Construction
- ASCE/SEI/SFPE 29-05 Standard Calculation Methods for Structural Fire Protection
- SEI/ASCE 30-00 Guideline for Condition Assessment of the Building Envelope
- SEI/ASCE 31-03 Seismic Evaluation of Existing Buildings
- SEI/ASCE 32-01 Design and Construction of Frost-Protected Shallow Foundations
- EWRI/ASCE 33-01 Comprehensive Transboundary International Water Quality Management Agreement

STANDARDS

- EWRI/ASCE 34-01 Standard Guidelines for Artificial Recharge of Ground Water
- EWRI/ASCE 35-01 Guidelines for Quality Assurance of Installed Fine-Pore Aeration Equipment
- CI/ASCE 36-01 Standard Construction Guidelines for Microtunneling
- SEI/ASCE 37-02 Design Loads on Structures during Construction
- CI/ASCE 38-02 Standard Guideline for the Collection and Depiction of Existing Subsurface Utility Data
- EWRI/ASCE 39-03 Standard Practice for the Design and Operation of Hail Suppression Projects
- ASCE/EWRI 40-03 Regulated Riparian Model Water Code
- ASCE/SEI 41-06 Seismic Rehabilitation of Existing Buildings
- ASCE/EWRI 42-04 Standard Practice for the Design and Operation of Precipitation Enhancement Projects
- ASCE/SEI 43-05 Seismic Design Criteria for Structures, Systems, and Components in Nuclear Facilities
- ASCE/EWRI 44-05 Standard Practice for the Design and Operation of Supercooled Fog Dispersal Projects
- ASCE/EWRI 45-05 Standard Guidelines for the Design of Urban Stormwater Systems
- ASCE/EWRI 46-05 Standard Guidelines for the Installation of Urban Stormwater Systems
- ASCE/EWRI 47-05 Standard Guidelines for the Operation and Maintenance of Urban Stormwater Systems
- ASCE/SEI 48-05 Design of Steel Transmission Pole Structures
- ASCE/EWRI 50-08 Standard Guideline for Fitting Saturated Hydraulic Conductivity Using Probability Density Functions
- ASCE/EWRI 51-08 Standard Guideline for Calculating the Effective Saturated Hydraulic Conductivity
- ASCE/SEI 52-10 Design of Fiberglass-Reinforced Plastic (FRP) Stacks
- ASCE/G-I 53-10 Compaction Grouting Consensus Guide

FOREWORD

The Board of Direction approved revisions to the ASCE Rules for Standards Committees to govern the writing and maintenance of standards developed by ASCE. All such standards are developed by a consensus standards process managed by the ASCE Codes and Standards Committee. The consensus process includes balloting by a balanced standards committee and reviewing during a public comment period. All standards are updated or reaffirmed by the same process at intervals not exceeding five years.

The provisions of this document are written in permissive language and, as such, offer to the user a series of options or instructions but do not prescribe a specific course of action. Significant judgment is left to the user of this document.

This, the first edition of the *Compaction Grouting Consensus Guide*, has been written to promote good practice in compaction grouting. The authors of this guide believe that compaction grouting is a reliable methodology for improving the density and strength of the soil. Similar to other grouting technologies, compaction grouting is a technology based on sound engineering principles, not a

“black magic” that can only be understood by a chosen few. And, like all other soil improvement techniques, compaction grouting needs to be applied competently.

This guide provides background for those interested in specifying, designing, and/or undertaking compaction grouting. This guide is not a manual and is not intended for use as a code of practice; hence it is not accidental that nonmandatory language is used throughout the text. But those involved in the development of this guide hope that it will become a useful reference for all those interested in compaction grouting.

This standard has been prepared in accordance with recognized engineering principles and should not be used without the user’s competent knowledge for a given application. The publication of this standard by ASCE is not intended to warrant that the information contained herein is suitable for any general or specific use, and ASCE takes no position respecting the validity of patent rights. The user is advised that the determination of patent rights or risk of infringement is entirely their own responsibility.

COMPACTION GROUTING COMMITTEE ROSTER

Dawn Shuttle, *Chair*
Samuel Bandimere
Richard Berry
Michael Byle
Allen Cadden
Jerry Di Maggio
Eric Drooff
Curtis M. Fitzgerald
Jeffrey Geraci

Lawrence B. Gruner
Michael G. Jefferies
Lawrence F. Johnsen
Scott Kieffer
Michael J. Miluski
Silas Nichols
Cumaraswamy Vipulanandan
James Warner
Peter T. Yen

SCOPE OF THE CONSENSUS GUIDE

Compaction grouting is a ground improvement technique that improves the strength and/or stiffness of the ground by slow and controlled injection of a low-mobility grout. The soil is displaced and compacted as the grout mass expands. Provided the injection process progresses in a controlled fashion, the grout material remains as a growing mass within the ground and does not permeate or fracture the soil. This behavior enables consistent densification around the expanding grout mass, resulting in stiff inclusions of grout surrounded by soil of increased density.

This guide focuses specifically on applications of compaction grouting where the increased strength and/or stiffness of the soil due to compaction is a primary element of the ground improvement. Applications where a ground improvement design requires the injected grout to obtain a strength greater than that of the surrounding soil, although potentially a valid application of low-mobility grout, are not considered to be compaction grouting for the purposes of this guide and hence are beyond the scope of this document.

Both practical and theoretical aspects of compaction grouting are discussed.

This guide follows the guidelines of the ASCE and uses the International System of Units (SI) as the primary system of units; imperial units are also provided in parentheses. Compaction grouting in North America typically uses imperial units in the field; hence many of the SI units have been calculated from the original imperial equivalents. In these cases an effort has been made to keep the “rule of thumb” values in their original form, and some loss of accuracy in the conversion between units may occur.

This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address the safety problems associated with its application. It is the responsibility of whoever uses this standard to establish appropriate safety and health practices and to determine the applicability of regulatory and nonregulatory limitations.

CONTENTS

Standards	iii
Foreword	v
Compaction Grouting Committee Roster	vii
Scope of the Consensus Guide	ix
1 Introduction to the Compaction Grouting Guide	1
1.1 What Is Compaction Grouting?	1
1.2 Short History of Compaction Grouting	1
1.3 Purpose and Development of This Guide	2
2 Mechanics of Compaction Grouting	5
2.1 Basic Mechanics	5
2.2 Soil Conditions	6
2.3 Field Evidence on Compaction Grout Behavior	7
3 Compaction Grouting Materials	9
3.1 Introduction	9
3.2 Factors Affecting Grout Mobility	9
3.3 Composition	10
3.4 Design of the Grout Mix	10
4 Grouting in the Field	13
4.1 Methodology	13
4.2 Equipment	15
4.2.1 Mixing	15
4.2.2 Pumps	16
4.2.3 Hoses and Fittings	16
4.2.4 Safety on Site	16
4.2.5 Casings	17
4.2.6 Headers	17
4.2.7 Fittings	17
4.2.8 Pressure Gauges	18
4.3 Drilling	18
5 Subsurface Investigation for Compaction Grouting	21
5.1 Investigation Planning	21
5.2 General Investigations	21
5.2.1 Data Review	22
5.2.2 Sampling	22
5.2.3 Investigation Limits	22
5.2.4 Laboratory Testing	23
5.2.5 Analysis and Report	23
5.3 Investigations for Grouting Design	24
5.3.1 Defining the Purpose of Grouting	24
5.3.2 Defining the Mechanism of Grouting	24
5.3.3 Determining the Extent of Grouting	24
5.3.4 Selecting Exploration Methods	25
5.3.5 Logging of Field Investigation	25

CONTENTS

5.3.6	Field Inspectors	25
5.3.7	Flexibility to Accommodate the Unexpected	26
5.3.8	Record and Report Everything	26
6	Design of Compaction Grouting	27
6.1	Introduction	27
6.2	Geometric Idealization of the Grout Mass	27
6.3	Suitability of In Situ Soil for Compaction Grouting	28
6.4	Pressure–Volume Behavior of In Situ Soil	30
6.5	Pressure–Volume Behavior of Grout	31
6.6	Pressure Losses in the Casing	32
6.7	Injection Sequence	32
6.8	Injection Spacing	33
6.9	Estimating Grout Quantities	33
6.9.1	Densification	33
6.10	Limitations on Grout Injection	34
6.10.1	Soil Confinement	34
6.10.2	Influence on Structures	35
6.11	Measuring Refusal	36
6.12	Grouting Records	36
7	Analysis of Compaction Grouting	37
7.1	Introduction	37
7.2	Methods of Analysis	37
7.2.1	Geometric Idealization	37
7.2.2	Alternative Soil Models	37
7.2.3	Importance of Large Strain	39
7.2.4	Simple Approach	40
7.2.5	Numerical Cavity Expansion	40
7.2.6	Commercial Finite Element Codes	41
7.2.7	Consolidation of the In Situ Soil during and after Grouting	41
7.3	Importance of Monitoring Grout Injection	43
7.4	Centrifuge Modeling	43
7.5	Field Trials	44
8	Verification of Grouting Effectiveness	45
8.1	Overview of Verification Program Development	45
8.2	Planning an Effective Program	46
8.2.1	Goals of Verification	46
8.2.2	Verification by Design	46
8.2.3	Test or Preconstruction Grouting	46
8.2.4	Monitoring During Construction	46
8.3	Verification Methods	47
8.4	Detecting Movement	47
8.4.1	Crack Monitors	48
8.4.2	Tiltmeters	48
8.4.3	String Lines, Plumb Bobs, and Spirit Levels	49
8.4.4	Fluid Levels	49
8.4.5	Rotating Laser Levels	50
8.5	Evaluating Density Changes	51
8.5.1	Penetration Resistance	51
8.5.2	Excavation and Coring	52
8.6	Geophysical Methods	52
8.7	Summary and Conclusions	52

9 Applications	55
9.1 Settlement Correction	55
9.1.1 Soil Improvement under Existing Structures	55
9.1.2 Deep Foundations	55
9.1.3 Improving Collapsible Soils	55
9.1.4 Settlement Mitigation References	56
9.2 Preconstruction Soil Densification Applications	56
9.2.1 Liquefaction Mitigation	56
9.2.2 Soil Improvement under Proposed Structures	56
9.2.3 Soft Ground Tunneling	56
9.2.4 Foundations Involving Lateral Loading	56
9.2.5 Preconstruction Soil Densification References	57
9.3 Sinkhole Remediation	57
9.4 Further Information	57
Appendix A Guide Specifications for Compaction Grouting Using the Bottom-Up System	59
References	71
Index	77

INTRODUCTION TO THE COMPACTION GROUTING GUIDE

1.1 WHAT IS COMPACTION GROUTING?

Compaction grouting is a ground improvement technique that improves the strength and/or stiffness of the ground by slow and controlled injection of a low-mobility grout. The soil is displaced and compacted as the grout mass expands. Provided that the injection process progresses in a controlled fashion, the grout material remains as a growing mass within the ground and does not permeate or fracture the soil. This behavior enables consistent densification around the expanding grout mass, resulting in stiff inclusions of grout surrounded by soil of increased density. The process can be applied equally well above or below the water table. It is usually applied to loose fills and loose native soils that have sufficient drainage to prevent buildup of excess pore pressures.

1.2 SHORT HISTORY OF COMPACTION GROUTING

Although grouting as an engineered process is not new, with many records of grouting projects dating back before the 1800s, compaction grouting is a more recent grouting method, dating back only to the middle of the 20th century. Compaction grouting is also noteworthy as the only major grouting technology to originate in the United States. Today this technology is widely used worldwide. The development of compaction grouting is particularly interesting in that it appears to have come about serendipitously and seems to have progressed through the efforts and innovations of many small, independent contractors.

The first use of low-mobility grout (i.e., grouts that have a consistency similar to very stiff mortar) for ground improvement was in the latter part of 1952, when a small contractor in Los Angeles, California, named James Warner needed to fill some small voids under a structure (Warner 2003). Filling the void with a cement mortar seemed like the most expeditious repair, and “unable to find either established technology or equipment to pump the mortar, he constructed a ‘pump,’ which consisted of a length of six-inch-diameter steel casing about five feet long

and positioned vertically in a wooden frame. It had a two-inch hose attached to the bottom and a ‘piston’ consisting of a wood disk fitted with a few layers of old carpet cut to the casing diameter to form a seal. The piston was attached to a push rod of 2” × 4” lumber.”

Fortunately for the progress of compaction grouting, Warner was unaware of the then-well-established rule of thumb in grouting: “If you can’t pour it, you can’t pump it.” So he directed his efforts to pumping plastic-consistency grouts. He was fortunate to meet others with the similar goal of pumping another low-mobility mortar, Portland cement plaster, to elevated scaffolds. Success came two years later, in 1954, when mainly because of the efforts of Marvin Bennett, a working pump was constructed. Marvin Bennett, along with his brother Richard, also went on to develop the first plaster pump in 1954, followed by the first concrete pump in 1961. Warner, however, continued his efforts to develop appropriate equipment and technology for grouting.

During the late 1950s, the use of low-mobility grouts for void filling had become common. The use of these plastic-consistency grouts was further extended to jacking of structures, using the important feature of such grouts: that they move as a globular mass whose movement can be controlled. However, compaction grouting for increasing the soil’s strength was not yet a primary focus of the technology. The earliest mention of the use of stiff, mortarlike grout, termed *compaction grout*, was by Graf (1969), who described the use of the Koehring Mudjack, a machine dating from 1934, to pump a clayey loam mixture under pavement for highway maintenance. He reported that some of the mudjack operators had found it useful to pump “zero slump” grout through pipes driven into the ground for raising structures and that larger than calculated quantities were sometimes used, concluding that the surrounding soil was being compacted. He referred to this as *compaction grouting* and stated that “hundreds of jobs have now been successfully completed together with some failures,” although no examples were provided. The term *compaction grouting* was further used by Mitchell (1970) as a method of foundation soil treatment.