

Report on Roller-Compacted Mass Concrete

Reported by ACI Committee 207



American Concrete Institute®
Advancing concrete knowledge



First Printing
July 2011

American Concrete Institute®
Advancing concrete knowledge

Report on Roller-Compacted Mass Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at www.concrete.org/committees/errata.asp. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
U.S.A.

Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN 978-0-87031-277-9

Report on Roller-Compacted Mass Concrete

Reported by ACI Committee 207

Timothy P. Dolen
Chair

Jeffrey C. Allen
Terrence E. Arnold
Randall P. Bass
Anthony A. Bombich

Teck L. Chua
Barry D. Fehl
John W. Gajda
Rodney E. Holderbaum

David E. Kiefer
Gary R. Mass
Tibor J. Pataky
Jonathan L. Poole

Henry B. Prenger
Ernest K. Schrader
Stephen B. Tatro
Michael A. Whisonant

Note: ACI Committee 207 would like to acknowledge Tim Dolen and Nate Tarbox for their significant contributions to the document.

Consulting members

Eric J. Ditchey
Brian A. Forbes
Richard A. Kaden

William F. Kepler
Tom W. Read

Roller-compacted concrete (RCC) is a concrete of no-slump consistency in its unhardened state that is typically transported, placed, and compacted using earth and rockfill construction equipment. This report includes the use of RCC in structures where measures should be taken to cope with the generation of heat from hydration of the cementitious materials and attendant volume change to minimize cracking. Material mixture proportioning, properties, design considerations, construction, and quality control are covered.

The materials, processes, quality control measures, and inspections described in this document should be tested, monitored, or performed as applicable only by individuals holding the appropriate ACI certifications or equivalent.

Keywords: admixtures; aggregates; air entrainment; compacting; compressive strength; conveying; creep properties; curing; lift joints; mixture proportioning; monolith joints; placing; shear properties; vibration; workability.

ACI Committee Reports, Guides, Manuals, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

Chapter 1—Introduction, p. 2

- 1.1—General
- 1.2—What is roller-compacted concrete?
- 1.3—History
- 1.4—Advantages and disadvantages
- 1.5—Performance of RCC dams

Chapter 2—Notation and definitions, p. 9

- 2.1—Notation
- 2.2—Definitions

Chapter 3—Materials and mixture proportioning for roller-compacted concrete, p. 9

- 3.1—General
- 3.2—Materials
- 3.3—Mixture proportioning considerations
- 3.4—Mixture proportioning methods
- 3.5—Laboratory trial mixtures
- 3.6—Field adjustments

Chapter 4—Properties of hardened roller-compacted concrete, p. 19

- 4.1—General
- 4.2—Strength

ACI 207.5R-11 supersedes ACI 207.5R-99 and was adopted and published July 2011. Copyright © 2011, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 4.3—Elastic properties
- 4.4—Dynamic properties
- 4.5—Creep
- 4.6—Volume change
- 4.7—Thermal properties
- 4.8—Tensile strain capacity
- 4.9—Permeability
- 4.10—Durability
- 4.11—Density

Chapter 5—Design of roller-compacted concrete dams, p. 27

- 5.1—General
- 5.2—Foundation
- 5.3—Dam section considerations
- 5.4—Stress and stability analyses
- 5.5—Temperature studies and control
- 5.6—Contraction joints and cracks
- 5.7—Galleries and drainage
- 5.8—Facing design and seepage control
- 5.9—Spillways, aprons, and stilling basins
- 5.10—Outlet works

Chapter 6—Construction of roller-compacted concrete dams, p. 39

- 6.1—General
- 6.2—Aggregate production and batching and mixing plant location
- 6.3—Batching and mixing
- 6.4—Transporting and placing
- 6.5—Compaction
- 6.6—Lift joints
- 6.7—Contraction joints
- 6.8—Forms and facings
- 6.9—Curing and protection from weather
- 6.10—Galleries and drainage

Chapter 7—Quality control of roller-compacted concrete, p. 56

- 7.1—General
- 7.2—Activities before RCC placement
- 7.3—Activities during RCC placement
- 7.4—Activities after RCC placement

Chapter 8—References, p. 66

- 8.1—Referenced standards and reports
- 8.2—Cited references

CHAPTER 1—INTRODUCTION

1.1—General

Roller-compacted concrete (RCC) is probably the most important development in concrete dam technology in the past quarter century. The use of RCC has allowed many new dams to become economically feasible due to the reduced cost realized from the rapid construction method. It also has provided design engineers with an opportunity to economically rehabilitate existing concrete dams that have problems with stability and need buttressing in addition to improving existing embankment dams with inadequate spillway



Fig. 1.1—RCC compaction with dual-drum, vibrating roller (Serra do Facão Dam, Brazil, 2008).

capacity by providing a means by which they can be safely overtopped. RCC has allowed new embankment dams to optimize spillway capacity in over-the-embankment-type emergency spillways (Hansen 1992).

This document summarizes the current state of the art for design and construction of RCC in mass concrete applications. It is intended to guide the reader through developments in RCC technology, including materials, mixture proportioning, properties, design considerations, construction, and quality control and testing. Although this report deals primarily with mass placements, RCC is also used for pavements (refer to ACI 325.10R) and for dam stability improvement and as embankment dam slope protection (United States Society on Dams 2003).

1.2—What is roller-compacted concrete?

ACI Concrete Terminology (2010) defines roller-compacted concrete (RCC) as “concrete compacted by roller compaction; concrete that, in its unhardened state, will support a roller while being compacted.” RCC is usually mixed using high-capacity continuous mixing or batching equipment, delivered with trucks or conveyors, and spread with bulldozers in layers prior to compaction with vibratory rollers (Fig. 1.1). Because of RCC’s zero-slump consistency, subsequent lifts can be placed immediately after compaction of the previous lift. RCC can use a broader range of materials than conventional concrete, and derives its strength and durability from a mixture philosophy that relies on using just enough paste volume to fill the aggregate voids and no more water content than what is needed for proper workability.

1.3—History

The rapid worldwide acceptance of RCC is a result of economics and of RCC’s successful performance. A bibliography of dams constructed is available from the International Commission on Large Dams. Other listings of dams constructed can be obtained from the United States Society on Dams (2003) and from the U.S. Army Corps of Engineers (USACE), EM 1110-2-2006 (USACE 2000). During the 1960s and 1970s, applications of RCC materials led to the development of RCC in engineered concrete structures. In the 1960s, a high-production no-slump mixture that could be