

**Report on Grouting between  
Foundations and Bases for Support  
of Equipment and Machinery**

Reported by ACI Committee 351



**American Concrete Institute®**



First Printing  
March 2012

American Concrete Institute®  
*Advancing concrete knowledge*

## **Report on Grouting between Foundations and Bases for Support of Equipment and Machinery**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at [www.concrete.org/committees/errata.asp](http://www.concrete.org/committees/errata.asp). Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

**Order information:** ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**U.S.A.**  
**Phone: 248-848-3700**  
**Fax: 248-848-3701**

**[www.concrete.org](http://www.concrete.org)**

## Report on Grouting between Foundations and Bases for Support of Equipment and Machinery

Reported by ACI Committee 351

David Kerins\*, Chair

Mukti L. Das\*, Secretary

Omesh B. Abhat  
Richard P. Bohan  
William L. Bounds  
William D. Brant\*  
Michael M. Chehab  
Shu-Jin Fang  
Fred R. Goodwin  
Shraddhakar Harsh  
Erick N. Larson  
Robert R. McGlohn\*  
Carl A. Nelson  
Richard O'Malley\*

Michael A. Paipal\*  
Ira W. Pearce  
Charlie L. Rowan\*  
William E. Rushing Jr.  
Yasser Salem\*  
Larry W. Schulze  
Philip A. Smith\*†  
Widianto  
F. Alan Wiley  
Sheng-Chi Wu\*

\*Members of Subcommittee 351.1 who prepared this report.

†Subcommittee 351.1 Chair.

*This report provides an overview of current practices of grouting for support of equipment and machinery. Materials and installation methods are described for epoxy and cementitious-based grouts used as the load-transfer material between equipment bases and their foundations.*

*Characteristics of placed material, test methods for forecasting long-term performance, qualification of grout materials, foundation design and detailing considerations, and installation procedures are described.*

**Keywords:** bleeding; consistency tests; curing; durability; epoxy grout; cementitious-based grout; equipment grout; formwork (construction); foundations; grout; hydraulic cement grout; inspection; machinery grout; mixing; placing; sand-cement grout; stiffness; strength; tests; volume change.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

### CONTENTS

#### Chapter 1—Scope, p. 2

1.1—Scope

#### Chapter 2—Definitions, p. 2

2.1—Definitions

#### Chapter 3—Grout, p. 2

3.1—Requirements

3.2—Overview of nonshrink grouts

3.3—Selection

3.4—Common issues

#### Chapter 4—Nonshrink cementitious grouts, p. 5

4.1—Introduction

4.2—Properties

4.3—Material requirements

4.4—Testing

ACI 351.1R-12 supersedes ACI 351.1R-99 and was adopted and published March 2012. Copyright © 2012, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

**Chapter 5—Nonshrink epoxy grouts, p. 10**

- 5.1—Introduction
- 5.2—Properties
- 5.3—Material requirements
- 5.4—Testing

**Chapter 6—Design, detailing, and construction, p. 14**

- 6.1—Design and detailing considerations for grout
- 6.2—Preparation for grouting
- 6.3—Grout mixing and placing
- 6.4—Curing and protection
- 6.5—Quality control/assurance

**Chapter 7—References, p. 21**

- 7.1—Referenced standards and reports

**CHAPTER 1—SCOPE****1.1—Scope**

This report provides an overview of current practices for grouting to support equipment and machinery. Recommendations are provided for those portions of the grouting operation where a consensus could be developed among knowledgeable manufacturers and users. Various approaches are outlined for areas where opinions differ. Many statements and much of the information contained in this report are based on published manufacturers' data and observations and practical experience by technical representatives and users. There is little current published research available at this time, but the information in this report is the most current information available. This report describes materials and installation methods for grouts used as load-transfer material between machine or equipment bases and their foundations. Characteristics of the placed material, test methods for forecasting their long-term performance, and installation procedures are included. The information may also be appropriate for other types of applications where filling of the space between load-carrying members is required, such as under column baseplates or in joints between precast concrete elements.

Machinery and equipment that have precise tolerances for alignment or require uniform support cannot be placed directly on finished concrete surfaces. Both the concrete surface and the machine base have irregularities that result in alignment difficulties and bearing load concentrations. For this reason, machine bases or soleplates are aligned and leveled by shimming or other means, and the resulting space between the machine base and the foundation is filled with a load-transfer grout material. The load-transfer grout materials most frequently used are nonshrink cementitious grouts and nonshrink epoxy grouts.

**CHAPTER 2—DEFINITIONS**

ACI provides a comprehensive list of definitions through an online resource "ACI Concrete Terminology" (<http://terminology.concrete.org>). Definitions provided herein complement that resource.

**2.1—Definitions**

**aggregate reduction**—reducing the normal four bags of aggregate used with most commercial epoxy grout mixtures to two or three bags.

**amine blush**—cloudy finish to the surface of an epoxy grout that can inhibit bonding of subsequent applications.

**chock**—wedge or block for steadying a body and holding it motionless.

**cure time**—time after setting in which chemical and physical changes in the grout produces long-term durability strength and serviceability.

**flowable grout**—a cementitious grout consistency with a flow of 125 to 145 by the flow test in accordance with the applicable provisions of the ASTM C1437-07 test method; the flow expressed as a percentage of the original base diameter after five drops of the flow table in 3 seconds.

**fluid grout**—a cementitious grout consistency with a time of efflux of 10 to 30 seconds when tested by the flow cone procedure of the ASTM C939-10 test method.

**grout shoulder**—the portion of the grout that extends beyond the base plate toward the edge of the concrete foundation.

**plastic grout**—a cementitious grout consistency with a flow of 100 to 125 by the flow test in accordance with the applicable provisions of ASTM C1437-07 test method; the flow calculated after five drops of the flow table in 3 seconds.

**working time**—time in which the grout can be placed without having a detrimental effect on the strength and serviceability of the grout.

**CHAPTER 3—GROUT****3.1—Requirements**

After placement and hardening in the space between a machine or equipment base and the foundation, the grout is expected to perform one of the following functions:

- Permanently maintain the original level and alignment of the machinery or equipment and transfer all loads to the foundation when shims and other temporary positioning devices are removed.
- Act together with shims or other alignment devices in the transfer of loads to the foundation.
- Provide only stability support or corrosion protection for shims or other alignment devices that are designed to transfer all loads to the foundation.

The most important requirement for a grout intended to transfer loads to the foundation is the volume-change characteristics that result in complete and permanent filling of the space. Plain grouts consisting of cement, aggregate, and water do not have these characteristics. Other properties of the grout, such as consistency, strength, chemical resistance, temperature resistance, and compatibility with the operating environment are also important. These properties, however, are obtained more easily than the necessary volume-change characteristics.

For most applications, the space between the foundation and the machinery or equipment base can best be filled by placing a flowable grout into the space. To maintain