

**Guide to Design, Manufacture,  
and Installation of Concrete Piles**

Reported by ACI Committee 543



**American Concrete Institute®**



First Printing  
March 2012

American Concrete Institute®  
*Advancing concrete knowledge*

## **Guide to Design, Manufacture, and Installation of Concrete Piles**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at [www.concrete.org/committees/errata.asp](http://www.concrete.org/committees/errata.asp). Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

**Order information:** ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**U.S.A.**  
**Phone: 248-848-3700**  
**Fax: 248-848-3701**

[www.concrete.org](http://www.concrete.org)

# Guide to Design, Manufacture, and Installation of Concrete Piles

Reported by ACI Committee 543

William L. Gamble, Chair  
Roy M. Armstrong\*  
Robert N. Bruce Jr.  
William Ciggelakis  
M. T. Davisson  
Rudolph P. Frizzi  
Jorge L. Fuentes  
John S. Karpinski  
John B. Kelly

Viswanath Krishna Kumar  
Hugh S. Lacy  
Stanley Merjan  
Clifford R. Ohlwiler  
Chad A. Saunders  
John A. Tanner  
Edward J. Ulrich  
\*Deceased.

*Consulting members*

Ernest V. Acree Jr.

Jose I. Restrepo

Special acknowledgment to Rudolph P. Frizzi for his contribution to this report.

*This report presents recommendations to assist the design architect/engineer, manufacturer, construction engineer, and contractor in the design, manufacture, and installation of most types of concrete piles.*

**Keywords:** augered piles; bearing capacity; composite construction; concrete piles; corrosion; drilled piles; foundations; harbor structures; loads; prestressed concrete; quality control; steel reinforcement; soil mechanics; storage; tolerances.

## CONTENTS

### Chapter 1—Introduction, p. 2

- 1.1—General
- 1.2—Types of piles
- 1.3—Design considerations

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

### Chapter 2—Notation and definitions, p. 5

- 2.1—Notation
- 2.2—Definitions

### Chapter 3—Geotechnical design considerations, p. 5

- 3.1—General
- 3.2—Subsurface conditions
- 3.3—Bearing capacity of individual piles
- 3.4—Settlement
- 3.5—Group action in compression
- 3.6—Pile spacing
- 3.7—Lateral support
- 3.8—Batter piles
- 3.9—Axial load distribution
- 3.10—Long-term performance
- 3.11—Lateral capacity
- 3.12—Uplift capacity

### Chapter 4—Structural design considerations, p. 16

- 4.1—General
- 4.2—Loads and stresses to be resisted

ACI 543R-12 supersedes ACI 543R-00 and was adopted and published March 2012. Copyright © 2012, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 4.3—Structural strength design and allowable service capacities
- 4.4—Installation and service conditions affecting design
- 4.5—Other design and specification considerations

### **Chapter 5—Seismic design and detailing considerations, p. 27**

- 5.1—Introduction
- 5.2—General seismic impacts on pile behavior
- 5.3—Seismic pile behavior
- 5.4—Geotechnical and structural design considerations
- 5.5—Seismic detailing of concrete piles
- 5.6—Vertical accelerations

### **Chapter 6—Materials, p. 35**

- 6.1—Concrete
- 6.2—Grout
- 6.3—Reinforcement and prestressing materials
- 6.4—Steel casing
- 6.5—Structural steel cores and stubs
- 6.6—Splices

### **Chapter 7—Manufacture of precast concrete piles, p. 39**

- 7.1—General
- 7.2—Forms
- 7.3—Placement of steel reinforcement
- 7.4—Embedded items
- 7.5—Mixing, transporting, placing, and curing concrete
- 7.6—Pile manufacturing
- 7.7—Handling and storage

### **Chapter 8—Installation of concrete piles, p. 43**

- 8.1—Purpose and scope
- 8.2—Installation equipment, techniques, and methods
- 8.3—Prevention of damage to piling during installation
- 8.4—Handling and positioning during installation
- 8.5—Reinforcing steel and steel core placement
- 8.6—Concrete placement for CIP and CIS piles
- 8.7—Pile details
- 8.8—Extraction of concrete piles
- 8.9—Concrete sheet piles

### **Chapter 9—References, p. 57**

- 9.1—Referenced standards and reports
- 9.2—Cited references

## **CHAPTER 1—INTRODUCTION**

### **1.1—General**

Piles are slender structural elements installed in the ground to support a load or compact the soil. They are made of several materials or combinations of materials and are installed by impact driving, jacking, vibrating, jetting, drilling, grouting, or combinations of these techniques. Piles are difficult to summarize and classify because there are many types, and new types are still being developed. This report covers only the types of piles currently used in North American construction projects. A pile type can be assigned

a wide variety of names or classifications by various agencies, codes, technical groups, and in various geographical regions. No attempt is made herein to reconcile the wide variety of names used with a given pile type.

Piles can be described by the predominant material from which they are made: steel, concrete (or cement and other materials), or timber. Composite piles have an upper section of one material and a lower section of another. Piles made entirely of steel are usually H-sections or unfilled pipe; however, other steel members can be used. Timber piles are typically tree trunks that are peeled, sorted to size, and driven into place. The timber is usually treated with preservatives, but untreated piles can be used when positioned entirely below the permanent water table. The design of steel and timber piles is not considered herein except when used in conjunction with concrete. Most of the remaining types of existing piles contain concrete or a cement-based material.

Driven piles are typically top-driven with an impact hammer activated by air, steam, hydraulic, or diesel mechanisms, although vibratory drivers are occasionally used. Some piles, such as steel corrugated shells and thin-wall pipe piles, would be destroyed if top-driven. For such piles, an internal steel mandrel is inserted into the pile to receive the blows of the hammer and support the shell during installation. The pile is driven into the ground with the mandrel, which is then withdrawn. Driven piles tend to compact the soil beneath the pile tip.

Several types of piles are installed by drilling or rotating with downward pressure, instead of driving. Drilled piles usually involve concrete or grout placement in direct contact with the soil, which can produce side-friction resistance greater than that observed for driven piles. On the other hand, because they are drilled rather than driven, drilled piles do not compact the soil beneath the pile tip and, in fact, can loosen the soil at the tip. Post-grouting may be used after installation to densify the soil under the pile tip.

Concrete piles are classified according to the condition under which the concrete is cast. Some concrete piles (precast piles) are cast in a plant before driving, which allows controlled inspection of all phases of manufacture. Other piles are cast-in-place (CIP), a term used in this report to designate piles made of concrete placed into a previously-driven, enclosed container. Concrete-filled corrugated shells and closed-end pipe are examples of CIP piles. Other piles are cast-in-situ (CIS), a term used in this report to designate concrete cast directly against the earth. Drilled piers and auger-grout piles are examples of CIS piles.

### **1.2—Types of piles**

**1.2.1 Precast concrete piles**—This general classification covers both conventionally reinforced concrete piles and prestressed concrete piles. Both types can be formed by casting, spinning (centrifugal casting), slipforming, or extrusion and are made in various cross-sectional shapes, such as triangular, square, octagonal, and round. Some piles are cast with a hollow core. Precast piles usually have a uniform cross section but can have a tapered tip. Precast concrete piles are designed and manufactured to withstand handling and driving stresses in addition to service loads.