

Standard Test Method

Testing of Catalyzed Titanium Anodes for Use in Soils or Natural Waters

This NACE International standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing, purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this NACE standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. NACE assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official NACE interpretations issued by NACE in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this NACE standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This NACE standard may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this NACE standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: NACE standards are subject to periodic review, and may be revised or withdrawn at any time in accordance with NACE technical committee procedures. NACE requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of NACE standards may receive current information on all standards and other NACE publications by contacting the NACE FirstService Department, 1440 South Creek Dr., Houston, TX 77084-4906 (telephone +1 281-228-6200).

Revised 2012-06-22
Approved 2008-03-15
NACE International
1440 South Creek Drive
Houston, Texas 77084-4906
+1 281-228-6200

ISBN 1-57590-216-8
© 2012, NACE International

Foreword

This NACE International standard has been prepared to provide users and manufacturers of impressed current cathodic protection (CP) anodes with a test method for evaluating the anode's ability to achieve an expected lifetime. It is applicable to catalyzed titanium anodes intended for use in underground or underwater environments.

This test method is intended to evaluate whether such anode complies with required specifications of design life expectancy at rated current output. This is not a quality assurance (QA) test, but rather a test method that may be used to develop a QA test.

The appendixes of this test method are provided for guidance and as a supplement to the test method. They outline the logic for developing a QA test based on this test method.

This standard was originally prepared in 2008 by NACE Task Group (TG) 017, "Anodes, Catalyzed Titanium: Testing for Use in Soils and in Waters," and it was revised by TG 017 in 2012. TG 017 is administered by Specific Technology Group (STG) 05 on Cathodic/Anodic Protection. This standard is issued by NACE under the auspices of STG 05.

In NACE standards, the terms *shall*, *must*, *should*, and *may* are used in accordance with the definitions of these terms in the *NACE Publications Style Manual*. The terms *shall* and *must* are used to state a requirement, and are considered mandatory. The term *should* is used to state something good and is recommended, but is not considered mandatory. The term *may* is used to state something considered optional.

**NACE International
Standard Test Method**

**Testing of Catalyzed Titanium Anodes for Use in Soils
or Natural Waters**

Contents

1. General	1
2. Definitions	1
3. Test Apparatus	1
4. Test Electrolyte	3
5. Test Procedure	4
6. Test Completion.....	4
7. Reporting Test Results	5
Appendix A: Discussion	5
Appendix B: Development of a Correlation Curve	6
Appendix C: Development of Acceptance Criterion	7
FIGURES:	
Figure 1: Test Cell with Anode Measurement Setup.....	2
Figure 2: Test Cells in Series.....	3
Figure B1: Correlation Chart of Test Data.....	6
Figure C1: Design Requirements—Correlation Chart of Test Data	8
Figure C2: Sample Test Result Evaluation Using Correlation Chart	9

Section 1: General

1.1 Test Method for Catalyzed Titanium

This test method is for anodes comprised of a titanium substrate to which a mixed metal oxide (MMO) catalytic coating has been applied. This test method accelerates the time-to-failure by operating the anode at higher current than the application's design requirements.

1.2 The user should not imply that this test method is mandatory for any application of these anode materials.

1.3 Alternatively, the user may elect to use the manufacturer's rating instead of developing the test methodology independently.

1.4 Limitations

1.4.1 Accelerated testing should provide conservative results by stressing the anode more severely than normal applications. See Appendix A (Nonmandatory) for further discussion.

1.4.2 All manufacturers' products may not perform identically. Comparing test samples to a correlation curve established for a different manufacturer's product may lead to erroneous results.

1.4.3 The result for a sample run in the accelerated life test may be used to validate its performance at the design current density only if the correlation curve has been established for that material. See Appendix B (Nonmandatory) for development of the correlation curve using this test method.

1.4.3 This test method is not an acceptance criterion. It may be used to develop a test criterion as shown in Appendix C (Nonmandatory).

1.4.4 This test method outlines the test conditions that must be maintained for effective comparisons.

1.4.5 Varying the test conditions may have a significant effect on the sample lifetime, leading to erroneous results.

1.4.6 The test method as described in this standard should not be interpreted as being the only correct test method that may be used.

Section 2: Definitions

Mixed Metal Oxide (MMO): A mixture of a platinum group metal (Pt, Ir, Ru) oxide and a valve metal (Ti, Ta, Nb, Zr) oxide. The most common mixture used for cathodic protection is iridium oxide and tantalum oxide. Exact compositions may vary.

Section 3: Test Apparatus

3.1 The test equipment is comprised of an anode (test sample), a cathode, a thermometer, a glass vessel, electrolyte agitation device (e.g., magnetic stirrer), rubber stopper for tall glass beaker, a funnel for deionized water addition during the test, vent tubing, and power supply. See Figure 1.