

ACI 548.11R-12

**Guide for the Application of
Epoxy and Latex Adhesives for
Bonding Freshly Mixed and
Hardened Concretes**

Reported by ACI Committee 548



American Concrete Institute®



First Printing
September 2012

American Concrete Institute®
Advancing concrete knowledge

Guide for the Application of Epoxy and Latex Adhesives for Bonding Freshly Mixed and Hardened Concretes

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at www.concrete.org/committees/errata.asp. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
U.S.A.
Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN 978-0-87031-774-3

Guide for the Application of Epoxy and Latex Adhesives for Bonding Freshly Mixed and Hardened Concretes

Reported by ACI Committee 548

Bradley Nemunaitis, *Chair*

Mahmoud M. Reda Taha, *Secretary*

Ashraf I. Ahmed
Mohammad A. Alhassan
Milton D. Anderson
Jacques A. Bertrand
Constantin Bodea
Timothy Bower
David W. Fowler
Robert W. Gaul
Quentin L. Hibben
Albert O. Kaeding
John R. Milliron
Myles A. Murray
Joseph A. Nuciforo, Jr.
John R. Robinson

Donald A. Schmidt
Raymond J. Schutz
Qizhong Sheng
Joe Solomon
Michael M. Sprinkel
Michael S. Stenko
Donald P. Tragianese
Wafeek S. Wahby
David White
David P. Whitney
Richard E. Wollmershauser

Consulting Members
Lu Anqi

Craig A. Ballinger
John J. Bartholomew
Shashi P. Bhatnagar
Zhi-Yuan Chen
Inz Lech Czarniecki
Harold (Dan) R. Edwards
Larry J. Farrell
Jack J. Fontana
George Horeczko
David P. Hu
Bert Paul Kreikemans
Deon Kruger
William Lee
Troy D. Madeley

Henry N. Marsh, Jr.
Peter Mendis
Peter J. Moss
Yoshihiko Ohama
Kelly M. Page
Jerzy Pietrzykowski
Richard C. Prusinski
Hamid Saadatmanesh
Donald A. Schmidt
Meyer Steinberg
Harold H. Weber, Jr.

This guide provides information, requirements, and procedures for bonding freshly mixed and hardened concretes by using epoxy or latex adhesives. This guide covers evaluation of hardened concrete, selection of suitable epoxy or latex adhesive and application methods.

Keywords: adhesives; bonding; epoxy adhesives; evaluation; latex adhesive; preparation.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

Chapter 1—Scope, p. 2

Chapter 2—Definitions, p. 2

Chapter 3—Hardened concrete evaluation, p. 2

Chapter 4—Removal of unsound concrete, p. 2

Chapter 5—Surface preparation, p. 2

Chapter 6—Use of epoxy adhesives, p. 3

6.1—Selection of epoxy adhesive

6.2—Mixing of epoxy adhesive

6.3—Application of epoxy adhesive

ACI 548.11R-12 supersedes ACI 503.6R-97(03) and became effective September 6, 2012.

Copyright © 2012, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

Chapter 7—Use of latex adhesives, p. 3

7.1—Selection of latex adhesive

7.2—Application of latex adhesive

Chapter 8—References, p. 4**CHAPTER 1—SCOPE**

This guide provides information, requirements, and procedures for bonding freshly mixed and hardened concretes by using epoxy or latex adhesives. This information will be of particular use to contractors.

This guide consists of:

- a) Evaluation of hardened concrete to determine proper preparation and surface conditioning before application of adhesives
- b) Selection of suitable epoxy or latex adhesive depending on the expected performance and environmental conditions (ACI 503.5R)
- c) Application methods

CHAPTER 2—DEFINITIONS**2.1—Definitions**

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <http://terminology.concrete.org>.

CHAPTER 3—HARDENED CONCRETE EVALUATION

Contaminated and deteriorated concrete can be detected by visual inspection; however, in many cases, visual determination of the soundness of the concrete is not sufficient to select the repair and preparation methods. It is necessary to determine the extent and cause of deterioration, and if that cause is active. For guidance on surveys for these determinations, refer to ACI 201.1R, ACI 364.1R, and ASTM C823/C823M.

Methods common for evaluating and determining concrete condition include sounding with a hammer or chain drag, ultrasonic pulse velocity, petrographic analysis, infrared thermography, radar detection, core evaluation, impact echo, measurement of chloride ion content, and bond tests as described in ACI 228.1R and ASTM C1583/C1583.

Proper preparation, as described in Chapter 5, of any concrete to receive an adhesive is of primary importance. Inadequate preparation may result in bond failure at the adhesive interface.

The surface conditions required for different types of adhesive are described in Chapters 4 and 5.

CHAPTER 4—REMOVAL OF UNSOUND CONCRETE

The removal of unsound or damaged concrete prior to placing an adhesive and before placement of the freshly mixed concrete is a necessary part of the rehabilitation of structures.

The first step involves saw cutting the periphery of the removal area to a depth of 1 in. (25 mm) or to a lesser depth

necessary to clear the reinforcing steel (VDOT 2007). This saw cutting delineates the repair area and reduces edge spalling and weakness introduced by outlining the area using other methods. Saw cutting also provides a shoulder against which the repair materials can be placed and finished, resulting in a neater appearance. The saw-cut line should be located outside of the determined limits of the defect to ensure that all defective concrete is removed and that the fresh material is bonded to sound concrete.

Several types of systems are available to remove unsound concrete.

- a) Scabblers or bush hammers are tools with several points that remove concrete by pulverizing or fracturing the surface
- b) Scarifiers have wheels with several points that are tipped with carbide, tungsten, or diamonds. This equipment removes concrete by scraping or impacting the surface
- c) Water blasting (hydrodemolition) removes concrete by projecting jets of potable water
- d) Jackhammers remove concrete by impacting the surface

CHAPTER 5—SURFACE PREPARATION

After the concrete has been removed by one or more of the aforementioned methods (USACE 1995), except for water blasting, all newly exposed surfaces should be abrasive blasted and washed thoroughly with a water jet that has a pressure of at least 1500 psi (10 MPa). The surface should then be dried with oil-free compressed air or vacuumed to remove any residual debris.

Surfaces or parts of surfaces not requiring removal of concrete should be cleaned to remove all surface contaminants detrimental to the bond of the adhesive. Such contaminants may include laitance, curing membranes, surface coatings, treatments, oil, grease, rust stains, and dust.

These methods are commonly used to remove contaminants

- a) Shot blasting, which projects metal balls of varying size at high velocity to impact and abrade the surface
- b) Abrasive blasting, which projects particles of varying size to impact and abrade the surface. The particles may be carried by air or water
- c) Scabbling, which uses bush hammers
- d) Scarification
- e) Water blasting

One or more of these methods may be required for preparation. For guidance, refer to ASTM D4258 and D4259 and ICRI No. 310.1R, No. 310.2R, and No. 310.3R.

Regardless of surface preparation method, the results should be such that the surface is abraded to expose the coarse aggregate in the surface with a maximum surface texture of 0.01 in. (0.254 mm) measured in accordance with ASTM E965. Heavier textures require the use of excessive adhesive.

To determine if surface preparation is adequate for bonding, test for pulloff strength in accordance with ASTM C1583/C1583. If 250 psi (1.7 MPa) is achieved, then the surface preparation and concrete quality is adequate. If the pullout value is less than 250 psi (1.7 MPa) and 50 percent or more of the failure area is in the concrete at a depth of 0.236 in. (6 mm) or greater, then the surface preparation