

ACI 310R-13

Guide to Decorative Concrete

Reported by ACI Committee 310



American Concrete Institute®



First Printing
December 2013

American Concrete Institute®
Advancing concrete knowledge

Guide to Decorative Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at www.concrete.org/committees/errata.asp. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
U.S.A.
Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN: 978-0-87031-853-5

Guide to Decorative Concrete

Reported by ACI Committee 310

Larry Rowland, Chair

Lance Boyer
Clark Branum
Walter B. Burns
Terry C. Collins
Daniel P. Dorfmueller
James A. Farny
Roy E. Harvey

David E. Hoyt
Allyn C. Luke
Scott C. Metzger
Michael E. Murray
Dionne Ojeda
Joe A. Reardon
Todd A. Scharich

Michael S. Smith
Nicholas J. Sorrentino
Cori E. Sutton
James Vermillion

Consulting members
Doug Bannister

Larry E. Good
Robert P. Harris
Harry P. Moats
Joseph V. Nasvik
Frank Piccolo

ACI Committee 310 wishes to extend special acknowledgements to the following individuals for their contribution to the development of this guide: M. S. Smith, N. Blackburn, J. Strieder, and A. Werner.

This guide describes techniques for imparting aesthetic finishes to concrete flatwork, of which many can be combined for unique effects. The designer/engineer will acquire detailed, practical guidance for achieving aesthetic effects using proven techniques. Recommendations are made for the production of cast-in-place decorative concrete flatwork, decorative stains, and overlays. In addition to attention to the specified materials, mixture designs, concrete placement, curing, protection, sealing, and other treatments, this guide also considers the effects of these treatments on the overall aesthetics of the facility.

Keywords: aggregates; cementitious materials; decorative overlays; dry-shake hardeners; dry-shake release agents; embedment; embossing; engraving; etching; flatwork; imprinting; inlays; pavements; polishing; sealants; stains; stamping; tooling.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3

CHAPTER 2—DEFINITIONS, p. 3

CHAPTER 3—GENERAL AND DESIGN CONSIDERATIONS, p. 4

- 3.1—General, p. 4
- 3.2—Process development, p. 4
- 3.3—Substrate preparation, p. 5
- 3.4—Jointing, p. 5
- 3.5—Joint filling, p. 6
- 3.6—Proper installation and quality control, p. 6
- 3.7—Climate, p. 7
- 3.8—Curing, p. 7
- 3.9—Sealers, p. 8
- 3.10—Safety, p. 10
- 3.11—Reinforcement, p. 10
- 3.12—Sustainability, p. 10

CHAPTER 4—PLASTIC CONCRETE COLOR TECHNIQUES, p. 10

- 4.1—General, p. 10
- 4.2—Integral color, p. 10
- 4.3—Color shake-on hardeners, p. 12
- 4.4—Exposed aggregate, p. 13
- 4.5—Advantages, p. 15
- 4.6—Disadvantages, p. 15
- 4.7—Special procedures and tools, p. 15
- 4.8—Required products, p. 15
- 4.9—Safety, p. 15
- 4.10—Maintenance, p. 15

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 310R-13 was adopted and published December 2013.
Copyright © 2013, American Concrete Institute

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 5—PLASTIC CONCRETE TEXTURING AND PATTERNING TECHNIQUES, p. 15

- 5.1—Texturing: embossing, imprinting, stenciling, and stamping, p. 15
- 5.2—Stamping, p. 17
- 5.3—Texture and pattern rollers, p. 17
- 5.4—Stencils (paper templates), p. 19
- 5.5—Object impressing, p. 20
- 5.6—Texturing with standard tooling, p. 20

CHAPTER 6—POST-PLACEMENT COLORING TECHNIQUES, p. 21

- 6.1—General, p. 21
- 6.2—Reactive stains, p. 24
- 6.3—Concrete dyes, p. 28
- 6.4—Acid etching, p. 28

CHAPTER 7—POST-PLACEMENT TEXTURING AND PATTERNING TECHNIQUES, p. 29

- 7.1—General, p. 29
- 7.2—Ground and polished concrete, p. 30
- 7.3—Sandblast stenciling (abrasive blast stenciling), p. 37
- 7.4—Engraved concrete, p. 39
- 7.5—Decorative saw-cutting (scoring), p. 40

CHAPTER 8—DECORATIVE OVERLAYS AND REPAIR METHODS, p. 41

- 8.1—General, p. 41
- 8.2—Special procedures and tools, p. 42
- 8.3—Required products, p. 43
- 8.4—Application, p. 43
- 8.5—Touch-ups and post-repair aesthetic treatments, p. 44

CHAPTER 9—MAINTENANCE, p. 44

- 9.1—General, p. 44
- 9.2—Coatings and sealers, p. 44
- 9.3—Stained concrete, p. 44
- 9.4—Color hardened and densified concrete, p. 44
- 9.5—Maintenance plan and closeout documentation, p. 45

CHAPTER 10—REFERENCES, p. 45

- Cited references, p. 45

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

Decorative concrete has been in existence since approximately 70 AD, when concrete was used for defining affluent or important areas of living space in communal cultures. Early examples of this type of adornment are the streets and paving throughout the city of Pompeii near Naples, Italy. Early decorative concrete used colored aggregates and varying shapes or natural materials embedded in concrete paving.

Traditionally, concrete has been specified more for its functional characteristics than as an enhancement to the aesthetics of the structure. Landscape architects were leaders in using concrete flatwork to enhance the visual appeal of hardscapes. Using color and texture introduced concrete as a



Fig. 1.1a—Stamped, colored concrete with slate and brick patterns in landscape setting (courtesy of Decorative Concrete Resources).



Fig. 1.1b—Concrete slab enhances design aesthetic with mimic of stone slab (courtesy of L. M. Scofield Company).

landscape feature in addition to its functionality. An example is flatwork textured and colored to replicate the look of slate, brick, or natural stone as shown in Fig. 1.1a and 1.1b.

The use of decorative concrete has been well received and considered as an alternative to other building materials for durable, versatile, and economical finishes. More designers are creating greater aesthetic appeal in projects by using one or more combinations of special concrete placement techniques including integral concrete colors, color hardeners, chemical stains, pigments and dyes, surface texturing, jointing, exposed aggregate, surface embossing, polishing,



Fig. 1.2—Cast-in-place decorative concrete combining treatments during and post placement to achieve aesthetic effects (courtesy of Concrete Mystique Engraving).

and the use of sealants and coatings. The combinations of techniques and mediums described in this guide are exclusive; they cannot be replicated by any other durable medium.

1.2—Scope

This guide describes several techniques for imparting aesthetic finishes to concrete, many of which can be combined for unique effects (Fig. 1.2). The guide provides detailed practical guidance for achieving aesthetic effects using proven techniques, both within and beyond the context of ACI 302.1R, which also governs these concrete elements.

Recommendations for the production of cast-in-place decorative concrete, stains, and overlays are presented. In addition to attention to specified materials, mixture designs, concrete placement, curing, protection, sealing, and other treatments, consideration of the effects of these treatments on the overall aesthetics of the structure is also addressed.

CHAPTER 2—DEFINITIONS

“2013 ACI Concrete Terminology” provides a comprehensive list of definitions that are available online at: <http://terminology.concrete.org>. The definitions provided here complement that source.

acid (or chemical) stain—see **reactive stain**.

color hardener—similar to traditional one-component hardeners, having additional constituent materials formulated to color the concrete surface.

concrete dye—colorant for concrete that is applied to the concrete while it is in solution and results in a stained appearance; concrete dyes do not produce color via chemical reaction—they are usually a synthetic organic compound and can degrade when exposed to light or alkalinity.

crack chaser—rotary tool using a v-shaped diamond blade to enlarge cracks in concrete to facilitate repair. The v-shape of the blade assists the operator in following the curves of the crack so as to not cause unnecessary damage to the piece being prepared for repair.

decorative aggregate—specially selected aggregates chosen for their artistic contribution to the project; examples of materials used as decorative aggregate include colored stone, intrinsically valuable gathered stone, semiprecious stone, or colored glass.

decorative overlay—mixture of cementitious materials installed over an existing concrete substrate; they can be integrally colored, stenciled, or used for artistic enhancement post-placement.

densifier—combination of silicate and water-based compounds that react in the surface of the concrete to produce additional calcium silicate hydrate (C-S-H); silicates are combined with carrier compounds, most commonly sodium-, potassium-, or lithium-based to aid the process. Some products also contain silicate.

embossing—creating a raised print or reverse replication of an object in the concrete surface.

engraving—cutting with a mechanical rotary or impact tool to texture a concrete surface product.

etch—textured surface produced by cutting with a mechanical impact tool or by chemical etching by use of acid.

grinding—intentional removal of a visually apparent amount of surface without consideration of gloss.

integral color—pigment that changes the color of the paste portion of the concrete mixture to produce a color change throughout the hardened concrete matrix.

microtopping—bonded cementitious overlay usually 1/8 to 3/16 in. (3 to 5 mm) in thickness; when installed over an existing concrete substrate post-placement, it can be integrally colored, stenciled, or used for artistic enhancement.

needle scaler—reciprocal impact tool that uses single or multiple thin rods to strike a surface.

polished concrete—post-placement architectural finish or texturing technique where concrete undergoes sequential mechanical abrasion resulting in a glossy surface with clarity ranging from matte to high gloss, depending on which point in the sequence the abrasion is ended; does not achieve gloss solely by the use of surface coatings. The complete process commonly includes chemical densification for increased strength and reduction of absorption.

polished overlay—bonded cementitious overlay 3/8 to 1 in. (10 to 25 mm) in depth cast over an existing concrete substrate designed to accept diamond abrading for a polished concrete appearance.

reactive stain—reactive solution of one or more metal salts stabilized by acid that produces coloration in a concrete substrate by neutralization of acid followed by precipitation of metal hydroxides or oxides.

stain(v)—use of a chemical stain or a concrete dye to change the color of the concrete surface that can be a penetrant or a low build coating that does not appreciably change the concrete’s texture; some acid stains can etch the concrete’s surface and can alter the texture.

stamping—process of applying a surface pattern to decorative concrete by using impact pressure to emboss texture, patterns, or faux joints into the surface of plastic concrete; usually providing a pattern of simulated natural materials