

ACI 347.3R-13

**Guide to Formed Concrete
Surfaces**

Reported by ACI Committee 347



American Concrete Institute®



First Printing
January 2014

American Concrete Institute®
Advancing concrete knowledge

Guide to Formed Concrete Surfaces

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://www.concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised *ACI Manual of Concrete Practice* (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
U.S.A.
Phone: 248-848-3700
Fax: 248-848-3701

www.concrete.org

ISBN: 978-0-87031-863-4

Guide to Formed Concrete Surfaces

Reported by ACI Committee 347

Kenneth L. Berndt, Chair

Rodney D. Adams
Mary Bordner-Tanck
George Charitou
James N. Cornell II
Jack L. David
William A. Dortch Jr.
Jeffrey C. Erson
Noel J. Gardner

William A. Giorgi
Timothy P. Hayes
Gardner P. Horst
David W. Johnston
Roger S. Johnston
Robert G. Kent
Kevin R. Koogle
H. S. Lew

Robert G. McCracken
Eric S. Peterson
William R. Phillips
Douglas J. Schoonover
Aviad Shapira
John M. Simpson
Rolf A. Spahr*
Pericles C. Stivaros

Daniel B. Toon
Ralph H. Tulis
Consulting members
Samuel A. Greenberg
R. Kirk Gregory
Donald M. Marks

*Principal author

The primary goal of the construction team is to produce as-cast concrete surfaces that meet project specifications and expectations. Although various descriptions, interpretations, and methods exist to achieve an as-cast concrete surface, no unified definitions of different concrete surfaces exist.

This document defines four quality levels of formed concrete surfaces and provides methods to achieve and evaluate them. These quality levels are identified by three surface finish categories: 1) form facing; 2) concrete surface void ratio; and 3) characteristics of form-facing materials. The basic procedures for classification are defined using tables derived from recommendations of the German Concrete Association (DBV) (Merkblatt Sichtbeton Deutscher Beton- und Bautechnik-Verein e.V. 2004).

This guide assists the project owner, design team, contractor, formwork and concrete suppliers, and all other parties in reaching a more specific understanding of how to produce a more clearly defined as-cast concrete surface. All other parties should understand the procedures, processes, and costs for producing defined surfaces of formed concrete. The guide also discusses all phases of construction relating to concrete surfaces from planning, description of work, and construction through acceptance of a concrete surface.

This guide can be used by both specifier (architect/licensed design professional) and contractor as a supplemental tool for defining, specifying, and evaluating concrete surfaces and offers guidance to the development of concrete surface specifications and expecta-

tions. Please refer to ACI 303R-12 for information regarding post-construction treatment of formed concrete surfaces.

This guide also describes an entire process for comprehensive use, including the creation of a concrete surface team and its defined roles and responsibilities in the construction process.

Keywords: color uniformity; exposed to view; form facing; job-built formwork; mockup; offsets; panelized formwork; reference area; surface finish; surface void ratio; texture; tolerances.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 2

CHAPTER 2—DEFINITIONS, p. 2

CHAPTER 3—FORMED CONCRETE SURFACE DESCRIPTIONS, p. 2

3.1—General, p. 2

3.2—Examples and determination of surface void ratio, p. 5

CHAPTER 4—BASICS OF LAYOUT AND DESIGN, p. 7

4.1—General, p. 7

4.2—Design and construction recommendations, p. 7

4.3—Planning and detailing, p. 8

4.4—Formwork and facing selection, p. 9

4.5—Premanufactured panelized formwork, p. 11

4.6—Job-built formwork, p. 11

4.7—Design with form liners, p. 14

4.8—Post-construction treated concrete surfaces, p. 14

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 347.3R-13 was adopted and published January 2014.

Copyright © 2014, American Concrete Institute

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 5—SPECIFICATIONS, p. 14

- 5.1—General description, p. 14
- 5.2—Design features, p. 14
- 5.3—Surface finish limitations, p. 14

CHAPTER 6—CONSTRUCTION, p. 15

- 6.1—Formwork, p. 15
- 6.2—Reinforcement and inserts, p. 15
- 6.3—Concrete mixture, p. 15
- 6.4—Concrete placement, p. 16
- 6.5—Concrete surface team, p. 16

CHAPTER 7—EVALUATION OF FORMED CONCRETE SURFACES, p. 16

- 7.1—Basics, p. 16
- 7.2—Overall impression, p. 16
- 7.3—Procedure in case of deviations, p. 16

CHAPTER 8—REFERENCES, p. 17

Authored references, p. 17

CHAPTER 1—INTRODUCTION

The scope of this guide is to solve a lack of uniformity in the appearance criteria of concrete surfaces, provide definitions for the various levels of formed concrete surfaces, and give objective evaluations of them.

Although there are various reference sources for constructing and evaluating concrete surfaces, none exist that offer a comprehensive guidance and understanding to its production and evaluation. Several ACI and ASCC documents, however, do provide partial guidance:

1) ACI 347-04 provides terms for classes of formed concrete surfaces, discusses irregularities in formed surfaces, and gives general guidance for the use of formwork for concrete;

2) ACI 309R-05 provides terms about visible effects of consolidation on formed concrete surfaces, why they occur, and how to avoid them;

3) ACI 303R-12 discusses architectural concrete, applications, and details of production including formwork, release agents, repair, and economics;

4) ACI 301-10 specifies concrete surfaces (Section 5.3.3.3);

5) The ASCC Education and Training Committee (1999) guide uses samples of concrete surfaces to illustrate appearance expectations.

These references, which exclude uniform appearance criteria or a process for evaluating formed concrete surfaces, make it difficult to achieve a wide range of expectations.

The ultimate authority on a project is the contract document. The contract document is a guide for the:

- a) Designer to specify the desired surface finish;
- b) Owner to understand what the final product will approximately look like;
- c) Contractor to select facing materials, concrete mixture, release agents, and construction methods to achieve the specified surface finish.

CHAPTER 2—DEFINITIONS

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <http://www.concrete.org/Tools/ConcreteTerminology.aspx>. Definitions provided herein complement that source.

area exposed to view—portion of structure that can be observed by the public during normal use.

blushing—slight pink or rose color on concrete surface.

flatness—deviation of a surface from a plane.

form facing—the form material that comes in direct contact with the concrete.

gap—space between abutting edges of the form-facing materials measured on the plane of the form surface.

mockup—a sample of a component of the building as specified in the contract documents that is used to establish the expected surface finish.

reference area—a significantly large area of a completed concrete surface serving as a basis of comparison for the acceptance of a surface category of work at a specified location of a given project.

surface void ratio—the ratio of the total surface void area to the total concrete surface area after stripping with no subsequent surface treatment.

CHAPTER 3—FORMED CONCRETE SURFACE DESCRIPTIONS**3.1—General**

Tables 3.1a through 3.1d define the various measurable properties pertaining to formed concrete surface texture, surface void ratio, color, flatness, and joints. Four concrete surface categories (CSCs) are defined in Table 3.1a. CSC1 has the lowest classifications and CSC4 the highest for a finished surface. The individual constituents used to define each CSC are further described in Table 3.1b. The classification for form-facing materials is described in Table 3.1c. The surface void ratio is defined and categorized according to net pore area in Table 3.1d.

Concrete surface levels are specified for individual parts of the structure to reflect the owner’s needs, desires, and budget. Possible examples include:

- a) Basement walls: CSC1;
- b) Industrial structures: CSC1 or CSC2;
- c) Electrical and mechanical rooms: CSC1 or CSC2;
- d) Stairwells: CSC1, CSC2, or CSC3;
- e) Commercial building exteriors: CSC3;
- f) High-end commercial building exteriors: CSC3 or CSC4;
- g) Religious structures or museums: CSC3 or CSC4;
- h) Monumental or landmark structures: CSC4.

These examples are only provided to illustrate the various classifications of concrete surfaces and are not recommendations of the committee.

Concrete surface finish schedules should be designated as part of the contract documents in drawings or by designations on exterior/interior views of the structure.