

ACI 213R-14

Guide for Structural Lightweight-Aggregate Concrete

Reported by ACI Committee 213



American Concrete Institute
Always advancing



Guide for Structural Lightweight-Aggregate Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Guide for Structural Lightweight-Aggregate Concrete

Reported by ACI Committee 213

Jiri G. Grygar*, Chair

Mauricio Lopez*, Secretary

David J. Akers
Theodore W. Bremner
Michael A. Caldarone
David A. Crocker
Per Fidjestol
Dean M. Golden
Ralph D. Gruber
Thomas A. Holm*

Bruce W. Jones
Edward S. Kluckowski
Mervyn J. Kowalsky
Ronald L. Kozikowski
Michael L. Leming
Keith A. McCabe
Fred Meyer*
Avi A. Mor

Dipak T. Parekh
Bruce W. Ramme
John. P. Ries*
G. Michael Robinson*
Jeffrey F. Speck
Jody R. Wall
William H. Wolfe
Shelley Wright

Min-Hong Zhang

Consulting Members
Tor Arne Hammer
W. Calvin McCall
William X. Sypher†
Alexander M. Vaysburd

*Members of the Task group who prepared the update of this guide.

†Deceased.

Special thanks to the following associate members for their contribution to the revision of this document: Reid W. Castrodale, and W. Jason Weiss. The committee would also like to thank the late William X. Sypher for his contribution to revision of the guide.

SYNOPSIS

The guide summarizes the present state of technology, presents and interprets the data on lightweight-aggregate concrete from many laboratory studies and the accumulated experience resulting from its successful use, and reviews performance of structural lightweight aggregate concrete in service.

This guide includes a definition of lightweight-aggregate concrete for structural purposes and discusses, in a condensed fashion, the production methods for and inherent properties of structural lightweight aggregates. Current practices for proportioning, mixing, transporting, and placing; properties of hardened concrete; and the design of structural concrete with reference to ACI 318 are all discussed.

Keywords: abrasion resistance; aggregate; bond; contact zone; durability; fire resistance; internal curing; lightweight aggregate; lightweight concrete; mixture proportion; shear; shrinkage; specified density concrete; strength; thermal conductivity.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

1.1—Introduction, p. 2

1.2—Scope, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 3

2.1—Notation, p. 3

2.2—Definitions, p. 4

CHAPTER 3—STRUCTURAL LIGHTWEIGHT AGGREGATES, p. 4

3.1—Internal structure of lightweight aggregates, p. 4

3.2—Production of lightweight aggregates, p. 4

3.3—Aggregate properties, p. 5

CHAPTER 4—SPECIFYING, PROPORTIONING, MIXING, AND HANDLING, p. 7

4.1—Scope, p. 7

4.2—Specifying lightweight concrete, p. 7

4.3—Materials, p. 7

4.4—Mixture proportioning criteria, p. 8

4.5—Proportioning and adjusting mixtures, p. 9

4.6—Aggregate preparation for mixing, p. 10

4.7—Placing and finishing, p. 10

4.8—Curing, p. 11

4.9—Laboratory and field control, p. 11

ACI 213R-14 supersedes ACI 213R-03 and was adopted and published in June 2014..

Copyright © 2014, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CHAPTER 5—PHYSICAL AND MECHANICAL PROPERTIES OF STRUCTURAL LIGHTWEIGHT AGGREGATE CONCRETE, p. 11

- 5.1—Scope, p. 11
- 5.2—Compressive strength, p. 11
- 5.3—Density of lightweight concrete, p. 12
- 5.4—Tensile strength, p. 12
- 5.5—Modulus of elasticity, p. 14
- 5.6—Poisson's ratio, p. 14
- 5.7—Ultimate strain, p. 14
- 5.8—Creep, p. 15
- 5.9—Shrinkage, p. 15
- 5.10—Bond strength, p. 16
- 5.11—Thermal expansion, p. 16
- 5.12—Heat flow properties, p. 17
- 5.13—Fire endurance, p. 18
- 5.14—Energy absorption and blast resistance, p. 19

CHAPTER 6—DURABILITY OF STRUCTURAL LIGHTWEIGHT-AGGREGATE CONCRETE, p. 20

- 6.1—General, p. 20
- 6.2—Absorption, p. 20
- 6.3—Contact zone / interface, p. 20
- 6.4—Resistance to corrosion, p. 22
- 6.5—Alkali-aggregate reaction, p. 24
- 6.6—Abrasion resistance, p. 24

CHAPTER 7—DESIGN OF STRUCTURAL LIGHTWEIGHT-AGGREGATE CONCRETE, p. 24

- 7.1—Scope, p. 24
- 7.2—General considerations, p. 24
- 7.3—Modulus of elasticity, p. 25
- 7.4—Tensile strength, p. 25
- 7.5—Shear and diagonal tension, p. 25
- 7.6—Development length, p. 26
- 7.7—Deflection, p. 27
- 7.8—Columns, p. 27
- 7.9—Prestressed lightweight concrete, p. 27
- 7.10—Thermal design considerations, p. 28
- 7.11—Seismic design, p. 28
- 7.12—Fatigue, p. 28

CHAPTER 8—PERFORMANCE AND APPLICATIONS OF LIGHTWEIGHT-AGGREGATE CONCRETE, p. 30

- 8.1—Scope and historical development, p. 30
- 8.2—Structural efficiency of lightweight concrete, p. 30
- 8.3—Applications of high-performance lightweight concrete, p. 30
- 8.4—Self-consolidating lightweight concrete, p. 34
- 8.5—Advantages of lightweight concrete, p. 35
- 8.6—Sustainability of lightweight concrete, p. 36

CHAPTER 9—ENHANCED PERFORMANCE DUE TO INTERNALLY STORED WATER (INTERNAL CURING), p. 36

- 9.1—Concept of internal curing, p. 36
- 9.2—Mixture proportioning for internal curing, p. 37

- 9.3—Properties of the aggregate for internal curing, p. 38
- 9.4—Influence of internal curing on concrete properties and behavior, p. 39
- 9.5—Field experience, p. 44
- 9.6—Internal curing summary and potential impact on sustainability, p. 45

CHAPTER 10—REFERENCES, p. 45

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

The objectives of this guide are to provide information and guidelines for designing and using lightweight concrete. By using such guidelines and construction practices, the structures can be designed and performance predicted with the same confidence and reliability as normalweight concrete and other building materials.

This guide covers the unique characteristics and performance of structural lightweight-aggregate (LWA) concrete. General historical information is provided along with detailed information on LWA and proportioning, mixing, and placing of concrete containing these aggregates. The physical properties of the structural LWA, along with design information and applications, are also included.

Structural lightweight concrete has many and varied applications, including multistory building frames and floors, curtain walls, shell roofs, folded plates, bridge decks and girders, prestressed or precast elements of all types, and marine structures. In many cases, the architectural expression of form, combined with functional design, is achieved more readily with structural lightweight concrete than with any other medium. Many architects, engineers, and contractors recognize the inherent economies and advantages offered by this material, as evidenced by the many impressive lightweight concrete structures found throughout the world.

Because much of the properties and performance of lightweight concrete are dependent on the type of LWA used, the ready mix supplier, LWA producer, or both, might be an important source of specific information for attaining the project objectives.

1.2—Scope

1.2.1 Historical background—The first known use of lightweight concrete dates back over 2000 years. There are several lightweight concrete structures in the Mediterranean region, but the three most notable structures were built during the early Roman Empire and include the Port of Cosa, the Pantheon Dome, and the Coliseum.

Built in approximately 273 BC, the Port of Cosa used lightweight concrete made from natural volcanic materials. These early builders learned that expanded aggregates were better suited for marine facilities than the locally available beach sand and gravel. They traveled 25 mi. (40 km) to the northeast to quarry volcanic aggregates at the Volcine complex for use in the harbor at Cosa (Bremner et al. 1994). This harbor on the west coast of Italy consists of a series of

four piers (~13 ft [4 m] cubes) extending into the sea. For two millennia the piers have withstood the forces of nature with only surface abrasion. They became obsolete only because of siltation of the harbor.

Built circa 126 AD, the Pantheon incorporates concrete varying in density from bottom to top of the dome. Roman engineers had sufficient confidence in lightweight concrete to build a dome with a diameter of 142 ft (43 m), which was not exceeded for almost two millennia. The structure is in excellent condition and is still being used today for spiritual purposes (Bremner et al. 1994).

The dome contains intricate recesses formed with wooden formwork to reduce the dead load and the imprint of the grain of the wood can still be seen. The excellent cast surfaces that are visible to the observer clearly show that these early builders had successfully mastered the art of casting concrete made with LWA. The Roman writer, architect, and engineer, Vitruvius, who took special interest in building construction, commented on several unusual features of the Pantheon. The fact that he did not single-out lightweight concrete for comment could imply that these early builders were fully familiar with this material (Morgan 1960).

Built in 75 to 80 AD, the Coliseum is a gigantic amphitheater with a seating capacity of 50,000 spectators. The foundations were cast with lightweight concrete using crushed volcanic lava. The walls were made using porous, crushed-brick aggregate. Vaults and spaces between the walls were constructed using porous-tufa cut stone.

1.2.2 Development of manufacturing process—After the fall of the Roman Empire, lightweight concrete use was limited until the 20th century when a new type of manufactured expanded shale LWA became available for commercial use.

The rotary kiln process was developed in 1918 and is used to produce expanded shale, clay, and slate. LWAs are manufactured by heating small particles of shale, clay, or slate in a rotary kiln. A particle size was discovered that, with limited crushing, produced an aggregate grading suitable for making lightweight concrete (Expanded Shale, Clay and Slate Institute 1971). When clay bricks are manufactured, it is important to heat the preformed clay slowly so that evolved gases have an opportunity to diffuse out of the clay. If they are heated too rapidly, a bloater is formed that does not meet the dimensional uniformity essential for a successfully fired brick. These rejected bricks were recognized by Hayde as an ideal material for making a special concrete. When reduced to appropriate aggregate size and grading, these bloated bricks could be used to produce a lightweight concrete with mechanical properties similar to regular concrete.

Commercial production of expanded slag (that is, expanded shale, clay, or slate) began in 1928, and in 1948, the first structural-quality sintered-shale LWA was produced using shale in eastern Pennsylvania.

One of the earliest uses of reinforced lightweight concrete was in the construction of ships and barges in the early 1900s. The U.S. Emergency Fleet Building Corporation found that

for concrete to be effective in ship construction, the concrete would need a maximum density of about 110 lb/ft³ (1760 kg/m³) and a compressive strength of approximately 4000 psi (28 MPa) (Expanded Shale, Clay, and Slate Institute 1960). Concrete was obtained with a compressive strength of approximately 5000 psi (34 MPa) and a unit weight of 110 lb/ft³ (1760 kg/m³) or less using rotary-kiln-produced expanded shale and clay aggregate.

1.2.3 Early modern uses—Considerable impetus was given to the development of lightweight concrete in the late 1940s when a survey was conducted on the potential use of lightweight concrete for home construction. This led to an extensive study of concrete made with LWAs. Sponsored by the Housing and Home Finance Agency (1949), parallel studies were conducted simultaneously in the laboratories of the National Bureau of Standards (Kluge et al. 1949) and the U.S. Bureau of Reclamation (Price and Cordon 1949) to determine properties of concrete made with a broad range of LWA types. These studies and earlier works focused attention on the potential structural use of some LWA concrete and initiated a renewed interest in lightweight members for building frames, bridge decks, and precast products in the early 1950s. Following the collapse of the original Tacoma Narrows Bridge in Washington, the replacement suspension structure design used lightweight concrete in the deck to incorporate additional roadway lanes without the necessity of replacing the original piers.

During the 1950s, many multistory structures were designed with lightweight concrete from the foundations up, taking advantage of reduced dead weight. Examples include the 42-story Prudential Life Building in Chicago, which used lightweight concrete floors, and the 18-story Statler Hilton Hotel in Dallas, designed with a lightweight concrete frame and flat plate floors.

These structural applications stimulated more concentrated research into the properties of lightweight concrete. In energy-related floating structures, such as an oil drilling rig, great efficiencies are achieved when a lightweight material is used. A reduction of 25 percent in mass in reinforced normalweight concrete will result in a 50 percent reduction in load when submerged. Because of this, the oil and gas industry recognized that lightweight concrete could be used to good advantage in its floating structures and structures built in a graving dock, and then floated to the production site and bottom-founded. To provide the technical data necessary to construct huge offshore concrete structures, a consortium of oil companies and contractors was formed to evaluate which LWA candidates were suitable for making high-strength lightweight concrete that would meet their design requirements. The evaluations began in the early 1980s with results available in 1992. As a result of this research, design information became readily available and has enabled lightweight concrete to be used for new and novel applications where high strength and high durability are desirable (Hoff 1992).