

ACI 232.3R-14

Report on High-Volume Fly Ash Concrete for Structural Applications

Reported by ACI Committee 232



American Concrete Institute
Always advancing



Report on High-Volume Fly Ash Concrete for Structural Applications

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Report on High-Volume Fly Ash Concrete for Structural Applications

Reported by ACI Committee 232

Karthik H. Obla*, Chair
Robert E. Neal, Vice Chair

Michael D. A. Thomas*, Vice Chair
Lawrence L. Sutter, Secretary

Thomas H. Adams
Gregory S. Barger
James C. Blankenship
Julie K. Buffenbarger
Ramon L. Carrasquillo
Barry A. Descheneaux
Jonathan E. Dongell
John M. Fox
Thomas M. Greene
Harvey H. Haynes†
James K. Hicks

R. Doug Hooton
Morris Huffman
James S. Jensen
Tilghman H. Keiper
Steven H. Kosmatka
Adrian Marc Nacamuli
Bruce W. Ramme*
Steve Ratchye*
Michael D. Serra
Ava Shypula
Boris Y. Stein

Oscar Tavares
Paul J. Tikalsky
Thomas J. Van Dam
Craig R. Wallace
Orville R. Werner II

G. Terry Harris, Sr.
Jan R. Prusinski
Harry C. Roof
Della M. Roy

Consulting Members
Mark A. Bury
James E. Cook
Dean M. Golden
William Halczak

*Task group member who participated in preparing this report.

†Lead task group member.

This report presents technical information to support the use of high-volume fly ash concrete for structural applications. The advantages and limitations of high-volume fly ash concrete are discussed, and the characteristics of the fresh and hardened materials and the durability of the material to various aggressive environments are covered. Field applications are presented along with sustainability features.

Keywords: alkali-silica reaction; compressive strength; corrosion of reinforcement; cracking; deicing salts; fly ash; heat of hydration; mixture proportions; modulus of elasticity; shrinkage; sulfate attack; sustainability; tensile strength.

CONTENTS

CHAPTER 1—GENERAL, p. 2

- 1.1—Introduction, p. 2
- 1.2—Significance, p. 2

- 1.3—Historical background, p. 2
- 1.4—Sustainability, p. 3
- 1.5—Classification of HVFA concrete, p. 4
- 1.6—Types of fly ash and portland cement, p. 4
- 1.7—Codes and specifications, p. 5
- 1.8—In-place strength, p. 5

CHAPTER 2—DEFINITIONS, p. 5

CHAPTER 3—CHARACTERISTICS OF FRESH HVFA CONCRETE, p. 5

- 3.1—Materials and mixture proportions, p. 5
- 3.2—Slump and workability, p. 6
- 3.3—Setting time, p. 6
- 3.4—Heat of hydration, p. 6
- 3.5—Plastic shrinkage cracks, p. 7

CHAPTER 4—CHARACTERISTICS OF HARDENED HVFA CONCRETE, p. 7

- 4.1—Compressive strength, p. 7
- 4.2—Tensile strength, p. 9
- 4.3—Modulus of elasticity, p. 9
- 4.4—Shrinkage and creep, p. 10

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 232.3R-14 was adopted and published October 2014.
Copyright © 2014, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 5—DURABILITY, p. 10

- 5.1—Cracking, p. 10
- 5.2—Permeability, p. 10
- 5.3—Alkali-silica reaction, p. 11
- 5.4—Sulfate attack, p. 11
- 5.5—Corrosion of reinforcing steel, p. 11
- 5.6—Freezing and thawing, p. 12
- 5.7—Deicing salts, p. 12
- 5.8—Physical salt attack, p. 13
- 5.9—Carbonation, p. 13

CHAPTER 6—FIELD APPLICATIONS, p. 13

- 6.1—General, p. 13
- 6.2—Placement and consolidation, p. 14
- 6.3—Finishing and curing, p. 14
- 6.4—Strength development and schedule, p. 14
- 6.5—Cold weather placement, p. 14
- 6.6—Hot weather placement, p. 15
- 6.7—100 percent Class C fly ash concrete, p. 15
- 6.8—Barriers to the use of HVFA concrete, p. 15

CHAPTER 7—HVFA CONCRETE AND SUSTAINABLE CONSTRUCTION, p. 15

- 7.1—Sustainability rating systems, p. 15

CHAPTER 8—REFERENCES, p. 16

- Authored documents, p. 16

CHAPTER 1—GENERAL**1.1—Introduction**

High-volume fly ash (HVFA) concrete is a sustainable construction material when proportioned properly and used in appropriate construction applications. This report summarizes published data on the composition and properties of the material, such as workability, strength, and durability. The report affirms the viability of HVFA concrete for structural applications and discusses construction issues.

HVFA concrete is defined as having a large replacement by mass of portland cement with fly ash. [Malhotra \(1986\)](#) defined HVFA concrete as concrete containing 50 percent or more fly ash by mass of total cementitious materials, and [Ramme and Tharaniyil \(2000\)](#) defined it as concrete with 37 percent or more fly ash by mass as total cementitious materials.

[Naik and Ramme \(1985\)](#) tested HVFA concrete using ASTM C618 Class C fly ash mixtures and having water-cementitious material ratios (w/cm) ranging from 0.42 to 0.57, without the use of high-range water-reducing admixtures. In 1986, however, a significant research program was initiated to explore the possibility of HVFA concrete attaining compressive strengths of 7250 psi (50 MPa) or higher for structural applications ([Malhotra 1986](#)). This research used concrete mixtures containing ASTM C618 Class F fly ash, 0.30 w/cm , and high-range water-reducing admixtures. The results of this work showed the potential of HVFA concrete as a sustainable material with workability, strength, and durability exceeding that of conventional port-

land-cement concrete having similar cementitious content. Summaries of the results on HVFA concrete using Class F fly ash are given by [Malhotra \(1992, 2002\)](#), [Bilodeau and Malhotra \(2000\)](#), and [Malhotra and Mehta \(2012\)](#).

Low-strength HVFA concrete mixtures are not covered herein. In this document, HVFA concretes that have minimum specified compressive strengths of 2500 psi (17 MPa) are discussed.

1.2—Significance

This report provides background information and technical data to support the use of HVFA concrete for structural applications. From a sustainability standpoint, HVFA concrete not only significantly reduces consumption of portland cement, but also results in a concrete of superior quality in many aspects when compared with that of conventional concrete in regard to workability, strength, and durability. In addition, this technology is currently available for wide-scale implementation and is backed by more than 25 years of field usage and test results.

1.3—Historical background

In 1937, [Davis et al. \(1937\)](#) experimented with concretes containing fly ash of up to 50 percent replacement by mass of portland cement. They concluded that the use of HVFA in mass concrete has definite advantages, such as lower temperature rise due to heat of hydration and less risk due to thermal cracking. These findings were applied in the first significant use of fly ash in concrete for Hungry Horse Dam in Montana, which was built from 1948-1952. In those early years, concretes using high levels of fly ash were limited to mass concrete structures. The incentive was to reduce the adiabatic temperature rise resulting from heat of hydration of portland cement. Compressive strengths were generally low at early ages with strengths increasing from 1450 to 2900 psi (10 to 20 MPa) at 90 days.

In the late 1970s, the use of fly ash at 60 to 70 percent by mass of cementitious material was found to significantly improve the performance of roller-compacted concrete ([Dunstan 1983](#)). The Upper Stillwater Dam in Utah was constructed using this material in early 1980. During a full-scale trial test of roller-compacted concrete in 1978, a slipformed vertical facing element was constructed using concrete containing approximately 40 percent fly ash by mass ([Dunstan 1983](#)). Subsequently, the first major placement of concrete containing over 50 percent fly ash replacement by mass of portland cement was in 1981, where the concrete was consolidated by immersion vibration for the construction of access roads at the Didcot Power Station in Oxfordshire, UK ([Dunstan 1983](#)). Success in this project led to use of the material in other applications between 1982 and 1984: foundation and retaining walls for an oil tank storage area (51 percent fly ash by mass), marine slipway (52 percent), sewage treatment works (54 percent), and concrete viaducts (35 to 65 percent). Five of these structures were evaluated by visual examination and testing of cores approximately 10 years after construction, and were found to be in excellent condition ([Dunstan et al. 1992](#)).