

An ACI/TMS Standard

Code Requirements for Determining Fire Resistance of Concrete and Masonry Construction Assemblies

Reported by ACI/TMS Committee 216



American Concrete Institute
Always advancing





This document is the intellectual property of ACI and the cosponsor, and both have copyright. All rights reserved. This material may not be reproduced or copied, in whole or in part, in any printed, mechanical, electronic, film, or other distribution and storage media, without written consent. ACI is the lead sponsor of this joint committee and its operating procedures were followed. ACI's information is below; the cosponsor's information is on the inside back cover of this document.

Code Requirements for Determining Fire Resistance of Concrete and Masonry Construction Assemblies

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Code Requirements for Determining Fire Resistance of Concrete and Masonry Construction Assemblies

An ACI and TMS Standard

Reported by ACI Committee 216 joint with TMS

Venkatesh Kumar R. Kodur, Chair

Charles B. Clark Jr.
Donald O. Dusenberry
William L. Gamble
Dennis W. Graber
Thomas F. Herrell
Robert Iding
Joel R. Irvine

Phillip J. Iverson
T. D. Lin
Richard J. McGrath
John D. Perry
Stephen Pessiki
Long T. Phan
Walter J. Prebis

John P. Ries
Thomas J. Rowe
Jay G. Sanjayan
Jeffrey F. Speck
Stephen S. Szoke

Consulting Members
Max Kalafat
Wasseem Khan
Steven K. Rowe
Phillip J. Samblanet

Fire resistance of building elements is an important consideration in building design. While structural design considerations for concrete and masonry at ambient temperature conditions are addressed by ACI 318 and TMS 402/ACI 530/ASCE 5, respectively, these codes do not consider the impact of fire on concrete and masonry construction. This standard contains design and analytical procedures for determining the fire resistance of concrete and masonry members and building assemblies. Where differences occur in specific design requirements between this standard and ACI 318 and TMS 402/ACI 530/ASCE 5, as in the case of cover protection of steel reinforcement, the more stringent of the requirements shall apply.

Keywords: beams; columns; compressive strength; concrete slabs; fire endurance; fire ratings; fire resistance; fire tests; masonry walls; modulus of elasticity; prestressed concrete; prestressing steels; reinforced concrete; reinforcing steel; structural design; temperature distribution; thermal properties; walls.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

PREFACE, p. 2

CHAPTER 1—GENERAL, p. 2

1.1—Scope, p. 2

1.2—Alternative methods, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

2.1—Notation, p. 2

2.2—Definitions, p. 3

CHAPTER 3—REFERENCED STANDARDS, p. 5

CHAPTER 4—CONCRETE, p. 5

4.1—General, p. 5

4.2—Concrete walls, floors, and roofs, p. 6

4.3—Concrete cover protection of steel reinforcement, p. 8

4.4—Analytical methods for calculating structural fire resistance and cover protection of concrete flexural members, p. 10

4.5—Reinforced concrete columns, p. 14

4.6—Structural steel columns protected by concrete, p. 18

4.7—Hollow structural steel columns filled with concrete, p. 20

ACI 216.1-14 supersedes ACI 216.1-07, was adopted October 30, 2014, and published November 2014.

Copyright © 2014, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 5—CONCRETE MASONRY, p. 21

- 5.1—General, p. 21
- 5.2—Equivalent thickness, p. 21
- 5.3—Concrete masonry wall assemblies, p. 22
- 5.4—Reinforced concrete masonry columns, p. 22
- 5.5—Reinforced concrete masonry lintels, p. 22
- 5.6—Structural steel columns protected by concrete masonry, p. 22

CHAPTER 6—CLAY BRICK AND TILE MASONRY, p. 23

- 6.1—General, p. 23
- 6.2—Equivalent thickness, p. 23
- 6.3—Clay brick and tile masonry wall assemblies, p. 23
- 6.4—Reinforced clay masonry columns, p. 25
- 6.5—Reinforced clay masonry lintels, p. 25
- 6.6—Expansion or contraction joints, p. 25
- 6.7—Structural steel columns protected by clay masonry, p. 25

CHAPTER 7—EFFECTS OF FINISH MATERIALS ON FIRE RESISTANCE, p. 27

- 7.1—General, p. 27
- 7.2—Calculation procedure, p. 27
- 7.3—Installation of finishes, p. 27

PREFACE

This standard provides requirements for determining fire resistance of concrete and masonry elements and assemblies. Calculation procedures for determining fire resistance are provided for concrete walls, floors, roofs, and columns and masonry walls, lintels, and columns. Procedures are also included for determining requirements for concrete cover, protection of structural steel columns using concrete or masonry, and for hollow structural steel columns filled with concrete. Procedures for determining the contribution of additional fire resistance provided by finish materials on concrete or masonry assemblies are also included.

CHAPTER 1—GENERAL**1.1—Scope**

This standard describes acceptable methods for determining the fire resistance of concrete and masonry building assemblies and structural elements, including walls, floor and roof slabs, beams, columns, lintels, and masonry fire protection for structural steel columns. These methods shall be used for design and analysis purposes and shall be based on the fire exposure and applicable end-point criteria of **ASTM E119**. This standard does not apply to composite metal deck floor or roof assemblies.

The primary intended use of this standard is for determining the design requirements for concrete and masonry elements to resist fire and provide fire protection. Tolerance compliance to the provisions for concrete shall be based on information provided in **ACI 117**. Masonry construction shall comply with **TMS 402/ACI 530.1/ASCE 6**.

The provisions of this standard establish fire resistance based on calculations. The fire resistance associated with an element or assembly shall be deemed acceptable when established by the calculation procedures in this standard or when established in accordance with 1.2.

1.2—Alternative methods

Methods other than those presented in this standard shall be permitted for use in assessing the fire resistance of concrete and masonry building assemblies and structural elements if the methods are based on the fire exposure and applicable end-point criteria specified in **ASTM E119**. Computer models, when used, shall be validated and supported by published literature to substantiate their accuracy. Alternative methods include:

Qualification by testing—Materials and assemblies of materials of construction tested in accordance with the requirements set forth in **ASTM E119** shall be classified for fire resistance in accordance with the results and conditions of such tests.

Approval through past performance—The application of fire resistance ratings to elements and assemblies that have been applied in the past and have been proven through performance shall be permitted.

Other methods—The provisions of this standard are not intended to prevent the application of new and emerging technology for predicting the life safety and property protection implications of buildings and structures.

CHAPTER 2—NOTATION AND DEFINITIONS**2.1—Notation**

- $A_1, A_2, \text{ and } A_n$ = air factor for each continuous air space having a distance of 1/2 to 3-1/2 in. between wythes
- A_{ps} = cross-sectional area of prestressing tendons, in.²
- A_s = cross-sectional area of nonprestressed longitudinal tension reinforcement, in.²
- A_{st} = cross-sectional area of the steel column, in.²
- a = depth of equivalent rectangular concrete compressive stress block at nominal flexural strength, in.
- a_0 = depth of equivalent concrete rectangular stress block at elevated temperature, in.
- B = least dimension of rectangular concrete column, in.
- b = width of concrete slab or beam, in.
- b_f = width of flange, in.
- C = compressive force due to unfactored dead load and live load, kip
- c_c = ambient temperature specific heat of concrete, Btu/(lb·°F)
- d = effective depth, distance from centroid of tension reinforcement to extreme compressive fiber or depth of steel column, in.
- D = for hollow structural steel columns, outside diameter for circular columns, in.; outside dimension for square columns, in.; and least outside dimension for rectangular columns, in.
- D_c = oven-dried density of concrete, lb/ft³