

ACI 211.8R-15

Guide to Troubleshooting Concrete Mixture Issues as Influenced by Constitutive Materials, Jobsite Conditions, or Testing Practices

Reported by ACI Committee 211



American Concrete Institute
Always advancing



Guide to Troubleshooting Concrete Mixture Issues as Influenced by Constitutive Materials, Jobsite Conditions, or Testing Practices

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide to Troubleshooting Concrete Mixture Issues as Influenced by Constitutive Materials, Jobsite Conditions, or Testing Practices

Reported by ACI Committee 211

Gary F. Knight, Chair
Timothy S. Folks*, Vice Chair

Ed T. McGuire, Secretary

William L. Barringer*
Katie J. Bartojay
Muhammed P. A. Basheer
David A. Berg
James C. Blankenship*
Casimir J. Bognacki
Michael J. Boyle
Ramon L. Carrasquillo
Bryan R. Castles
Teck L. Chua
James E. Cook
John F. Cook*
David A. Crocker
D. Gene Daniel
Kirk K. Deadrick
Donald E. Dixon
Darrell F. Elliot
David W. Fowler

G. Terry Harris Sr*
Richard D. Hill
David L. Hollingsworth
Said Irvani
Tarif M. Jaber
Robert S. Jenkins
Joe Kelley
Frank A. Kozeliski
Darmawan Ludirdja
Allyn C. Luke*
Kevin A. MacDonald
Gary R. Mass
Warren E. McPherson Jr
Jon I. Mullarky
Karthik H. Obla
H. Celik Ozyildirim
James S. Pierce
Steven A. Ragan

Royce J. Rhoads
John P. Ries
G. Michael Robinson
James M. Shilstone Jr
Ava Shypula
Woodward L. Vogt*
Michael A. Whisonantz†
*Members who contributed to this document.
†Chair of subcommittee.
Subcommittee Members
Yasar Yahia Abualrous
David Anstine
Dale P. Bentz
Zane Bussler
Laurence M. Clodic
Cesar A. Constantino
Kenneth W. Day

Dimitri Feys
Plinio Estuardo Herrera
Gene Hightower
Berndt Kanduth
Kenneth G. Kazanis
Tyler Ley
Guy Lortie
Blaine B. Nye
Bryan L. Petty
Nicholas J. Popoff
Domenick Thomas Ruttura
Lawrence L. Sutter
Paul D. Tennis
James R. Van Acker
Herman W. Wentz
Patrick J. Harrison
Consulting Member
James N. Lingscheit

*This guide describes adjustments that can be made to existing proportions for normal-density concrete with and without chemical admixtures, pozzolans, and slag. These adjustments are based on the performance of the concrete mixture as used in construction. The adjustments consider evaluation for placeability, consistency, strength, and durability. The procedures used in making these adjustments can be found in **ACI 211.1**. Adjustments to concrete mixture proportions or sources may require resubmittal to the design professional as detailed in **ACI 301**. This guide also provides*

information regarding jobsite conditions and testing practices that should be evaluated before adjustments are made to the mixture.

Keywords: admixtures; aggregates; cementitious materials; durability; fine aggregates; fly ash; metakaolin; mixture proportioning; pozzolans; quality; silica fume; slag; slag cement; slump tests; water-cementitious material ratio.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

1.1—Introduction, p. 2

1.2—Scope, p. 2

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 211.8R-15 was adopted and published June 2015.

Copyright © 2015, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 2—DEFINITIONS, p. 2**CHAPTER 3—REASONS FOR ADJUSTING MIXTURE PROPORTIONS, p. 2****CHAPTER 4—REFERENCES, p. 9**

Authored documents, p. 9

CHAPTER 1—INTRODUCTION AND SCOPE**1.1—Introduction**

This document provides guidance for evaluating the performance of concrete mixture proportions and making adjustments during the construction process as well as identifying construction or testing issues that can be wrongfully attributed to mixture proportioning. Adjustments to the mixture proportions or materials in the production process may be needed to accommodate variations in materials, changes in climatic conditions, consistency or yield of the mixture, and deficiencies in the fresh or hardened concrete properties.

1.2—Scope

ACI 211.1 provides methods for selecting proportions for concrete mixtures. Concrete may require adjustments to the mixture proportions throughout the course of the project due to the normal variation of the materials used in production, and the various conditions under which it will be delivered, placed, consolidated, and finished. The concrete properties required in the hardened state may also require adjustments to the mixture proportions. It is important to note that no document can replace experience with the materials at hand when deciding what adjustments need to be made for a concrete mixture.

CHAPTER 2—DEFINITIONS

ACI provides a comprehensive list of definitions through an online resource “ACI Concrete Terminology” at <http://www.concrete.org/store/productdetail.aspx?ItemID=CT13>.

CHAPTER 3—REASONS FOR ADJUSTING MIXTURE PROPORTIONS

There are numerous reasons for adjusting the mixture proportions. The following are two examples showing the need to adjust mixtures to alleviate an existing problem on a jobsite and also to correct the yield as a result of the change.

3.1 Example No. 1—A mixture design is being used in the field and the water required to produce a 5 in. (130 mm) slump is 10 lb/yd³ (6 kg/m³) more than the mixture design. To correct the water content, it will be added into the design. The original mixture proportions are as follows:

- a) Cement: 550 lb/yd³ (326 kg/m³)
- b) No. 57 coarse aggregate: 1850 lb/yd³ (1098 kg/m³)
- c) Fine aggregate: 1083 lb/yd³ (643 kg/m³)
- d) Water: 268 lb/yd³ (159 kg/m³)
- e) Air content: 5 percent

The following is the information used in the original mixture design:

- a) Maximum water-cementitious material ratio (w/cm) required: 0.49
- b) Coarse aggregate factor: 0.7
- c) Specific gravity of cement: 3.15
- d) Specific gravity of coarse aggregate: 2.48
- e) Unit weight of coarse aggregate: 97.9 lb/ft³ (1568.2 kg/m³)
- f) Specific gravity of fine aggregate: 2.63

The adjustment for the water demand will be based on the w/cm .

The water will increase from 268 to 278 lb/yd³ (159 to 165 kg/m³). To keep the w/cm the same, the cement will increase to 568 lb/yd³ (337 kg/m³). The coarse aggregate will remain the same and the fine aggregate will be adjusted so the mixture will continue to yield 27 ft³/yd³ (1 m³/m³).

The adjusted mixture proportions will be as follows:

- a) Cement: 568 lb/yd³ (337 kg/m³)
- b) No. 57 coarse aggregate: 1850 lb/yd³ (1098 kg/m³)
- c) Fine aggregate: 1042 lb/yd³ (618 kg/m³)
- d) Water: 278 lb/yd³ (165 kg/m³)
- e) Air content: 5 percent

3.2 Example No. 2—A mixture proportioned for a design strength of 4000 psi (28 MPa) at 28 days is only achieving an average of 2700 psi (19 MPa) at 7 days. Based on historical data of the relationship of 7 to 28-day strengths, the 28-day strength is predicted to be approximately 3800 psi (26 MPa). The mixture proportion will be adjusted to increase the strength by a targeted 500 psi (3.4 MPa). The original mixture proportions are as follows:

- a) Cement: 550 lb/yd³ (326 kg/m³)
- b) No. 67 coarse aggregate: 1920 lb/yd³ (1139 kg/m³)
- c) Fine aggregate: 1187 lb/yd³ (704 kg/m³)
- d) Water: 275 lb/yd³ (163 kg/m³)
- e) Air content: 4 percent
- f) Water reducer: 17.0 oz./yd³ (658 mL/m³)

The following is the information used in the original mixture proportions:

- a) w/cm required: 0.52 maximum
- b) Coarse aggregate factor: 0.72
- c) Specific gravity of cement: 3.15
- d) Specific gravity of coarse aggregate: 2.68
- e) Unit weight of coarse aggregate: 100.2 lb/ft³ (1605.1 kg/m³)
- f) Specific gravity of fine aggregate: 2.63

This concrete mixture, with an expected 28-day compressive strength of 3800 psi (26 MPa) and having 550 lb/yd³ (326 kg/m³) of cement produces a cement efficiency at 28 days of 6.9 psi/lb (0.080 MPa/kg/m³) (3800 psi/550 lb/yd³ = 6.9 psi/lb/yd³ [26 MPa/326 kg/m³]). To adjust the mixture to yield an additional 500 psi (3.4 MPa) would take an additional 72 lb/yd³ (43 kg/m³) of cement (500 psi/6.9 psi/lb/yd³ = 72 lb/yd³ [3.4 MPa/0.080 MPa/kg/m³ = 43 kg/m³]).

The new mixture will be as follows:

- a) Cement: 622 lb/yd³ (370 kg/m³)
- b) No. 67 coarse aggregate: 1920 lb/yd³ (1139 kg/m³)
- c) Fine aggregate: 1126 lb/yd³ (668 kg/m³)
- d) Water: 275 lb/yd³ (163 kg/m³)
- e) Air content: 4 percent