

ACI 225R-16

Guide to the Selection and Use of Hydraulic Cements

Reported by ACI Committee 225



American Concrete Institute
Always advancing



Guide to the Selection and Use of Hydraulic Cements

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide to the Selection and Use of Hydraulic Cements

Reported by ACI Committee 225

Jay E. Whitt, Chair

Thomas J. Grisinger, Secretary

Gregory S. Barger
Claude Bedard
Glen E. Bollin
Michael M. Chehab
Marwan A. Daye
Jonathan E. Dongell

Thomas M. Greene
Michael S. Hammer
Geoffrey Hichborn Sr.
R. Doug Hooton
Francis Innis
Kenneth G. Kazanis

Kimberly E. Kurtis
Mark R. Lukkarila
Kirk L. McDonald
Leo M. Meyer, Jr.
Moncef L. Nehdi
James S. Pierce

Nicholas J. Popoff
Bryce P. Simons
Oscar Tavares
Paul D. Tennis
James I. Turici, Jr.
Stephen D. Wilcox

*The committee would like to acknowledge B. Blair and M. D. A. Thomas for their contributions in the development of this guide.

Cement is the most active component of concrete and usually has the greatest unit cost; therefore, its selection and proper use is imperative to attaining the desired balance of properties and cost for a particular concrete mixture. Selection should include consideration of the cement properties in relation to the required performance of the concrete. This guide covers the influence of cement on the properties of concrete, summarizing the composition and availability of commercial hydraulic cements and the factors affecting their performance in concrete. It includes a discussion of cement types, a brief review of cement chemistry, the influences of chemical admixtures and supplementary cementitious materials, and the effects of the environment on cement performance, and reviews the sustainability aspects for the use and manufacture of portland cement. Cement storage, delivery, sampling, and testing of hydraulic cements for conformance to specifications are addressed. Users will learn to recognize when a readily available, general-purpose cement will perform satisfactorily or when conditions require selection of a cement that meets additional requirements.

Keywords: admixture; blended cement; calcium-aluminate cement; cement storage; cement types; chemical analysis; hydraulic cement; pozzolan; physical properties; portland cement; slag cement; supplemental cementitious materials; sustainability.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

1.1—Introduction, p. 2

1.2—Scope, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 3

2.1—Notation, p. 3

2.2—Definitions, p. 3

CHAPTER 3—CEMENT TYPES, AVAILABILITY, AND SELECTION, p. 3

3.1—Portland and blended hydraulic cements, p. 3

3.2—Special-purpose, p. 4

3.3—Research and development, p. 5

3.4—Rational approach to selection, p. 5

CHAPTER 4—CEMENT CHEMISTRY, p. 8

4.1—Portland cement, p. 8

4.2—Blended hydraulic, p. 11

4.3—Shrinkage-compensating expansive, p. 11

4.4—Calcium-aluminate, p. 11

CHAPTER 5—INFLUENCE OF CHEMICAL ADMIXTURES, POZZOLANS, AND SLAG CEMENTS ON CEMENTITIOUS SYSTEMS, p. 12

5.1—Air-entraining admixtures, p. 12

5.2—Other chemical admixtures, p. 12

5.3—Pozzolans, p. 14

ACI 225R-16 supersedes ACI 225R-99 and was adopted and published September 2016.

Copyright © 2016, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

5.4—Slag cements, p. 15

CHAPTER 6—INFLUENCE OF ENVIRONMENTAL CONDITIONS ON THE HYDRATION OF CEMENTS, p. 15

- 6.1—Water requirements, p. 15
- 6.2—Temperature effects, p. 15
- 6.3—Composition, p. 15

CHAPTER 7—INFLUENCE OF CEMENT ON CONCRETE PROPERTIES, p. 15

- 7.1—Thermal cracking, p. 15
- 7.2—Placeability, p. 17
- 7.3—Strength, p. 17
- 7.4—Volume stability, p. 18
- 7.5—Elastic properties, p. 19
- 7.6—Creep, p. 20
- 7.7—Permeability, p. 20
- 7.8—Corrosion of embedded steel, p. 20
- 7.9—Resistance to freezing and thawing, p. 21
- 7.10—Resistance to chemical attack, p. 21
- 7.11—Resistance to high temperatures, p. 21
- 7.12—Cement-aggregate reactions, p. 21
- 7.13—Color, p. 23

CHAPTER 8—CEMENT STORAGE AND DELIVERY, p. 23

- 8.1—Storage, p. 23
- 8.2—Pack set (sticky cement), p. 24
- 8.3—Delivery, p. 24
- 8.4—Contamination and handling, p. 24
- 8.5—Worker protection, p. 25

CHAPTER 9—SAMPLING AND TESTING OF HYDRAULIC CEMENTS FOR CONFORMANCE TO SPECIFICATIONS, p. 25

- 9.1—Cement mill test report, p. 25
- 9.2—Sealed silos, p. 25
- 9.3—Cement certification, p. 26
- 9.4—Quality management, p. 26

CHAPTER 10—SUSTAINABILITY ASPECTS OF HYDRAULIC CEMENTS, p. 27

- 10.1—Hydraulic cements, p. 27
- 10.2—Energy consumption, p. 27
- 10.3—Use of supplementary cementitious materials (SCMs) as replacement for portland cement, p. 28
- 10.4—Use of cement in concrete, p. 28
- 10.5—Recycled raw materials as raw feed in the manufacture of portland cement, p. 28
- 10.6—Alternate fuels, p. 28
- 10.7—Combustion emissions, p. 29
- 10.8—Recent progress and strategy, p. 29

CHAPTER 11—REFERENCES, p. 29

Authored documents, p. 30

APPENDIX A—CALCIUM-ALUMINATE CEMENTS, p. 34

- A.1—Manufacture and properties, p. 34
- A.2—Influences of admixtures and supplementary cementitious materials, p. 34
- A.3—Influence of environment, p. 34
- A.4—Heat of hydration, p. 34
- A.5—Setting characteristics, p. 34
- A.6—Strength, p. 35
- A.7—Resistance to chemical attack, p. 35
- A.8—Resistance to high temperatures, p. 36

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

This guide assists specifiers and designers in choosing appropriate cement for specified concrete applications. Although hydraulic cements are only one ingredient of a concrete mixture, they are the active ingredient and, therefore, play a key role in the long-term viability of the structure, floor, or pavement. Cement choice depends on many variables, such as the service conditions for which the concrete is designed, properties of other materials used in the mixture, or the performance characteristics of the concrete required during or shortly after placement.

Cement paste is the binder in concrete or mortar that holds the fine aggregate, coarse aggregate, or other constituents together in a hardened mass. The term “hydraulic” in this guide refers to the basic mechanism by which the hardening of the cement takes place—a chemical reaction between the cement and water. The term also differentiates hydraulic cement from binder systems that are based on other hardening mechanisms, as hydraulic cements can harden underwater.

Concrete properties depend on the quantities and qualities of its constituents. Because cement is the most active component of concrete and usually has the greatest unit cost, its selection and proper use are fundamental in obtaining the most economical balance of properties desired for a particular concrete mixture. Most cements will provide adequate levels of strength and durability for general use. Some provide higher levels of certain properties than are needed in specific applications.

1.2—Scope

This guide summarizes information about the composition, availability, and factors affecting the performance of commercial hydraulic cements. It also provides information regarding:

- a) Cement selection, whether a cement is readily available, and if conditions require a general-purpose cement or a special cement
- b) How the chemical and physical characteristics of a cement can affect certain properties of concrete
- c) How interaction of cements with various additives, admixtures, and mixture designs can affect concrete

This guide only deals with hydraulic cements manufactured under North American standards (ASTM International, American Association of State Highway and Transportation

Officials [AASHTO], and Canadian Standards Association [CSA]). For information on other hydraulic cement standards, the user is directed to local specifications and building codes.

CHAPTER 2—NOTATION AND DEFINITIONS

2.1—Notation

Cement phases referred to throughout this guide follow the cement chemists' notations as follows:

A = Al_2O_3

C = CaO

\bar{C} = CO_2

F = Fe_2O_3

H = H_2O

M = MgO

S = SiO_2

\bar{S} = SO_3

tricalcium silicate: $3\text{CaO}\cdot\text{SiO}_2 = \text{C}_3\text{S}$

dicalcium silicate: $2\text{CaO}\cdot\text{SiO}_2 = \text{C}_2\text{S}$

tricalcium aluminate: $3\text{CaO}\cdot\text{Al}_2\text{O}_3 = \text{C}_3\text{A}$

tetracalcium aluminoferrite: $4\text{CaO}\cdot\text{Al}_2\text{O}_3\cdot\text{Fe}_2\text{O}_3 = \text{C}_4\text{AF}$

Tricalcium silicate, Ca_3SiO_5 , in conventional notation becomes $3\text{CaO}\cdot\text{SiO}_2$ in oxide notation, or C_3S in cement chemists' notation. Simple oxides, such as CaO or SiO_2 , are often written in full.

2.2—Definitions

ACI provides a comprehensive list of definitions through an online resource, "ACI Concrete Terminology," <https://www.concrete.org/store/productdetail.aspx?ItemID=CT16>.

Equivalent alkali in hydraulic cement is the total of sodium and potassium oxides as calculated from the chemical analysis, and using the formula: $\text{Na}_2\text{O}_{\text{eq}} = \% \text{Na}_2\text{O} + 0.658\% \text{K}_2\text{O}$ (ASTM C219).

CHAPTER 3—CEMENT TYPES, AVAILABILITY, AND SELECTION

Selection of cement is an important consideration when proportioning mixtures for specific project requirements and intended use. It is important that the specification for hydraulic cements be appropriate for the project and the hydraulic cements available in the area. Factors such as exposure conditions and desired properties can often require specific cement types based on the chemistry or physical properties. Specific cements may be available that are designed for applications where performance requirements cannot be achieved with ordinary portland cement.

3.1—Portland and blended hydraulic cements

A majority of the cement used for concrete construction in the United States is either portland cement, manufactured to meet the requirements of **ASTM C150/C150M**, blended hydraulic cement manufactured to meet the requirements of **ASTM C595/C595M**, or performance-based hydraulic cement manufactured to meet the requirements of **ASTM C1157/C1157M**. Tables 3.1a and 3.1b include basic characteristics of these cements as listed in ASTM. Other portland cement specifications can be found in **AASHTO M 85** or,

Table 3.1a—Characteristics of portland cements*

Type*	Description	Optional characteristics†
I	General use	1, 4
II	General use; moderate sulfate resistance	1, 4
II (MH)	General use; moderate heat of hydration	1, 4
III	High-early-strength	1, 2, 3
IV	Low heat of hydration	4
V	High sulfate resistance	4, 5

*For cements specified in ASTM C150/C150M.

†Optional characteristics:

1. Air entraining (A)
2. Moderate sulfate resistance: C_3A maximum, 8 percent
3. High-sulfate resistance: C_3A maximum, 5 percent
4. Low alkali: maximum of 0.60 percent alkalis, expressed as Na_2O equivalent
5. Alternative limit of sulfate resistance is based on expansion tests of mortar bars

for Canada, in **CSA-A3001**. Blended cements are also specified under the **AASHTO M 240** requirements. For more on hydraulic cement specifications and selection, refer to 3.4.

Portland cements are manufactured by a process that begins by combining a source of lime such as limestone, a source of silica and alumina such as clay, and a source of iron oxide such as iron ore. The properly proportioned mixture of the raw materials is finely ground and then heated to approximately 2700°F (1480°C) for the reactions that form cement phases to take place. The product of a cement kiln is portland cement clinker. After cooling, the clinker is ground with calcium sulfate (gypsum); processing additions; and, in many cases, limestone to form a portland cement. Processing additions are organic or inorganic materials used in the manufacture of cements that are added at the finish mill. Their use is governed by **ASTM C465**. Processing addition rates for portland cements are specified in **ASTM C150/C150M**. The specific gravity of portland cement will vary slightly depending on the amounts of limestone, gypsum, and inorganic processing addition added to the clinker (for further reference on inorganic process addition refer to **Taylor [2008]**). Most of these additions are less dense than clinker and tend to reduce the specific gravity of the portland cement. When proportioning concrete mixtures, unless an actual measurement of the specific gravity of the cement has been made, 3.15 has been used for portland cements (**Kosmatka and Wilson 2011**). As the amount of processing additions increase, the specific gravity value has been found to decrease.

Blended hydraulic cements are usually made by intergrinding portland cement clinker with calcium sulfate (gypsum); processing additions; and a quantity of a suitable material such as slag cement, fly ash, limestone, silica fume, or raw or calcined natural pozzolans. They may also be made by blending the finely ground ingredients, or by a combination of blending and intergrinding. The specific gravity of a blended cement will vary with the type and amount of material(s) that is interground or interblended.