

ACI 241R-17

# Report on Application of Nanotechnology and Nanomaterials in Concrete

Reported by ACI Committees 236 and 241



American Concrete Institute  
*Always advancing*



## **Report on Application of Nanotechnology and Nanomaterials in Concrete**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**Phone: +1.248.848.3700**  
**Fax: +1.248.848.3701**

[www.concrete.org](http://www.concrete.org)

# Report on Application of Nanotechnology and Nanomaterials in Concrete

Reported by ACI Committees 236 and 241

## ACI Committee 241

Konstantin Sobolev, Chair

Mahmoud M. Reda Taha, Secretary

Aali R. Alizadeh  
Muhammed P. A. Basheer  
Jon S. Belkowitz  
Haroldo de Mayo Bernardes  
Jeremy Betts  
Paul W. Brown  
Samir E. Chidiac  
Vyatcheslav R. Falikman  
Liberato Ferrara  
Ismael Flores-Vivian  
Brian H. Green

William S. Hart  
Aulis Kappi  
Shiho Kawashima  
Maria S. Konsta-Gdoutos  
Konstantin Kovler  
Kimberly E. Kurtis  
David A. Lange  
Berengere Lebental  
Samuel J. Lines  
Viktor Mechtcherine  
Anol Kanti Mukhopadhyay

Jose F. Munoz  
Scott Muzenski  
Moncef L. Nehdi  
Narayanan Neithalath  
Kamran M. Nemati  
Jan Olek  
H. Celik Ozyildirim  
Alva Peled  
Amirpasha Peyvandi  
Amal Puthur-Jayapalan  
Laila Raki

Todd S. Rushing  
Aly Said  
Florence Sanchez  
Surendra P. Shah  
Lin Shen  
Mohammed Sonebi  
Dietmar Stephan  
Valeria Strokova  
Peter Stynoski  
Zhihui Sun  
Jussara Tanesi

Kejin Wang  
Kay Wille  
Brett Anthony Williams  
Erik E. Wotring  
Ardavan Yazdanbakhsh  
Min-Hong Zhang  
Igor Zernovskiy  
Consulting Member  
Mohamadreza Moini

## Committee 236

The following voting members from Committee 236 drafted and voted on the initial report.

Maria G. Juenger, Chair  
Zachary C. Grasley\*,  
Secretary

*Voting Members*  
Emmanuel K. Attiogbe  
Muhammed P. A. Basheer\*  
Jeremy Betts\*  
Joseph J. Biernacki  
Andrew J. Boyd  
Paul W. Brown\*  
Van K. Bui  
Jeffrey W. Bullard  
Frederic Chapdelaine  
Samir E. Chidiac\*  
Peter A. Claisse\*  
Neil J. Crockett  
Matthew D. D'Ambrosia  
Christopher C. Ferraro  
Mette Geiker  
R. Doug Hooton

Jason H. Ideker  
O. Burkan Isgor  
Ara A. Jeknavorian  
Aulis Kappi\*  
Kamal H. Khayat  
Eric P. Koehler  
Konstantin Kovler\*  
Kimberly E. Kurtis\*  
David A. Lange\*  
Tyler Ley  
Jacques Marchand  
Benjamin J. Mohr  
Paramita Mondal\*  
Anol Kanti Mukhopadhyay\*  
Moncef L. Nehdi\*  
Narayanan Neithalath\*  
Kamran M. Nemati\*  
Michelle R. Nokken  
Jan Olek\*  
Sulapha Peethamparan\*  
Vincent Picandet

Aleksandra Radlinska  
Laila Raki\*  
Prasad R. Rangaraju\*  
Mahmoud M. Reda Taha\*  
Kyle Austin Riding  
David A. Rothstein  
Della M. Roy  
Aly Said\*  
Florence Sanchez\*  
Gaurav N. Sant\*  
Yixin Shao  
Caijun Shi  
Kenneth Snyder  
Konstantin Sobolev†  
Mohammed Sonebi\*  
Jussara Tanesi\*  
Peter C. Taylor\*  
Michael D. A. Thomas  
David Trejo  
Wilasa Vichit-Vadakan  
Kejin Wang\*

Zhaozhou Zhang  
*Subcommittee Members*  
Aali Alizadeh\*  
Mohamed Bassuoni\*  
Jon Belkowitz\*  
Haroldo de Mayo Bernardes\*  
Chul-Woo Chung\*  
Deborah D. L. Chung\*  
Vyatcheslav Falikman\*  
Liberato Ferrara\*  
Ismael Flores-Vivian\*  
Nishant Garg\*  
Brian Green\*  
William S. Hart\*  
Payam Hosseini\*  
Maria S. Konsta\*  
Berengere Lebental\*  
Samuel Lines\*  
Viktor Mechtcherine\*  
Jose Munoz\*

H Celik Ozyildirim\*  
Bekir Pekmezci\*  
Alva Peled\*  
Amal Puthur-Jayapalan\*  
Todd S. Rushing\*  
Joan Schoepfer\*  
Surendra P. Shah\*  
Lin Shen\*  
Caijun Shi\*  
Valeria Strokova\*  
Peter Stynoski\*  
Zhihui Sun\*  
Jacqueline N. Villa Prenger\*  
Brett Williams\*  
Min-Hong Zhang\*  
Igor Zernovskiy\*  
*Consulting Members*  
Barbara Lothenbach  
Weiping Ma  
Frank Winnefeld

\*Members of 236D subcommittee who drafted this report.

†Chair of 236D subcommittee who drafted this report.

Members of Committees 236 and 241 thank J. Beaudoin, M. Rahman, J. Kim, L. Brown, C. Gay, and T. Sato for their contributions to this report.

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 241R-17 was adopted and published January 2017.

Copyright © 2017, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

*This report presents information on nanotechnology of concrete, including recent developments related to investigation of nanostructure and nanodesign of cement-based materials, the effects of nanoparticles, field applications, and health and environmental safety concerns related to the use of nanomaterials.*

**Keywords:** biomimicry; carbon nanofibers; carbon nanotubes; nanobinder; nanoclay; nanoindentation; nanoparticles; nanosilica; nanotechnology; nanotitanium dioxide; superhydrophobic concrete.

## CONTENTS

### CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3

### CHAPTER 2—NOTATION AND DEFINITIONS, p. 3

- 2.1—Notation, p. 3
- 2.2—Definitions, p. 4

### CHAPTER 3—INVESTIGATION AND MODELING OF NANOSTRUCTURE AND HYDRATION MECHANISMS, p. 5

- 3.1—Investigation of nanostructure, p. 5
- 3.2—Nanocharacterization, p. 7
- 3.3—Modeling of cementitious nanostructures, p. 10

### CHAPTER 4—NANOASSEMBLY AND BIOMIMETICS IN CEMENT-BASED MATERIAL, p. 10

- 4.1—Nanoparticles in polymer/cement matrix, p. 11
- 4.2—Advanced fibers, p. 11
- 4.3—Superhydrophobic concrete, p. 11

### CHAPTER 5—NANOSIZED AND NANOSTRUCTURED MATERIALS IN CEMENT AND CONCRETE, p. 13

- 5.1—Application of nanoparticles, p. 13
- 5.2—Application of carbon nanotubes/nanofibers, p. 19
- 5.3—Synthesis of CNTs/CNFs on cement and cementitious material particles, p. 21
- 5.4—Nanocomposites, p. 21

### CHAPTER 6—NANOMATERIALS IN CONCRETE: FIELD APPLICATIONS, p. 22

### CHAPTER 7—ENVIRONMENTAL EFFECTS AND SAFETY OF NANOMATERIALS USED IN CONCRETE, p. 24

- 7.1—Nanoparticles and health effects, p. 24
- 7.2—Effects on environment, p. 24
- 7.3—Risk assessment, p. 25

### CHAPTER 8—REFERENCES, p. 25

- Authored documents, p. 25

## CHAPTER 1—INTRODUCTION AND SCOPE

### 1.1—Introduction

Nanotechnology is a multidisciplinary field of science and engineering focused on understanding and controlling matter at dimensions between 1 and 100 nanometers, where unique phenomena enable novel applications.

Nanotechnology was first introduced by Feynman (1960) and is rapidly becoming an interdisciplinary field; many developments have emerged in physics, chemistry, biology, and engineering in the study of various materials or substances at the nanoscale.

There are two main approaches in nanotechnology: 1) the top-down approach, in which larger structures are reduced in size to the nanoscale while maintaining their original properties without atomic-level control (for example, miniaturization in the domain of electronics), or deconstructed from larger structures into smaller, composite parts (top part of Fig. 1.1a); and 2) the bottom-up approach, also called molecular nanotechnology or molecular manufacturing, introduced by Drexler et al. (1991), in which materials are engineered from atoms, or molecular components, through a process of assembly or self-assembly (bottom part of Fig. 1.1a). While most contemporary technologies, including concrete, rely on the top-down approach, molecular nanotechnology holds great promise for advancement in materials and manufacturing, electronics, medicine and healthcare, energy, biotechnology, information technology, and national security.

Nanoscience and nanoengineering are commonly-used terms that describe nanotechnology applications in concrete (Sobolev and Ferrada-Gutiérrez 2005a; Scrivener and Kirkpatrick 2008; Scrivener 2009; Raki et al. 2009; Garboczi 2009). To date, nanotechnology applications and advances in the fields of construction and building materials have been inconsistent (Bartos 2009; Sanchez and Sobolev 2010; Sobolev and Sanchez 2012). Implementing nanotechnology into concrete on a commercial scale remains limited. Some research developments, however, have been successfully converted into marketable products. The main advances have been in nanoscience of cementitious and pozzolanic materials, providing an increase in the knowledge and understanding of basic phenomena in cement at the nanoscale (Scrivener and Kirkpatrick 2008; Scrivener 2009). Examples include structure and mechanical properties of the main hydrate phases, origins of cement cohesion, cement hydration, interfaces in concrete, and mechanisms of degradation. Recent innovations in instrumentation for observing and measuring at the nanoscale are providing a wealth of new and unprecedented information about concrete. This information is crucial for a better understanding of mechanisms and factors influencing performance requirements, as well as predicting the service life of concrete and providing new insights for improvement. Important summaries and compilations of nanotechnology in construction can be found in Sobolev and Ferrada-Gutiérrez (2005a), Bartos et al. (2006), de Miguel et al. (2006), Scrivener and Kirkpatrick (2008), Sobolev and Shah (2008), Sobolev et al. (2008b), Sanchez




Fig. 1.1a—Illustration of the top-down and bottom-up approaches in nanotechnology (Sobolev and Ferrada-Gutiérrez 2005a).

and Sobolev (2010), Sobolev and Sanchez (2012), and Birgisson et al. (2012).

Concrete, the most ubiquitous construction material, is a “nanostructured, multiphase, porous composite material, composed of amorphous phases, nanometer- to micrometer-size crystals, and bound and free water” (Sanchez and Sobolev 2010). The properties of concrete exist at multiple length scales, nano to micro to macro (Fig. 1.1b). The properties of each scale derive from those of the next-smaller scale (Jennings et al. 2008; Sanchez et al. 2009). The amorphous phase, calcium-silicate-hydrate (C-S-H), is the phase that holds concrete together (Chong and Garboczi 2002), and is itself a nanostructured material (Fig. 1.1c).

Viewed from the bottom-up, concrete at the nanoscale is a composite of molecular assemblages, surfaces such as aggregates and fibers, and chemical bonds that interact through local chemical reactions, intermolecular forces,

and intra-phase diffusion. Properties characterizing this scale include surface properties and chemical bond properties such as type, length, strength/energy, and density. Structures of the amorphous and crystalline phases and the interphase boundaries originate from this scale. Properties and processes at the nanoscale define interactions that occur between particles and phases at the microscale, the effects of working loads, and the surrounding environment at the macroscale. Processes occurring at the nanoscale ultimately affect the engineering properties and performance of the bulk material (Garboczi and Bentz 1996, 1998; Xi et al. 2000; Jennings et al. 2008; Scrivener and Kirkpatrick 2008; Sanchez et al. 2009).

## 1.2—Scope

This report provides information for those involved in concrete design and construction so they are familiar with the factors involved in the effective use of nanomaterials and nanotechnology. This document is not intended as a primary reference source for researchers. Rather, it is aimed at engineers and architects who wish to gain further understanding of the effects of nanomaterials and nanoadditives being used or proposed for application in concrete.

Application of available technology is demonstrated for a range of nanoconcrete structures to show that technological risks are at a known and acceptable level and high industry standards maintained. An overview reports on the main developments in the fields of nanotechnology and nanoscience that are related to concrete, along with their implications and key findings. Factors affecting performance of fresh and hardened concrete are discussed to enable those involved in the evaluation and formulation of concrete mixtures to determine the effects of these factors.

The potential of nanotechnology to improve concrete performance can lead to the development of novel, sustainable, advanced cement-based composites with unique mechanical, thermal, and electrical properties. New developments have already taken place in nanoengineering and nanomodification of concrete. Current challenges, including proper dispersion, compatibility of the nanomaterials in cement, processing, manufacturing, safety, handling issues, and cost all need to be solved before the complete potential of nanotechnology can be realized in concrete applications. Additionally, introduction of these novel materials into the construction practice requires an evaluation and understanding of their potential impact on the environment and human health.

## CHAPTER 2—NOTATION AND DEFINITIONS

### 2.1—Notation

A	= aluminum oxide ( $\text{Al}_2\text{O}_3$ )
$A_i$	= area of indentation impression, $\mu\text{m}^2$
C	= calcium oxide (CaO)
$\text{CaCO}_3$	= calcium carbonate
CH	= calcium hydroxide
C/S	= the molar or mass ratio of calcium oxide (CaO) to silicon dioxide ( $\text{SiO}_2$ )
C-S-H	= amorphous calcium silicate hydrate phase