

ACI 423.3R-17

Recommendations for Concrete Members Prestressed with Single- Strand Unbonded Tendons

Reported by Joint ACI-ASCE Committee 423



American Concrete Institute
Always advancing



Recommendations for Concrete Members Prestressed with Single-Strand Unbonded Tendons

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, on CD-ROM, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised ACI Manual of Concrete Practice (MCP).

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Recommendations for Concrete Members Prestressed with Single-Strand Unbonded Tendons

Reported by Joint ACI-ASCE Committee 423

Carin L. Roberts-Wollmann, Chair

Amy M. Reineke Trygestad, Secretary

Theresa M. Ahlborn
Rashid Ahmed*
Robert W. Barnes
Florian G. Barth
Asit N. Baxi*
Roger J. Becker
Charles W. Dolan*
James P. Donnelly
Pierre Esselinck

Martin J. Fradua
William L. Gamble
Harry A. Gleich
Pawan R. Gupta
William M. Hale
H. R. Trey Hamilton III
Carol Hayek*
Mohammad Iqbal
Donald P. Kline*


Larry B. Krauser
Jason J. Krohn
Theodore L. Neff
Sami H. Rizkalla
James Rogers
Brandon Ross
Bruce W. Russell
Thomas C. Schaeffer*
Richard W. Stone

Miroslav Vejvoda
Jeffrey S. Volz
H. Carl Walker
Zuming Xia
Paul Zia

Consulting Members

Kenneth B. Bondy*
Robert N. Bruce Jr.
Ned H. Burns

Chunsheng "Steve" Cai
Steven R. Close
Henry J. Cronin Jr.

Ward N. Marianos Jr. 
Hani Melhem
Antoine E. Naaman

Thomas E. Nehil
Andrea J. Schokker

*Subcommittee members involved in updating this report.

This report provides information for the design of flexural concrete members in buildings post-tensioned with single-strand unbonded tendons. The report is intended to complement the commentary in ACI 318 and to provide suggestions for revisions and additions to ACI 318. Consideration is given to design for gravity and lateral loads, determination of fire endurance, design for seismic forces, and design for catastrophic loadings. Recommendations concerning details and properties of tendons, protection against corrosion, and construction procedures are presented.

Keywords: concrete slabs; cracking; fire resistance; joints; punching shear; unbonded post-tensioning.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 2

- 1.1—General, p. 2
- 1.2—Objective, p. 2
- 1.3—Scope, p. 2

CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

- 2.1—Notation, p. 2
- 2.2—Definitions, p. 3

CHAPTER 3—MEMBER DESIGN, p. 3

- 3.1—General, p. 3
- 3.2—One-way systems, p. 3
- 3.3—Two-way systems, p. 4
- 3.4—Beams, p. 8
- 3.5—Effects of supporting walls and columns on prestress forces, p. 9

CHAPTER 4—ANCHORAGE ZONES, p. 10

- 4.1—Anchorage zone reinforcement, p. 10

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 423.3R-17 supersedes ACI 423.3R-05 and was adopted and published July 2017. Copyright © 2017, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

CHAPTER 5—SEISMIC DESIGN, p. 11

5.1—Earthquake loading, p. 11

CHAPTER 6—DESIGN CONSIDERATIONS, p. 13

6.1—General, p. 13
 6.2—Design strength, p. 13
 6.3—Tendon stress at factored load, p. 13
 6.4—Prestress losses, p. 14
 6.5—Average prestress, p. 14
 6.6—Serviceability requirements, p. 15
 6.7—Continuous members, p. 15
 6.8—Corrosion protection, p. 15
 6.9—Fire resistance, p. 16

CHAPTER 7—MATERIALS, p. 18

7.1—Tendons, p. 18
 7.2—Protection materials, p. 18
 7.3—Protection of anchorage zones, p. 18
 7.4—Concrete cover, p. 18

CHAPTER 8—CONSTRUCTION, p. 19

8.1—Construction joints, p. 19
 8.2—Closure strips, p. 19
 8.3—Placement of tendons, p. 19
 8.4—Concrete placement and curing, p. 19
 8.5—Stressing operations, p. 20
 8.6—Form removal and reshoring, p. 21
 8.7—Welding and burning, p. 21
 8.8—Protection of tendons, p. 21

CHAPTER 9—REFERENCES, p. 21

Authored documents, p. 21

CHAPTER 1—INTRODUCTION**1.1—General**

Since the publication of previous ACI 423.3R reports, many of their recommendations have been incorporated into ACI 318. All references to ACI 318 refer to ACI 318-14 unless specifically noted. The recommendations in this report have been prepared to provide a comprehensive guide for design, materials, and construction for concrete members prestressed with single-strand unbonded tendons. Suggested revisions and additions to ACI 318 are also included in this report. Mandatory language used in this report reflects requirements in ACI 318.

1.2—Objective

This report presents recommendations for design, materials, and construction for concrete structures prestressed with unbonded tendons that are commensurate with the strength, serviceability, and safety requirements of ACI 318. Practitioners should use their judgment when applying the recommendations of this report. This report is not intended for reference in a specification or a code.

1.3—Scope

Recommendations pertinent to design with single-strand unbonded tendons considered in this report include the design of slabs, beams, and continuous members; details and properties of tendons and anchors; and protection from corrosion during construction and throughout the life of the structure.

The recommendations in this report are not intended for unbonded construction stages of elements using bonded tendons; for multistrand unbonded tendons used as external tendons; for members subject to direct tension, such as tiebacks, cable stays, arch ties, or circumferential tendons for containment structures; or for ground-supported post-tensioned slabs for light residential construction.

CHAPTER 2—NOTATION AND DEFINITIONS**2.1—Notation**

A_b = net bearing plate area, in.² (mm²)
 A_b' = maximum area of the portion of the concrete anchorage surface that is geometrically similar to and concentric with the area of the anchorage, in.² (mm²)
 A_c' = cross-sectional area of the slab, perpendicular to the slab edge, between the center of the exterior span and the slab edge, in.² (mm²)
 A_{cf} = larger of gross cross-sectional areas of the slab-beam strips of the two orthogonal equivalent frames intersecting at the column, in.² (mm²)
 A_{ps} = area of prestressed longitudinal tension reinforcement, in.² (mm²)
 $A_{s,min}$ = minimum bonded reinforcement in negative moment areas of two-way systems
 b = width of compression face of member, in. (mm)
 b_f = total flange width
 b_n = effective overhang flange width for normal forces, in. (mm)
 b_o = perimeter of critical section for two-way shear in slabs, in. (mm)
 b_w = effective flange width for normal forces at post-tension anchor, in. (mm)
 d_p = distance from extreme compression fiber to centroid of prestressing reinforcement, in. (mm)
 E_s = modulus of elasticity of prestressing reinforcement, psi (MPa)
 f_{ci}' = strength of concrete at time of initial prestress, psi (MPa)
 f_{cp} = permissible concrete compressive stress, psi (MPa)
 f_{pc} = compressive stress in concrete, after allowance for all prestress losses, at centroid of cross section resisting externally applied loads or at junction of web and flange where the centroid lies within the flange, psi (MPa); in a composite member, f_{pc} is the resultant compressive stress at centroid of composite section, or at junction of web and flange where the centroid lies within the flange, due to both prestress and moments resisted by precast member acting alone, psi (MPa)

f_{ps}	= stress in prestressing reinforcement at nominal flexural strength, psi (MPa)
$f_{ps\theta}$	= stress in post-tensioned tendons at nominal strength at high temperatures, psi (MPa)
f_{pu}	= specified tensile strength of prestressing reinforcement, psi (MPa)
$f_{pu\theta}$	= tensile strength of tendons at high temperatures, psi (MPa)
f_{se}	= effective stress in prestressing reinforcement, after allowance for all prestress losses, psi (MPa)
f_y	= specified yield stress of reinforcement, psi (MPa)
h	= slab thickness, in. (mm)
L	= span length of beam or one-way slab; clear projection of cantilever, in. (mm)
ℓ	= length of tendon, in. (mm)
M	= total applied static moment (unfactored), lb-in. (kN-m)
M_{1q}^+	= retained midspan moment, lb-in. (kN-m)
$M_{11\theta}^-$	= retained negative moment capacity at Column 1, lb-in. (N-m)
$M_{12\theta}^-$	= retained negative moment capacity at Column 2, lb-in. (N-m)
N_c	= resultant tensile force acting on the portion of the concrete cross section that is subjected to tensile stresses due to the combined effects of service loads and effective prestress, lb (N)
P	= average force in the prestressing reinforcement, lb (N)
V_p	= vertical component of effective prestress forces crossing the critical section
v_c	= stress corresponding to nominal two-way shear strength provided by concrete, psi (MPa)
v_{cw}	= nominal shear stress provided by concrete where diagonal cracking results from high principal tensile stress in web, lb (N)
w	= uniformly distributed load, plf (kN/m)
α_s	= constant used to calculate V_c in slabs, lb (MPa)
Δ_ℓ	= tendon elongation, in. (mm)
ϕ	= strength reduction factor
λ	= modification factor to reflect the reduced mechanical properties of lightweight concrete
ρ_p	= ratio of A_{ps} to bd_p

2.2—Definitions

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology,” <https://www.concrete.org/store/productdetail.aspx?ItemID=CT16>. Definitions provided herein complement that source.

encapsulated tendon—a tendon that is completely enclosed in a watertight covering from end to end, including anchorages, sheathing, post-tensioning coating, sleeves, and an encapsulation cap over the strand tail at each end.

post-tensioning coating—material between prestressing reinforcement and sheathing used to protect against corrosion and reduce friction.

prestressing reinforcement—strand, wire, or bar tensioned to impart forces to the concrete.

sheathing—material encasing prestressing reinforcement to prevent bonding of the prestressing reinforcement with the surrounding concrete, to provide corrosion protection, and to contain the corrosion-inhibiting coating.

CHAPTER 3—MEMBER DESIGN

3.1—General

The design provisions of ACI 318 apply to the contents of this chapter, but some recommendations are offered that complement those of ACI 318. Significant changes were made in [ACI 318-02](#), [ACI 318-08](#), [ACI 318-11](#), and [ACI 318-14](#) that impact the design of prestressed concrete members and unify the design approach for prestressed and nonprestressed members. ACI 318 limits for flexural reinforcement and moment redistribution are specified in terms of the net tensile strain in the extreme tension reinforcement ϵ_r . Prestressed members are grouped into three design categories: uncracked (U), transition (T), and cracked (C). Each category is defined according to the maximum calculated flexural tensile stress under service load conditions. For C members, there is no upper limit on calculated flexural tensile stresses under service loads, and any combination of stressed and unstressed reinforcement is permitted. Serviceability requirements related to C and T members are given in ACI 318.

3.2—One-way systems

One-way slabs are addressed in ACI 318-14 Chapter 7. The chapter organization provides design limits, required strength, required design strength, reinforcement limits, and reinforcing detailing.

3.2.1 Minimum bonded reinforcement—The minimum bonded reinforcement required in ACI 318-14, 7.6.2, is considered adequate to limit crack widths due to dead load and live load by providing adequate crack distribution ([Burns et al. 1978](#); [Yamazaki et al. 1969](#); [Burns and Pierce 1967](#)). This amount of reinforcement also provides an independent load-carrying system in the event of a catastrophic failure of the tendons or abnormal loading in one span of a continuous one-way post-tensioned element with unbonded tendons. For this reason, ACI 318-14, 7.7.4.2, requires that bonded reinforcement used as part of the design moment strength be detailed in accordance with the provisions of ACI 318-14, 7.7.3. Such bonded reinforcement provides an independent load path in one-way systems.

All prestressed concrete slabs (Classes U, T, and C) in ACI 318-11 were exempt from the reinforcement spacing limits in ACI 318-11, 7.6.5 (deformed flexural reinforcement spacing to be less than $3h$ and 18 in. [610 mm]). However, this requirement was changed in 7.7.2 of ACI 318-14 for Class C prestressed concrete slabs to make it similar to nonprestressed. Based on field experience with the performance of Class U and Class T unbonded post-tensioned slabs, the maximum spacing of the deformed reinforcement should be limited to six times the slab thickness or 36 in. (910 mm), whichever is less. Extension requirements for