

ACI 549R-18

Report on Ferrocement

Reported by ACI Committee 549



American Concrete Institute
Always advancing



Report on Ferrocement

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Report on Ferrocement

Reported by ACI Committee 549

Antonio Nanni, Chair

Corina-Maria Aldea, Secretary

Nemkumar Banthia
Christian Carloni
Paolo Casadei
Antonio De Luca
Michael E. Driver
Ashish Dubey
Mahmut Ekenel

Brad L. Erickson
Garth J. Fallis
John Jones*
Barzin Mobasher
Hani H. Nassif†
James E. Patterson
Alva Peled

Larry Rowland
Surendra P. Shah
Yixin Shao
Lesley H. Sneed
J. Gustavo Tumialan
Consulting Members
Gordon B. Batson

James I. Daniel
Antoine E. Naaman†
Paul Nedwell†
P. Paramasivam†
Parviz Soroushian

*Chair of subcommittee that prepared this report

†Members of subcommittee that prepared this report.

This report provides an overview of the history, formulation, construction, and applications of ferrocement. The focus of this report is to create an awareness in engineers, architects, and potential end-users of the characteristics and capabilities of ferrocement.

Keywords: compressive strength; construction materials; crack width; ferrocement; fibers; flexural strength; mechanical properties; reinforced concrete; welded wire reinforcement.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 1

- 1.1—Introduction, p. 1
- 1.2—Scope, p. 2

CHAPTER 2—DEFINITIONS, p. 2

CHAPTER 3—HISTORY, p. 2

CHAPTER 4—COMPOSITION AND CONSTRUCTION, p. 4

- 4.1—Basic matrix components, p. 4
- 4.2—Reinforcements, p. 4
- 4.3—Manufacturing techniques, p. 4

CHAPTER 5—FERROCEMENT APPLICATIONS, p. 7

- 5.1—Overview, p. 7
- 5.2—Future trends and potential uses, p. 8

CHAPTER 6—REFERENCES, p. 9

Authored references, p. 10

APPENDIX A—CASE STUDIES, p. 12

- A.1—Yanbu Cement Company, p. 12
- A.2—Apicorp Headquarters roof and soffit panels, p. 15
- A.3—Sustainable Serbian house, p. 19
- A.4—Prefabricated Serbian warehouse/multi-use building, p. 21

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

Ferrocement is a form of reinforced concrete that differs from conventional reinforced or prestressed concrete primarily by the manner in which the reinforcing elements are dispersed and arranged. It consists of closely spaced, multiple layers of mesh or fine rods completely embedded in cementitious mortar. A composite material is formed that behaves differently from conventional reinforced concrete in strength, deformation, and potential applications, and thus is classified as a separate and distinct material. It can be formed into thin panels or sections, mostly less than 1 in. (25 mm) thick, with only a thin mortar cover over the outermost layers of reinforcement. Unlike conventional

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 549R-18 supersedes ACI 549R-97 and was adopted and published January 2018.

Copyright © 2018, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

concrete, ferrocement reinforcement can be assembled into its final desired shape and the mortar plastered directly in place without the use of a form.

The term “ferrocement” implies the combination of a ferrous reinforcement embedded in a cementitious matrix, yet there are characteristics of ferrocement that can be achieved with reinforcement other than steel meshes or rods. The use of nonmetallic mesh is being explored by several researchers around the world (Brameshuber 2015). Such meshes include woven alkali-resistant glass; organic woven fabrics such as polypropylene; and organic natural fabrics made with jute, burlap, or bamboo fibers. Therefore, the term “ferrocement” currently includes material other than steel as reinforcement.

The definition for ferrocement has developed over the years to reflect advances in technology and practice. IFS 10-01 describes it as:

... a type of reinforced concrete commonly constructed of hydraulic cement mortar reinforced with closely spaced layers of relatively small wire diameter mesh. The mesh may be made of metallic or other suitable materials. The fineness of the mortar mixture and its composition should be compatible with the opening and tightness of the reinforcing system it is meant to encapsulate. The matrix may contain discontinuous fibers.

1.2—Scope

This report includes the history, development, and applications of ferrocement together with composition and construction. Appendix A of this report provides several case studies of ferrocement applications.

CHAPTER 2—DEFINITIONS

ACI provides a comprehensive list of definitions through an online resource, “ACI Concrete Terminology.”

CHAPTER 3—HISTORY

The origins of ferrocement can be traced to the work of Jean Louis Lambot who, in 1855, filed a patent for a material he called ferciment (Naaman 2000), which he claimed could replace wood in construction. He made numerous items, including two boats, one of which can be seen in Fig. 3a. Other contemporary researchers were looking at reinforcing of cement-based matrix with metallic reinforcement. Due to the difficulties in producing suitable wire reinforcement, the larger bars became popular and reinforced concrete was produced as we know it today.

Ferrocement, however, had a niche following and became a popular method for constructing boats, as shown in Fig. 3b.

Following the Second World War, Italian architect and engineer Pier Luigi Nervi developed the material for both marine and terrestrial applications with considerable success, as seen in Fig. 3c of his yacht, “Nanelle” (Huxtable 1960). Figure 3d shows an early warehouse and Fig. 3e shows the Turin Exhibition Hall roof. Further development moved to



Fig. 3a—Lambot's boat.




Fig. 3b—Early boat.

New Zealand where there was a thriving boat building and pontoon industry.

In 1972, the National Academy of Sciences, through its Board on Science and Technology for International Development, established the Ad Hoc Panel on the Utilization of Ferrocement in Developing Countries. The report of the panel (National Academy of Sciences 1973) stimulated interest in non-marine applications of this versatile material.

This led directly to the founding of the International Ferrocement Information Center (IFIC) at the Asian Institute of Technology, Bangkok, Thailand, in October 1976. In collaboration with the New Zealand Ferro Cement Marine Association (NZFCMA), the IFIC started publishing a quarterly journal, *The Journal of Ferrocement*. The IFIC developed outreach and training programs, and hosted the Second (Austriaco et al. 1985) and Eighth (Nimityongskul 2006) International Symposia. Unfortunately, through lack of funding, IFIC ceased production of the publication in 2006, and following intensive flooding in 2011, most of the remaining archive has been destroyed. A significant body of work, however, has been gathered from enthusiasts around the world and is held at the University of Manchester in the United Kingdom, where an electronic archive is being created.