

ACI 544.4R-18

# Guide to Design with Fiber-Reinforced Concrete

Reported by ACI Committee 544



American Concrete Institute  
*Always advancing*



## **Guide to Design with Fiber-Reinforced Concrete**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**Phone: +1.248.848.3700**  
**Fax: +1.248.848.3701**

[www.concrete.org](http://www.concrete.org)

# Guide to Design with Fiber-Reinforced Concrete

Reported by ACI Committee 544

Barzin Mobasher\*, Chair  
Neven Krstulovic-Opara, Secretary

Clifford N. MacDonald, Membership Secretary

Corina-Maria Aldea  
Salah Ahmed Altoubat\*  
Emmanuel K. Attiogbe\*  
Mehdi Bakhshi\*  
Nemkumar Banthia  
Joaquim Oliveira Barros\*  
Amir Bonakdar\*†  
Amanda C. Bordelon  
Jean-Philippe Charron  
Xavier Destree\*

Ashish Dubey  
Mahmut Ekenel  
Alessandro P. Fantilli  
Liberato Ferrara\*  
Gregor D. Fischer  
Dean P. Forgeron  
Emilio Garcia Taengua\*  
Rishi Gupta  
Marco Invernizzi  
John Jones

David A. Lange  
Michael A. Mahoney\*  
Bruno Massicotte\*  
James Milligan  
Nicholas C. Mitchell Jr.  
Verya Nasri  
Jeffrey L. Novak\*  
Giovanni A. Plizzari\*  
Klaus Alexander Rieder\*  
Pierre Rossi

Steve Schaeef\*  
Surendra P. Shah  
Flavio de Andrade Silva  
Luca Sorelli  
Gerhard Vitt\*  
Thomas E. West Jr.  
Kay Wille  
Robert C. Zellers

## Consulting Members

P. N. Balaguru  
Hiram Price Ball Jr.  
Gordon B. Batson

Arnon Bentur  
Andrzej M. Brandt  
James I. Daniel

Sidney Freedman  
Christian Meyer  
Antoine E. Naaman\*

Venkataswamy Ramakrishnan

\*Members of the task group that prepared this guide.

†Chair of the task group that prepared this guide.

The committee would like to thank the following for their contribution to this guide: A. Burran, H. Helmink, and A. Lubell.

*New developments in materials technology and the addition of field experience to the engineering knowledge base have expanded the applications of fiber-reinforced concrete (FRC). Fibers are made with different materials and can provide different levels of tensile/flexural capacity for a concrete section, depending on the type, dosage, and geometry. This guide provides practicing engineers with simple, yet appropriate, design guidelines for FRC in structural and nonstructural applications. Standard tests are used for characterizing the performance of FRC and the results are used for design purposes, including flexure, shear, and crack-width control. Specific applications of fiber reinforcement have been discussed in this document, including slabs-on-ground, composite slabs-on-metal decks, pile-supported ground slabs, precast units, shotcrete, and hybrid reinforcement (reinforcing bar plus fibers).*

**Keywords:** crack control; fiber-reinforced concrete; flexural toughness; macrofiber; moment capacity; precast; residual strength; shear capacity; shotcrete; slabs-on-ground; steel fibers; synthetic fibers; tensile strength; toughness.

## CONTENTS

### CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3
- 1.3—Historical aspects, p. 3

### CHAPTER 2—NOTATION AND DEFINITIONS, p. 6

- 2.1—Notation, p. 6
- 2.2—Definitions, p. 7

### CHAPTER 3—CHARACTERISTICS OF FRC, p. 7

- 3.1—Classification of fibers, p. 7
- 3.2—Performance of FRC, p. 8
- 3.3—Standard test methods for FRC, p. 9
- 3.4—Strain softening and strain hardening, p. 10

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 544.4R-18 supersedes ACI 544.4R-88 and was adopted and published July 2018. Copyright © 2018, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

## CHAPTER 4—DESIGN CONCEPTS AND GUIDES, p. 13

- 4.1—Design concepts, p. 13
- 4.2—Tensile stress-strain response for FRC, p. 13
- 4.3—Correlation of tensile and flexural response for FRC, p. 13
- 4.4—Design of RC for flexure (stress block), p. 14
- 4.5—Design of FRC for flexure (ASTM C1609/C1609M, in conjunction with RILEM TC 162-TDF [2003]), p. 14
- 4.6—Design of FRC for flexure (Model Code 2010 [*fib* 2013]), p. 15
- 4.7—Design of FRC for flexure-hybrid reinforcement, p. 16
- 4.8—Design of FRC for shear, p. 17
- 4.9—Parametric-based design for FRC, p. 18

## CHAPTER 5—DESIGN FOR SPECIFIC APPLICATIONS, p. 21

- 5.1—Slabs-on-ground, p. 21
- 5.2—Extended joint spacing, p. 23
- 5.3—Elevated floors/slabs-on-piles, p. 24
- 5.4—Composite steel decks, p. 24
- 5.5—Precast units, p. 25
- 5.6—Shotcrete, p. 26
- 5.7—Crack control and durability, p. 27

## CHAPTER 6—CONSTRUCTION PRACTICES, p. 28

- 6.1—Mixture design recommendations for FRC, p. 28
- 6.2—Workability of FRC, p. 28
- 6.3—Adding and mixing fibers, p. 28
- 6.4—Placing, consolidation, and finishing FRC, p. 28
- 6.5—Quality control for FRC, p. 30
- 6.6—Contraction (control) joints, p. 30
- 6.7—Specifying FRC, p. 30

## CHAPTER 7—REFERENCES, p. 30

Authored references, p. 31

## APPENDIX—SOLVED EXAMPLE PROBLEMS FOR SECTION 4.9—PARAMETRIC BASED DESIGN FOR FRC, p. 34

Case A: Calculation of the moment capacity of a given section, p. 34

Case B: Calculation of  $\mu$  based on parametric-based design for FRC (ACI 544.8R), p. 36

Case C: Calculation of  $\mu$  for the replacement of reinforcement in a singly reinforced slab (ACI 544.8R), p. 37

## CHAPTER 1—INTRODUCTION AND SCOPE

### 1.1—Introduction

The aim of this guide is to provide practicing engineers with design guidelines and recommendations for fiber reinforcement. Several approaches for designing fiber-reinforced concrete (FRC) have been developed over the years that are based on conventional design methods modified by special procedures to account for contributions of the fibers. These methods generally modify the internal forces in the member to account for the additional tensile capacity

provided by the fibers. When compared with full-scale test data, these methods have provided satisfactory designs for FRC members (Parra-Montesinos 2006; Moccichino et al. 2006; Altoubat et al. 2009).

Concrete is a brittle material that is strong in compression but weak in tension. Steel bars are traditionally used to carry the tensile forces after concrete has cracked in structural applications. In reinforced concrete, the tensile strain of the concrete at cracking is much lower than the yield strain of the steel bars, which results in cracking of concrete before any significant load is transferred to the steel. Steel reinforcement is also used to limit the crack widths under specified levels for serviceability requirements. Unlike reinforcing bars, fibers are uniformly distributed in the volume of concrete; hence, the distance between fibers is much smaller than the spacing between bars. Fibers can provide post-crack tensile and flexural capacity and crack-width control in concrete elements.

Natural sources of reinforcement were used for brittle construction materials more than 3000 years ago, such as straw reinforcement in mud bricks. The first scientific studies on the use of steel fibers in concrete date back to the 1960s (Romualdi and Batson 1963; Naaman and Shah 1976). Since then, thousands of projects have been successfully completed using fiber reinforcement, including slabs-on-ground, composite steel decks, slabs-on-pile, precast, and shotcrete.

The major differences in the proposed methods are in the determination of the increase in tensile capacity of concrete provided by the fibers and the manner in which the total force is calculated. A conservative but justifiable approach in structural members such as beams, columns, walls, or elevated suspended slabs is that reinforcing bars should be used to support the total tensile loads. ACI 544.6R, however, describes the design for elevated suspended slabs where steel fibers are used as the primary reinforcement along with a minimum of continuous bars from columns to columns. Fibers can be used, in general, to supplement and reduce the reinforcing bars in various structural members. In applications where the presence of continuous reinforcement is not essential to the safety and integrity of the structure such as slabs-on-ground, pavements, overlays, shotcrete linings, slabs-on-piles (ACI 544.6R), and some precast units, fibers may be used as the sole means of reinforcement.

Fibers reliably control cracking and improve material resistance to deterioration as a result of fatigue, impact, and shrinkage, or thermal stresses. Fibers can contribute to the improved performance of concrete members in two ways: 1) by resisting the tensile stresses and, therefore, playing a structural role; or 2) by controlling crack development and, therefore, improving the durability of concrete. When fibers are intended to contribute to the structural performance of an element or structure, the FRC should be designed accordingly and the fiber contribution to the load-bearing capacity should be properly assessed and justified.

The commercial momentum for using steel fibers occurred during the 1970s for industrial floors as a major application. Other applications for steel fibers include composite metal

deck, pile-supported slabs, precast units, and shotcrete. Synthetic macrofibers became available in the 1990s with applications such as slabs-on-ground, composite decks, pavements, shotcrete, and some precast units. Steel fibers and synthetic macrofibers can be viable alternatives for full replacement of steel bars in concrete elements with continuous support such as slabs-on-ground or shotcrete. For free-standing elements such as suspended slabs and tunnel lining segments, steel fibers at medium to high dosages have been shown to successfully replace a large portion of steel bars in the section (ACI 544.6R; ACI 544.7R).

The term “fibers” in this document only concerns macrofibers made of steel and polymeric (polyolefin) synthetic materials; hence, the design guides are not applicable to microfibers. Fiber diameter of 0.012 in. (0.3 mm) is the defining limit between microfibers and macrofibers. Synthetic microfibers have been used in concrete since the 1970s and are solely intended to control plastic shrinkage cracks (and sometimes drying shrinkage cracks) without any significant improvement in the mechanical properties of hardened concrete (ACI 360R). They may also affect the bleeding rate of fresh concrete, improving the near-surface properties of the hardened concrete. These fibers have been used to reduce the spalling of concrete exposed to fire and explosion.

When macrofibers are used in concrete to replace steel reinforcement, they can provide enhanced ductility, toughness, and durability. Fiber dosage can be engineered to provide a desired level of crack control, post-crack tensile and flexural capacity, or both. Similar to steel bars for which the size and spacing are calculated to provide the required reinforcement ratio, the dosage of fibers is also calculated to satisfy engineering requirements. Parameters affecting the performance of FRC include fiber type (material, size, and geometry), as well as bond characteristics and concrete mixture design. Fiber dosage may be limited by the practicality of their use in concrete; however, chemical admixtures are widely used for incorporating higher dosages of fibers. In certain applications, especially with congested steel bars, hybrid reinforcement (steel bars plus fibers) can be a viable alternative to conventional reinforcement. Using FRC may allow for applying alternative construction techniques—for example, tailgating concrete instead of pumping it for slabs-on-ground when steel reinforcement is eliminated. This can help in scheduling the project, resulting in a more cost-effective construction. Improved job-site safety is also among the benefits of using fibers from the reduced handling or tripping over the reinforcement at the job site. Using fibers can additionally eliminate the problems caused by misplacing conventional steel at its design position. The durability aspects of FRC and the associated benefits from fibers are extensively presented in ACI 544.5R.

## 1.2—Scope

Although FRC has been used since the 1960s, there are no agreed design approaches in North America for some of its applications. Unlike reinforced concrete with steel bars or welded wire mesh, the design of fiber reinforcement is not

properly covered by national design codes. In Model Code 2010 (*fib* 2013), sections were added for new developments in the design of FRC as a part of the building code. ACI 318 has limited discussion on the use of fibers, such as provisions for using steel fibers as shear reinforcement in flexural members. ACI 360R presents the basics of fiber-reinforced slabs-on-ground, and ACI 506.1R discusses the design and application of fiber-reinforced shotcrete. It is the intent of this document to provide practicing engineers with simple yet appropriate design guidelines and state-of-the-art applications for FRC. This guide is intended for designers who are familiar with structural concrete containing conventional steel reinforcement, but who may need more guidance on the design and specification for FRC. In this document, fibers are treated as reinforcement in concrete and not as an admixture.

This guide discusses the types and typical dosages for fibers, general material properties, and available test methods for characterization of FRC. Explaining the design concepts and existing guidelines for fiber reinforcement is the focus of this document, including constitutive laws, design for flexure, design for shear, and design for crack-width control. This is further extended to specific applications for slabs-on-ground, composite slabs-on-metal decks, pile-supported ground slabs, precast units, shotcrete, and special applications. The final portion of this guide provides brief recommendations for specifying and building with FRC that includes general guidelines for mixing, placing, and finishing.

Although there are several types of fibers commercially available, this document is only applicable to steel fibers and polyolefin synthetic macrofibers that comply with ASTM C1116/C1116M. The formulas and applications discussed in this document should be verified for any other types of fibers. This document provides design guidelines based on the mechanical and structural properties of FRC as a composite material and not individual fiber products. Different fiber products may exhibit different performances in concrete; hence, it is crucial to design and specify FRC properties in addition to fiber types and materials that are suitable to achieve such properties.

## 1.3—Historical aspects

**1.3.1 Introduction**—Prior to presenting test methods, design philosophies, and applications of FRC, it is beneficial to review some of the historical aspects of this technology. This section summarizes the historical background of FRC since its development, including the mechanical characterization, analytical modeling, and test methods. Some of the earlier design and analysis guides addressing FRC during the 1970s and 1980s are discussed in Hoff (1982), ACI SP-44, SP-81, SP-105, and Shah and Skarendahl (1986). It should be noted that most of the earlier studies and applications of FRC incorporated steel fibers only.

**1.3.2 Mechanical characteristics and modeling**—Understanding the mechanical properties of FRC and their variation with fiber type and dosage is an important aspect of successful design. Fibers influence the mechanical properties of concrete in all failure modes, including compression,