

ACI 211.9R-18

Guide to Selecting Proportions for Pumpable Concrete

Reported by ACI Committee 211



American Concrete Institute
Always advancing



Guide to Selecting Proportions for Pumpable Concrete

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

www.concrete.org

Guide to Selecting Proportions for Pumpable Concrete

Reported by ACI Committee 211

Gary F. Knight, Chair

Timothy S. Folks, Vice Chair

Ed T. McGuire, Secretary

William L. Barringer
Katie J. Bartojay
Muhammed P. A. Basheer
James C. Blankenship
Casimir J. Bognacki
Ramon L. Carrasquillo
Bryan R. Castles
Teck L. Chua
John F. Cook
David A. Crocker
D. Gene Daniel

Kirk K. Deadrick
Donald E. Dixon
Bernard J. Eckholdt III
Darrell F. Elliot
David W. Fowler
G. Terry Harris
Richard D. Hill
David L. Hollingsworth
Said Irvani
Tarif M. Jaber
Robert S. Jenkins

Joe Kelley
Eric P. Koehler
Frank A. Kozeliski
Tyler Ley
Darmawan Ludirdja
Allyn C. Luke
Kevin A. MacDonald
Warren E. McPherson Jr.
Karthik H. Obla
H. Celik Ozyildirim
James S. Pierce

Steven A. Ragan
Royce J. Rhoads
John P. Ries
G. Michael Robinson
James M. Shilstone Jr.
Ava Shypula
Woodward L. Vogt
Michael A. Whisonant

Subcommittee Members

Yasar Yahia Abualrous
David Anstine
Dale P. Bentz
Zane Bussler
Laurence M. Clodic
Kenneth W. Day

Dimitri Feys
Patrick J. Harrison
Plinio Estuardo Herrera
Gene Hightower
Berndt Kanduth
Kenneth G. Kazanis

Guy Lortie
Blaine B. Nye
Bryan L. Petty
Nicholas J. Popoff
Domenick Thomas Ruttura
Lawrence L. Sutter

Paul D. Tennis
Paul J. Thomas
James R. Van Acker
Hermann W. Wentz

Consulting Member

James N. Lingscheit

The committee would like to thank J. Bury for his contribution to this guide.

This guide addresses methods for selecting proportions for hydraulic-cement concrete placed by pumping. Specific numerical guidelines are given as applicable to mixture component proportions that lead to the most efficient concrete pumping results. Comments are also included in this guide on how pumping affects the supplied concrete and how the proportions affect the concrete's pumpability. This guide complements ACI 304.2R and is also intended as a supplement to ACI 211.1 and ACI 211.2.

The mass of an object is defined as the amount of matter that is present. Mass is independent of any other property; weight is the force arising from specific gravitational field or other acceleration acting on a mass. The weight is thus dependent on both the mass and the acceleration due to gravity rotation. In the common engineering system, a pound of mass is accelerated by gravity to be 1 lb of force. There is no need for distinction, and mass and weight are often used interchangeably in that the numerical values are the same. A mass of 1 lb exerts a weight of 1 lb. There is a hidden gravitational constant. In the SI system, mass is expressed in grams and weight in Newtons. A mass of 1 kg exerts a weight of 9.81 N. It is correct, therefore, to use the term "mass" when determining how much material is being loaded into the plant, and when the mixtures are designed and proportioned. The industry, however, conventionally uses weight for these items. In the common measurement system, this creates no confusion. Thus, the vernacular term for the massing

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 211.9R-18 was adopted and published August 2018.

Copyright © 2018, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

elements of the concrete plant is the weigh hopper. The batch record showing masses of materials in the concrete mixture are collectively referred to as batch weights. In an acknowledgement of this widespread industry practice, and to make the document as widely useable as possible, the term “weight” is used throughout to represent mass in the text. This is technically incorrect but is in line with common practice. In all conversions, both mass and weight are given (kilograms and Newtons).

Keywords: admixtures; aggregate; cementitious material; concrete mixture design; fiber; grading; fineness modulus; lightweight aggregate; mass concrete; normalweight aggregate; pumpability; unit weight.

CONTENTS

CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 2

CHAPTER 2—DEFINITIONS, p. 2

CHAPTER 3—AGGREGATE GRADING, p. 2

- 3.1—Considerations, p. 2
- 3.2—Normalweight aggregate, p. 2
- 3.3—Lightweight aggregate, p. 4

CHAPTER 4—CEMENTITIOUS MATERIALS, p. 7

- 4.1—General, p. 7

CHAPTER 5—WATER, p. 7

- 5.1—General, p. 7

CHAPTER 6—ADMIXTURES, p. 7

- 6.1—General, p. 7
- 6.2—Admixture types, p. 7

CHAPTER 7—FIBER REINFORCEMENT, p. 8

CHAPTER 8—TRIAL MIXTURES AND PUMPABILITY TESTING, p. 8

CHAPTER 9—REFERENCES, p. 8

- Authored documents, p. 8

CHAPTER 1—INTRODUCTION AND SCOPE

1.1—Introduction

As construction projects grow more sophisticated, concrete placement by pumps has become one of the most widely used practices in construction. To meet the demand of the industry, concrete mixture proportions need to be designed considering pumpability requirements. However, when proportioning a mixture, pumpability is only one of several factors. Because hardened properties determine the durability and serviceability of concrete, the professional responsible for design of concrete mixtures should also consider exposure conditions, strength, curing characteristics, flowability, sustainability, delivery, and placement. In some cases, where these are in direct conflict, a compromise or

alternative solution is required. Given the prevalence and benefits of placement by pumping, it is sometimes critical to certain applications that the components and their mixture proportions be designed with consideration to pumpability. The extent to which attention should be given to the components and proportions in a mixture depends on the application and equipment being used.

1.2—Scope

This guide addresses methods for selecting proportions specific to hydraulic-cement concrete to be placed by pumping. The primary focus of this document is to discuss the principles of mixture proportioning for normalweight and lightweight concrete. Any specific information regarding pumping equipment and field practices are covered elsewhere (ACI 304.2R). The methods provided for selecting proportions for hydraulic cement begin with an approximation of the proportions intended to be checked by trial batches in the laboratory or field, which will then be adjusted as necessary to produce the desired pumpability characteristics while confirming it meets the other performance requirements such as durability and strength. Selection of the mixture proportions should be done by considering both fresh and hardened properties required for a given application. The size of the pump and pump line should be evaluated to accommodate the volume of coarse aggregates and nominal maximum aggregate size used in the mixture. This guide does not address slump because concrete of all slumps and slump flows can be successfully pumped, provided the proper equipment and mixture proportions are used. Slump or slump flow should meet other project and application requirements, as discussed in ACI 211.1.

CHAPTER 2—DEFINITIONS

Please refer to the latest version of “ACI Concrete Terminology” for a comprehensive list of definitions.

CHAPTER 3—AGGREGATE GRADING

3.1—Considerations

Quality concrete proportioning begins with the appropriate combined aggregate grading. This is also true for pumpable concrete. Consistency in grading promotes consistency in the pumpability of any mixture. Thus, aggregate grading should be monitored and blends adjusted when required to assure consistency in the combined aggregate grading.

3.2—Normalweight aggregate

3.2.1 Coarse normalweight aggregate—The nominal maximum size (NMS) of coarse aggregate is limited to one-third of the smallest inside diameter of the pipeline. The NMS required should be specified and provisions made for the elimination of oversized particles in the concrete by use of finish screening (ACI 304R; ASTM C33/C33M) or by careful selection of coarse aggregate.

The NMS has a significant effect on the volume of coarse aggregate that may be efficiently used. The quantity of coarse aggregate should be reduced as the NMS is reduced