

ACI 239R-18

# Ultra-High-Performance Concrete: An Emerging Technology Report

Reported by ACI Committee 239

*Emerging Technology Series*



American Concrete Institute  
*Always advancing*



## **Ultra-High-Performance Concrete: An Emerging Technology Report**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**Phone: +1.248.848.3700**  
**Fax: +1.248.848.3701**

[www.concrete.org](http://www.concrete.org)

# Ultra-High-Performance Concrete: An Emerging Technology Report

Reported by ACI Committee 239

Theresa M. Ahlborn, Chair

Charles Kennan Crane\*, Secretary

Claus Brix  
Eckart R. Buhler  
Dominique Corvez  
Ashish Dubey  
Sidney Freedman

Benjamin Graybeal  
Brian H. Green  
Katrin Habel  
William M. Hale  
Fred Meyer

James Milligan  
John J. Myers  
Vic Perry  
Carin L. Roberts-Wollmann  
Bjarne Roursgaard

Surendra P. Shah  
Kay Wille

## Subcommittee 239-A

Sriram R. Aaleti  
Jon S. Belkowitz

Devin K. Harris  
Robert Moser

Eric P. Steinberg  
Charles A. Weiss Jr.

\*Chair of Subcommittee 239-A.

## Consulting Members

James K. Hicks

Antoine E. Naaman

Larry Rowland

*ACI encourages the development and appropriate use of new and emerging technologies through the publication of Emerging Technology Reports. These documents present information and recommendations based on available test data, technical reports, limited experience with field applications, and the opinions of committee members. The presented information and recommendations, and their basis, may not be as extensively developed and tested as those for more mature technologies. This report identifies areas in which information is believed to be less fully developed and describes related research needs. The professional using this document should understand the limitations of this document and exercise judgment as to the appropriate application of this emerging technology.*

*This emerging technology report gives an overview of ultra-high-performance concrete. It briefly introduces the production of these concretes, their properties, design principles for their use, and example applications. It is not intended to be an exhaustive document, but rather to serve as a starting point for the concrete practitioner on understanding this class of materials.*

**Keywords:** applications; ductility; durability; fiber-reinforced concrete; ultra-high-performance concrete.

## CONTENTS

### CHAPTER 1—INTRODUCTION AND SCOPE, p. 2

- 1.1—Introduction, p. 2
- 1.2—Scope, p. 3

### CHAPTER 2—DEFINITIONS, p. 3

- 2.1—Definitions, p. 3

### CHAPTER 3—PRODUCTION, p. 3

- 3.1—Materials, p. 3
- 3.2—Mixture proportioning, p. 3
- 3.3—Mixing, p. 3

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

ACI 239R-18 was adopted and published October 2018.

Copyright ©2018, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 3.4—Placement, p. 4
- 3.5—Curing, p. 5

## CHAPTER 4—CONCRETE PROPERTIES, p. 5

- 4.1—Early-age and time-dependent properties, p. 5
- 4.2—Mechanical properties, p. 5
- 4.3—Durability, p. 7

## CHAPTER 5—STRUCTURAL DESIGN OF UHPC COMPONENTS, p. 7

- 5.1—Design principles, p. 7
- 5.2—Structural design guidance for UHPC, p. 8
- 5.3—Structural research needs, p. 8

## CHAPTER 6—APPLICATIONS, p. 9

- 6.1—Highway bridges, p. 9
- 6.2—Pedestrian bridges, p. 9
- 6.3—Seismic retrofit, p. 10
- 6.4—Rehabilitation, p. 10
- 6.5—Piles/foundations, p. 12
- 6.6—Field-cast connections, p. 12
- 6.7—Safety and security, p. 14
- 6.8—Spent nuclear fuel storage, p. 14
- 6.9—Facades, p. 15
- 6.10—Impact resistance, p. 15
- 6.11—Aggressive environments, p. 16
- 6.12—Canopies/shells, p. 17

## CHAPTER 7—CONCLUSIONS, p. 18

## CHAPTER 8—REFERENCES, p. 18

Authored documents, p. 18

### CHAPTER 1—INTRODUCTION AND SCOPE

Ultra-high-performance concrete (UHPC) is a class of advanced cementitious materials with greater strength, tensile ductility, and durability properties when compared to conventional or even high-performance concrete. For the purposes of this document, UHPC is limited to concrete that has a minimum specified compressive strength of 22,000 psi (150 MPa) with specified durability tensile ductility and toughness requirements; fibers are generally included to achieve specified requirements. UHPC typically exhibits elastic-plastic or strain-hardening characteristics under uniaxial tension and has a very low permeability due to its dense and discontinuous pore structure.

#### 1.1—Introduction

UHPC typically consists of cement; silica fume; fine quartz sand; high-range water-reducing admixtures; and fibers with water-binder ratios ( $w/b$ ) usually ranging between 0.15 and 0.25. However, multiple variations of UHPC matrixes have been developed that contain other supplementary cementitious materials and sometimes coarse aggregate. Alternate formulations often make trade-offs to achieve enhancement of one property that may negatively impact others. The main characteristics of UHPC are achieved through the following three principles (Richard and Cheyrezy 1995):

1. Homogeneity enhancement by eliminating coarse aggregates in the matrix
2. Density enhancement by optimizing the packing density of the matrix; this is achieved through optimizing gradation and mixture proportions between the main matrix constituents
3. Ductility enhancement by introduction of fibers. As the matrix is very brittle, fiber reinforcement is added to obtain elastic-plastic or strain-hardening behavior in tension. Typically, UHPC has fiber contents of 2 percent or more by volume. The maximum fiber content is a function of the fiber aspect ratio and fiber shape as well as production issues such as workability.

UHPC development originated with studies on high-strength cement pastes with low water-cementitious materials ratios ( $w/cm$ ) of 0.20 to 0.30 by Yudenfreund et al. (1972a,b,c), Odler et al. (1972a,b), and Brunauer et al. (1973a,b). These pastes had low porosity leading to compressive strengths up to 29 ksi (200 MPa) and low dimensional changes. Strength enhancement by hot pressing techniques was first applied by Roy and Gouda (1973) and Roy et al. (1972) and resulted in very-high-strength cement pastes with compressive strengths up to 98 ksi (680 MPa). With the development of high-range water-reducing admixtures and pozzolanic admixtures such as silica fume, two kinds of materials emerged in the 1980s. Polymer-modified cementitious materials called macro-defect-free (MDF) concretes had a compact matrix but were susceptible to deterioration by water and had high creep due to the presence of certain polymers (Kendall et al. 1983; Alford and Birchall 1985). Densified systems containing homogeneously arranged ultrafine particles (DSP) used the interaction of high-range water-reducing admixtures and silica fume to decrease the porosity of the material and to increase the strength. DSP still exists and was the basis for modern UHPC development (Bache 1987). The density of the matrix of UHPC mixtures was theoretically investigated and optimized (de Larrard and Sedran 1994). The brittleness of the matrixes was recognized, and various combinations of steel and synthetic fibers were used to increase ductility of the materials (Richard and Cheyrezy 1995; Bache 1987).

The first commercial applications of UHPC started in the 1990s in Europe and has spread worldwide. Several major research programs on UHPC have been carried out worldwide, such as early research in France and Japan, resulting in code-style guidelines (AFGC 2002; Japanese Society of Civil Engineers 2008), a large federally funded program in Germany (Schmidt 2008), as well as several research programs in Canada and the United States (Russell and Graybeal 2013; Graybeal 2011). UHPC has been used in multiple applications such as bridges and infrastructure, facades, buildings, elements in aggressive environments, and for security and blast resistance. Applications include new construction and rehabilitation using both cast-in-place and precast UHPC components. UHPC in its present form became commercially available in North America in approximately 2000.

## 1.2—Scope

UHPC is still in the process of finding a broader use. The objective of this report is to introduce UHPC through a brief overview of production, properties, design, and applications, and to promote further use of UHPC and integration into today's construction market. Because the cost of UHPC is high when compared to conventional concrete, use should be focused toward applications that engage several of the exceptional properties of the material. Current research needs have been identified as improved design guidance, standardization, and broader material knowledge.

## CHAPTER 2—DEFINITIONS

### 2.1—Definitions

Please refer to the latest version of ACI Concrete Terminology for a comprehensive list of definitions. Definitions provided herein complement that resource.

**conventional concrete**—concrete that has a specified compressive strength for design of less than 8000 psi (55 MPa).

**strain hardening**—ability to carry increasing tensile load beyond the point of first crack.

**strain softening**—ability to carry a reduced (but non-zero) tensile load beyond the point of first cracking.

**ultra-high-performance concrete**—concrete that has a minimum specified compressive strength of 22,000 psi (150 MPa) with specified durability tensile ductility and toughness requirements; fibers are generally included to achieve specified requirements.

## CHAPTER 3—PRODUCTION

### 3.1—Materials

The materials used to make ultra-high-performance concrete (UHPC) are similar to those commonly found in traditional concrete. Constituent materials are selected based on their particle size to optimally pack the matrix to reduce voids between the particles. While some commercially available UHPC mixtures are proprietary, with their exact composition not reported, other mixture compositions are readily available. Some mixtures feature less common components such as silica flour, which is silica sand ground to achieve a specific particle size. The addition of high-strength steel fibers to the matrix results in improved ductility and the ability to eliminate some of the mild steel reinforcement normally found in conventional reinforced concrete members (Graybeal 2006a).

### 3.2—Mixture proportioning

The high strengths and superior performance achieved with UHPC stem from the reduction of void space in the matrix and discontinuous pore structure, depending more on the material's behavior on a microscopic level than on the properties of its constituent components. Through the proper selection of components based on both their particle size and mechanical properties, the number of contact points between particles is increased, which in turn causes the level of stress transferred between particles through the paste to be reduced

**Table 3.2—Two possible UHPC mixture proportions by mass**

UHPC component	Mixture Proportion 1	Mixture Proportion 2
Cement	1	1
Silica fume	0.325	0.389
Sand	1.432	0.967
Quartz powder/silica flour	0.300	0.277
High-range water-reducing admixture	0.027	0.017
Water	0.280	0.208
Steel fibers	0.200	0.310

Note: Mixture Proportion 1 is from Bonneau et al. (1996). Mixture Proportion 2 is from Williams et al. (2009).

and less variable. This reduction and more even distribution of forces alleviates the formation of microcracks in the matrix and ultimately results in improved mechanical properties. Table 3.2 depicts two representative mixture proportions for UHPC and demonstrates how the mass proportions can vary based on the particle sizes.

The matrix of UHPC is optimized for particle packing, that is, the mixture proportions of typical components such as sand, silica fume, and cement are optimized to achieve the densest packing possible, as investigated by de Larrard and Sedran (1994). Another unique aspect of UHPC is that some cementitious material particles may not take part in the hydration process, but merely serve as fine aggregate in the overall matrix. It is common for 30 to 50 percent of the cement to be hydrated in UHPC due to the low water content (Morin et al. 2001; Habel et al. 2006).

### 3.3—Mixing

UHPC has been produced using a wide variety of mixers, ranging from laboratory-sized pan mixers to revolving drum truck mixers. Mixing UHPC, in general, is a somewhat different process than mixing conventional concrete. UHPC typically includes a limited amount of water and little, if any, coarse aggregate. As such, the UHPC requires the input of extra mixing energy both to disperse the water and to overcome the low internal mixing action from the lack of coarse aggregate. A typical mixing process involves first charging the mixer with the dry components and ensuring that they are fully blended. Thereafter, the water and the liquid admixtures are added and dispersed. Mixing continues, sometimes for an extended period depending on the mixer energy input, until the UHPC changes from a dry powder into a fluid mixture. Once fluid, the fiber reinforcement (if included) is added in a deliberate manner to ensure uniform distribution through the mixture without agglomeration. After fiber dispersion, the mixing is complete and the UHPC is ready for discharge. Higher-energy shear mixers can produce UHPC in a few minutes, whereas lower-energy drum mixers could easily require 20 minutes or more to appropriately distribute the constituents and produce a fluid mixture. Care should be taken to ensure that the mixing process does not greatly increase the temperature of the UHPC, as this can