



©2018 NACE International, 15835 Park Ten Place, Suite 200, Houston TX 77084, USA. All rights reserved. Reproduction, republication or redistribution of this standard in any form without the express written permission of the publisher is prohibited. Contact NACE International by means of our website www.nace.org, email FirstService@nace.org, or (phone) 281-228-6223 for reprints of this standard.

NACE Publication 01101
Item Number 24214
ISBN #1-57590-386-5
Reaffirmed February 2018
Approved May 2001

NACE Publication 01101

Electrochemical Chloride Extraction from Steel-Reinforced Concrete— A State-of-the-Art Report

This NACE International (NACE) technical committee report represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone from manufacturing, marketing, purchasing, or using products, processes, or procedures not included in this report. Nothing contained in this NACE report is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by letters patent, or as indemnifying or protecting anyone against liability for infringement of letters patent. This report should in no way be interpreted as a restriction on the use of better procedures or materials not discussed herein. Neither is this report intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this report in specific instances. NACE assumes no responsibility for the interpretation or use of this report by other parties. Users of this NACE report are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this report prior to its use. This NACE report may not necessarily address all potential health and safety problems or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this report.

Users of this NACE report are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this report.

CAUTIONARY NOTICE: The user is cautioned to obtain the latest edition of this report. NACE reports are subject to periodic review, and may be revised or withdrawn at any time without prior notice. NACE reports are automatically withdrawn if more than 10 years old. Purchasers of NACE reports may receive current information on all NACE International publications by contacting the NACE *FirstService* Department, 15835 Park Ten Place, Houston, Texas 77084-5145 (telephone +1 281-228-6200 or email firstservice@nace.org).

NACE International
15835 Park Ten Place
Houston, Texas 77084-5145
+1 281-228-6200

© 2018 NACE International

Foreword

NACE technical committee reports are intended to convey technical information or state-of-the-art knowledge regarding corrosion. In many cases, they discuss specific applications of corrosion mitigation technology, whether considered successful or not. Statements used to convey this information are factual and are provided to the reader as input and guidance for consideration when applying this technology in the future. However, these statements are not intended to be recommendations for general application of this technology, and must not be construed as such.

The purpose of this NACE technical committee report is to present state-of-the-art information on electrochemical chloride extraction (ECE) from conventionally reinforced concrete surfaces. Included are discussions of common industry practices used by design engineers to control corrosion of reinforcing steel in portland cement concrete structures through the application of ECE.

This report is intended for use by engineers attempting to protect corroding reinforced concrete structures by the use of electrochemical treatment techniques. The information presented in this report is limited to ECE for atmospherically exposed reinforced concrete and is not applicable to prestressed or post-tensioned elements or concrete containing epoxy-coated reinforcing steel, galvanized steel, or other coated or nonferrous reinforcement.

This report, focusing on electrochemical chloride extraction, is Part I of a two-part series. Part II is intended to focus on the realkalization of carbonated concrete structures.

This technical committee report was originally prepared in 2001 by Task Group (TG) 054, "Electrochemical Chloride Extraction and Realkalization of Reinforced Concrete."⁽¹⁾ In 2018, it was reaffirmed by TG 920. It is issued by NACE under the auspices of administrative Specific Technology Group (STG) 01, "Reinforced Concrete."

⁽¹⁾ Chair John Broomfield, Consulting Corrosion Engineer, London, UK.

Introduction

Reinforced concrete is a versatile and widely used construction material. Its excellent performance and durability rely on the compatibility of the steel with the concrete surrounding it and the ability of the concrete to protect the steel from corrosion in most circumstances.

Unfortunately, corrosion protection is not guaranteed, and can fail if sufficient chlorides (usually in the form of sea salt, deicing salt, or chloride contamination of the original mix) or atmospheric carbon dioxide (CO₂) penetrate the concrete and break down the passive layer that protects the steel. This breakdown of the passive oxide layer leads to corrosion of the reinforcing steel if sufficient oxygen and water are available. Corrosion generally leads to the formation of a high-volume corrosion product that cracks the concrete leading to spalling of the cover zone, directly exposing the steel to the corrosive atmosphere. If untreated, corrosion leads to structural failure.

Regardless of the cause of depassivation (chlorides or carbonation), corrosion occurs by the movement of electrical charge from an anode (an area of steel where steel is dissolving) to the cathode (an area of steel where a charge-balancing reaction occurs, turning oxygen and water into hydroxyl ions). This means that the process is both electrical and chemical, i.e., electrochemical. In the case of chloride attack, patch repairs are only a local solution to corrosion, and repairing an anode can accelerate corrosion in adjoining areas.

One solution to this problem involves applying an electrochemical treatment that suppresses corrosion. Figure 1 shows the basic components of an electrochemical treatment system. The components are a direct current (DC) power source and an anode (temporary or permanent), usually distributed across the surface of the concrete. Electrochemical methods work by applying an external anode and passing current from it to the reinforcing steel so that all of the steel becomes a cathode.

Three electrochemical techniques are used to counter corrosion of steel in concrete. The first of these techniques is cathodic protection (CP). A newer alternative for chloride-contaminated structures is electrochemical chloride extraction (ECE), also known as electrochemical chloride removal (ECR), or desalination, as the process is called in Europe. A method for treating carbonated concrete has been developed and is gaining rapid acceptance as a rehabilitation method for carbonation in buildings and other structures. This is known as realkalization.

Chloride removal was the subject of two major studies conducted under Federal Highway Administration⁽²⁾ (FHWA) contracts in the 1970s.^{1,2} Both of these studies, as well as follow-up reports, concluded that chloride removal by electrochemical migration is a promising technique for use on chloride-contaminated concrete.




Figure 1: Schematic Diagram of Electrochemical Treatment System

Further research was undertaken in Norway by a private company, and under the Strategic Highway Research Program⁽³⁾ (SHRP) in the U.S. As a result of that research, a number of patents were published. Some of the principal U.S. patents directly relating to ECE are listed in the bibliography. The list is not comprehensive, can include expired patents, and does not include patents from other countries.

⁽²⁾ Federal Highway Administration (FHWA), 1200 New Jersey Ave, SE, Washington, DC 20590.

⁽³⁾ Strategic Highway Research Program (SHRP), Transportation Research Board, 500 Fifth St., NW, Washington, DC 20001.