

ACI 548.6R-19

# Polymer Concrete: Guidelines for Structural Applications

Reported by ACI Committee 548



American Concrete Institute  
*Always advancing*



## **Polymer Concrete: Guidelines for Structural Applications**

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. In spite of these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations with regard to health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

Order information: ACI documents are available in print, by download, through electronic subscription, or reprint and may be obtained by contacting ACI.

Most ACI standards and committee reports are gathered together in the annually revised the ACI Collection of Concrete Codes, Specifications, and Practices.

**American Concrete Institute**  
**38800 Country Club Drive**  
**Farmington Hills, MI 48331**  
**Phone: +1.248.848.3700**  
**Fax: +1.248.848.3701**

[www.concrete.org](http://www.concrete.org)

# Polymer Concrete: Guidelines for Structural Applications

Reported by ACI Committee 548

Mahmoud M. Reda Taha, Chair

Ashraf I. Ahmed  
 Mohammad A. Alhassan  
 Jacques A. Bertrand  
 Constantin Bodea  
 Chris Davis  
 Don Edwards

David W. Fowler  
 Quentin L. Hibben  
 Albert O. Kaeding  
 Jay Lee  
 John R. Milliron  
 Myles A. Murray

Bradley Nemunaitis  
 Joseph A. Nuciforo Jr.  
 John R. Robinson  
 Michael L. Schmidt  
 Joseph R. Solomon  
 Michael M. Sprinkel

Michael S. Stenko  
 Donald P. Tragianese  
 Wafeek S. Wahby  
 David White

## Consulting Members

Milton D. Anderson  
 Lu Anqi  
 Craig A. Ballinger  
 John J. Bartholomew  
 Shashi P. Bhatnagar  
 Jerry D. Byrne  
 Zhi-Yuan Chen

Lech Czarnecki  
 Harold (Dan) R. Edwards  
 Larry J. Farrell  
 George Horeczko  
 David P. Hu  
 Bert Paul Kriekemans  
 Deon Kruger

William Lee  
 Troy D. Madeley  
 Henry N. Marsh Jr.  
 Peter Mendis  
 Peter J. Moss  
 Yoshihiko Ohama  
 Kelly M. Page

Hamid Saadatmanesh  
 Donald A. Schmidt  
 Meyer Steinberg  
 Harold H. Weber Jr.

## Subcommittee 548B

Aly Said

*Polymer concrete (PC) can be used in the construction of structural elements with applications, including wall panels withstanding wind and seismic loads, underground vaults resisting lateral earth pressure, vault and utility box covers resisting vehicle loads, and railroad ties resisting static and dynamic rail loads. PC structural elements are used to resist bending moments and axial and shear loads. Creep, fatigue, and service temperature are important aspects for PC structural elements. These guidelines help the defining and understanding of mechanical properties and structural behavior of PC. Industrial standards and design guidelines governing design with PC have been developed and used by the PC industry for the last five decades. These guidelines highlight some of those standards.*

ACI Committee Reports, Guides, and Commentaries are intended for guidance in planning, designing, executing, and inspecting construction. This document is intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. The American Concrete Institute disclaims any and all responsibility for the stated principles. The Institute shall not be liable for any loss or damage arising therefrom.

Reference to this document shall not be made in contract documents. If items found in this document are desired by the Architect/Engineer to be a part of the contract documents, they shall be restated in mandatory language for incorporation by the Architect/Engineer.

**Keywords:** beam; creep; equipment foundation; fatigue; fire resistance; fracture; manholes; polymer; polymer concrete; reinforced polymer concrete; utility structures; walls.

## CONTENTS

### CHAPTER 1—INTRODUCTION, p. 2

### CHAPTER 2—NOTATION AND DEFINITIONS, p. 2

- 2.1—Notation, p. 2
- 2.2—Definitions, p. 2

### CHAPTER 3—MATERIALS AND PROPERTIES, p. 3

- 3.1—Materials for structural polymer concrete, p. 3
- 3.2—Polymer concrete types, p. 5
- 3.3—Mechanical properties, p. 6
- 3.4—Chemical and physical characteristics, p. 11
- 3.5—Standards and guides applicable to polymer concrete, p. 13

ACI 548.6R-19 supersedes ACI 548.6R-96 and was adopted and published January 2019.

Copyright © 2019, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 3.6—Safety, p. 13
- 3.7—Regulatory matters, p. 15
- 3.8—Current and suggested research, p. 16

## CHAPTER 4—STRUCTURAL MEMBERS, p. 16

- 4.1—Flexural members, p. 16
- 4.2—Compression members, p. 16
- 4.3—Reinforced polymer concrete, p. 16
- 4.4—Unreinforced polymer concrete, p. 17
- 4.5—Sandwich panels, p. 17

## CHAPTER 5—APPLICATIONS IN STRUCTURES, p. 17

- 5.1—Architectural and façade panels, p. 17
- 5.2—Applications in transportation, p. 19
- 5.3—Utility structures, p. 20
- 5.4—Hydraulic structures, p. 23
- 5.5—Hazardous waste containment structures, p. 23

## CHAPTER 6—REFERENCES, p. 24

Authored documents, p. 24

## APPENDIX A—EXAMPLE PC FORMULATIONS, p. 29

## APPENDIX B—TYPICAL PC PROPERTIES, p. 30

### CHAPTER 1—INTRODUCTION

Polymer concrete (PC) has been used in structural applications where strength, stiffness, durability, and ease in molding provide an advantage over other materials. Many types of reinforcement can be used with PC. This guide presents the structural uses of PC.

Polymer concrete is a mixture of aggregates and resins or monomers without portland cement that hardens by polymerization after it is placed. PC was first used commercially in the 1950s in the United States in the production of synthetic marble, followed by the manufacture of architectural facing panels in the late 1950s. Beginning in the 1970s, other structural products began to appear in the market, including floor drains, utility trenches, underground utility vaults and covers, high-voltage insulators, and highway median barrier shells. These products were followed by the introduction of manhole structures and machine tool bases. By the mid-1970s, PC was used as a repair material for portland-cement concrete structures, mainly on highways and bridges. In the United States in the 1980s, chemical companies developed an increasing interest in specific materials and material properties required to produce PC. As a result, many enhancements in the polymers used for PC were developed, and resins tailor-made for PC production became available. This development continues, and important material improvements are often achieved by manufacturers.

Research into the behavior of PC structural elements has been conducted at numerous research labs. Structural research has been conducted on such uses as steel-reinforced beams and panels, ballistic panels (barriers to armed assault on embassies, for instance), electric transmission

poles, structural sandwich elements, building blocks, utility trenches, utility covers, and insulation panels (Fowler 1988).

## CHAPTER 2—NOTATION AND DEFINITIONS

### 2.1—Notation

$A_1$	=	amplitude of first cycle
$A_n$	=	amplitude of the $n$ -th cycle
$E$	=	dynamic modulus, psi (MPa)
$f_1$	=	frequency of the first mode, Hz
$I$	=	section moment of inertia, in. <sup>4</sup> (mm <sup>4</sup> )
$l$	=	specimen length, in. (mm)
$n$	=	number of amplitude cycles
$T_g$	=	glass-transition temperature, °F (°C)
$W$	=	weight of the specimen, lbf (lbf/N)
$\beta$	=	$I^3/l$ , in. <sup>-1</sup> (m <sup>-1</sup> )
$\zeta$	=	specific damping factor

### 2.2—Definitions

**A/B components**—individual parts of a polymer binder system; in epoxy PC, the components typically consist of resin (A) and curing agent/hardener (B); in free radical PC, the components typically consist of resin (A) and initiator (B).

**accelerator**—chemical used to increase the rate of cure in a free radical system by reacting with the initiator.

**catalyst**—substance that markedly speeds up the cure of a binder when added in minor quantity.

**cross-linking**—joining of preformed linear polymer chains to each other to form three-dimensional networks.

**cross-linking agent**—chemical used to increase the cross-link density of the polymer network.

**cure time**—the interval after mixing in which a PC system gains adequate strength to support loads, such as foot traffic, vehicular traffic, or both.

**curing**—the change in properties of a chemical by an increase in molecular weight via polymerization or cross-linking, usually accomplished by the action of heat, catalyst, cross-linking agent, curing agent, or any combination, with or without pressure.

**fiberglass**—a composite material consisting of glass fibers in resin.

**flammable liquid**—any liquid having a flash point below 38°C (100°F).

**flash point**—minimum temperature at which a liquid gives off vapor within a test vessel in sufficient concentration to form an ignitable mixture with air near the surface of the liquid.

**flexibilizer**—additive that gives a rigid plastic flexibility.

**gel time**—time interval after mixing that a liquid material exhibits a significant viscosity increase.

**heat deflection temperature**—temperature at which a polymer or plastic sample deforms under a specified load.

**inhibitor**—substance that slows or stops a chemical reaction.

**initiator**—substance capable of causing the polymerization of a monomer by a chain reaction mechanism; often incorrectly called a catalyst.