



Dewatering characteristics of coarse coal in a vibrating centrifuge



This Australian Standard® was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 21 September 2016. This Standard was published on 14 October 2016.

The following are represented on Committee MN-001:

- Australasian Institute of Mining and Metallurgy
 - Australian Coal Industry Reference Samples
 - Australian Coal Preparation Society
 - Australian Energy Council
 - CSIRO
 - Department of Natural Resources and Mines, Qld
 - Minerals Council of Australia
 - National Association of Testing Authorities Australia
 - University of Newcastle
 - University of New South Wales
 - University of Queensland
-

This Standard was issued in draft form for comment as DR AS 5142:2016.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting www.standards.org.au

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

**Dewatering characteristics of coarse
coal in a vibrating centrifuge**

First published as AS 5142:2016.

COPYRIGHT

© Standards Australia Limited

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968.

Published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 978 1 76035 580 7

PREFACE

This Standard was prepared by the Standards Australia Committee MN-001, Coal and Coke, as a new Standard.

The moisture content of a product from a coal preparation plant is an important factor with respect to the quality and value of the coal. A significant majority of the product coal is coarse (nominally plus 0.5 mm) and has been cleaned in a water based process. After the cleaning step the product coal is screened to remove the majority of the water, then usually passed through a centrifuge to remove as much of the remaining water as possible.

It has been found that there are distinct limits to the final moisture contents that can be achieved. This is due to there being three types of water associated with the feed to the centrifuge, i.e. water which has little relationship with the coal and can be centrifuged off very easily; water which is closely related to the coal surface termed Exponentially Centrifugable Moisture (ECM); and water on the surface and in the internal pore structure of the coal, which cannot be removed by centrifugation at commercially available G forces, termed the Non Centrifugable Moisture (NCM).

This Standard specifies a laboratory test using the analysis of individual size fractions of a sample of product coal to provide an estimate of NCM values. The values generated from the tests are used to provide an estimate of the moisture held internally in the coal. This value varies markedly for different coals.

This Standard provides quantitative information with regard to the dewatering characteristics of a coarse coal in a vibrating basket centrifuge via an estimate of the amount of moisture held internally in the coal's pore structure (NCMi) and the potential moisture of the coal (NCM + ECM) after it has passed through a conventional vibrating basket centrifuge.

The term 'normative' has been used in this Standard to define the application of the appendix to which it applies. A 'normative' appendix is an integral part of a Standard.

CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	4
3 DEFINITIONS.....	4
4 APPARATUS.....	5
5 ACCURACY OF THE METHOD.....	5
6 SAMPLING AND SAMPLE PREPARATION.....	6
7 PROCEDURE FOR THE DETERMINATION OF ECM and NCM.....	6
8 ESTIMATE OF PRODUCT MOISTURE FROM A VIBRATING BASKET CENTRIFUGE.....	8
9 PROCEDURE FOR THE DETERMINATION OF NCM _i	8
10 PRECISION OF THE METHOD.....	9
11 TEST REPORT.....	9
APPENDIX A APPARATUS.....	17

STANDARDS AUSTRALIA

Australian Standard

Dewatering characteristics of coarse coal in a vibrating centrifuge**1 SCOPE**

This Standard specifies the apparatus and methods for determining the following three moisture elements that make up the final moisture content of a coarse (nominally 50 mm to 0.5 mm) product coal after centrifugation:

- (a) Exponentially Centrifugable Moisture (ECM).
- (b) Non Centrifugable Moisture (NCM).
- (c) Non Centrifugable Moisture Internal (NCMi).

NOTE: Figure 1 illustrates how this Standard relates to commonly used moisture terms (shaded area).

WARNING: USE OF THIS STANDARD CAN INVOLVE HAZARDOUS MATERIALS, OPERATIONS AND EQUIPMENT. THIS STANDARD DOES NOT PURPORT TO ADDRESS ALL OF THE SAFETY ISSUES ASSOCIATED WITH ITS USE. IT IS THE RESPONSIBILITY OF THE USER OF THIS STANDARD TO ESTABLISH APPROPRIATE SAFETY AND HEALTH PRACTICES AND DETERMINE THE APPLICABILITY OF REGULATORY LIMITATIONS PRIOR TO USE.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS	
1152	Specification for test sieves
2418	Coal and coke—Glossary of terms
ISO	
13909	Hard coal and coke—Mechanical sampling
13909-1	Part 1: General introduction

3 DEFINITIONS

For the purpose of this Standard the definitions given in AS 2418 and those below apply:

3.1 Exponentially Centrifugable Moisture (ECM)

Water closely related to the surface of the coal, and therefore results in a slow rate of moisture removal during centrifugation (exponential with time).

3.2 Non Centrifugable Moisture (NCM)

The moisture content of the coal after centrifugation in the laboratory test, i.e. the moisture content 'unrecoverable by centrifugation'.

3.3 Non Centrifugable Moisture Internal (NCMi)

An internal moisture closely related to the pore structure of the coal.

3.4 Non Centrifugable Moisture Surface (NCMs)

Water closely related to surface particles and surface topography. This moisture can be expressed as the difference between NCM and NCMi.

NOTE: A diagrammatic description of these definitions is given in Figure 1.