

Australian Standard[®]

**Copper, lead, zinc and nickel
concentrates—Determination of mass
loss of bulk material on drying**

STANDARDS
Australia



This Australian Standard® was prepared by Committee MN-005, Copper, Lead, Zinc and Nickel and Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 24 January 2008.

This Standard was published on 12 March 2008.

The following are represented on Committee MN-005:

- CSIRO Minerals
- Minerals Council of Australia

Additional Interests:

- Minerals Industry Analytical Laboratories
-

This Standard was issued in draft form for comment as DR 07040.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting **www.standards.org.au**

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at **mail@standards.org.au**, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

**Copper, lead, zinc and nickel
concentrates—Determination of mass
loss of bulk material on drying**

Originated as AS 2863—1986.
Previous edition 1999.
Third edition 2008.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia
ISBN 0 7337 8582 4

PREFACE

This Standard was prepared by the Standards Australia Committee MN-005, Copper, Lead, Zinc and Nickel and Ores and Concentrates, to supersede AS 2863—1999, *Copper, lead and zinc sulfide concentrates—Determination of mass loss of bulk material on drying*.

The objective of this Standard is to provide those involved in the analysis of sulfide concentrates with a standardized method of determining the mass loss of bulk material on drying.

The objective of this revision is to adopt the latest edition of the corresponding International Standard.

This Standard is identical with, and has been reproduced from, ISO 10251:2006, *Copper, lead, zinc and nickel concentrates—Determination of mass loss of bulk material on drying*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number appears on the cover and title page while the International Standard number appears only on the cover.
- (b) In the source text ‘this International Standard should read ‘this Australian Standard’.
- (c) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian Standard</i>
ISO	AS
9599 Copper, lead and zinc sulfide concentrates—Determination of hygroscopic moisture in the analysis sample—Gravimetric method	2816 Copper, lead and zinc sulfide concentrates—Determination of hygroscopic moisture in the analysis sample—Gravimetric method
12743 Copper, lead, zinc and nickel concentrates—Sampling procedures for determination of metal and moisture content	2862 Copper, lead, zinc and nickel concentrates—Sampling 2862.1 Part 1: Sampling procedures for determination of metal and moisture content

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the annex to which they apply. A ‘normative’ annex is an integral part of a Standard, whereas an ‘informative’ annex is only for information and guidance.

CONTENTS

	<i>Page</i>
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Drying method	2
5 Apparatus	4
6 Processing of samples	4
7 Moisture samples	4
8 Procedure for drying samples to constant mass	5
9 Calculation	6
10 Test report	9
Annex A (normative) Test for susceptibility of concentrates to oxidation, decomposition and sublimation	10
Annex B (normative) Determination of moisture content of cohesive or wet concentrates	11
Annex C (informative) Example of a work sheet for the determination of moisture content of each test portion in accordance with this International Standard	12
Bibliography	13

AUSTRALIAN STANDARD

Copper, lead, zinc and nickel concentrates — Determination of mass loss of bulk material on drying

WARNING — This International Standard may involve hazardous materials, operations and equipment. This International Standard does not purport to address all of the safety issues associated with its use. It is the responsibility of the user to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies methods for the determination of moisture content of a lot of copper, lead, zinc or nickel concentrate, defined as the percentage mass loss of the moisture test portion under the conditions of drying specified in this document.

In order to obtain an unbiased estimate of the metal content of the lot, it is important that the same drying conditions are used for the determination of bulk and hygroscopic moisture or for preparing a predried test portion.

This International Standard is not applicable to drying samples used for determination of volatile elements such as mercury and sulfur. Such samples are allowed to dry at ambient temperature, and a hygroscopic moisture determination is carried out according to ISO 9599 at the time of chemical analysis.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1**representative sample**

quantity of concentrate representing a larger mass of concentrate with both precision and bias within acceptable limits

3.2**lot**

quantity of concentrate to be sampled

3.3**lot sample**

quantity of concentrate that is representative of the lot