

Australian Standard™

**Higher rank coal and coke—Bulk
density**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 14 October 2002 and published on 25 October 2002.

The following are represented on Committee MN-001:

Australian Institute of Mining and Metallurgy
Australian Coal Association
Australian Coal Preparation Society
Australian Institute of Energy
Coalfield Geology Council of N.S.W.
CSIRO Energy Technology
Department of Mineral Resources and Mines(Qld)
Electricity Supply Association of Australia
Institution of Engineers Australia
Minerals Council of Australia
University of New South Wales
University of Newcastle
University of Queensland

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 02333.

Australian Standard™

**Higher rank coal and coke—Bulk
density**

Originated as AS 3899—1991.
Second edition 2002.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4885 6

PREFACE

This Standard was prepared by the Standards Australia Subcommittee MN-001-04, *Coal Sampling*, for Committee MN-001, *Coal and Coke*, as a revision of AS 3899—1991, *Higher rank coal and coke—Bulk density*.

The hopper-filled box method for the determination of bulk density of higher rank coal has been deleted from this edition.

Reference to ASTM D291, *Standard Test Method for Cubic Foot Weight of Crushed Bituminous Coal* should be made if a determination of bulk density by the hopper-filled box method is required.

CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 REFERENCED DOCUMENTS	5
3 DEFINITIONS	5
4 DETERMINATION OF BULK DENSITY OF HIGHER RANK COAL.....	5
5 DETERMINATION OF BULK DENSITY OF COKE	10
6 CALCULATION OF RESULTS.....	11
7 ACCEPTANCE OF RESULTS	12
8 REPORTING OF RESULTS.....	12
9 PRECISION.....	12
10 TEST REPORT	13

FOREWORD

The bulk density of coal and coke depends upon its physical characteristics, i.e. relative density and shape of particles, the dimensions of the container, the size distribution of the coal particles and their moisture content. Size analysis is important and it is therefore recommended that a separate size analysis be determined in accordance with AS 3881, *Higher rank coal—Size analysis*.

Results for bulk density will change according to variations in the above characteristics. In practice, results can be considered under two main headings:

- (a) *As poured (uncompacted)*—the bulk density that results from pouring the material into a heap or container in the absence of compacting forces.
- (b) *Aerated**—the bulk density created when particles are separated from each other by an air film. (Applies only to fine, dry powders.)

In any bulk density measurement, the test conditions should simulate or represent, as closely as possible, the actual conditions under which the bulk density needs to be known, as the method used will influence the result[†]. The method used to determine bulk density has to be specified in the test report.

* A brief description of this procedure is given in *Bulk solids physical properties test guide*, British Materials Handling Board, 1983

† CSIRO Report TC 19, *The control of bulk density by moisture and oil addition*, August 1957.

STANDARDS AUSTRALIA

Australian Standard Higher rank coal and coke—Bulk density

1 SCOPE

This Standard sets out the following three methods for the determination of the bulk density of crushed higher rank coal and coke:

- (a) Uncompacted box method, for coal less than 45 mm nominal top size (see Note to Clause 4.2.3(a)).
- (b) Measuring cylinder method, for coal typically less than 63 μm as used in pulverized fuel fired boilers and cement kilns.
- (c) Uncompacted box method for coke.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- | | |
|--------|---|
| 1038 | Coal and coke—Analysis and testing |
| 1038.1 | Part 1: Higher rank coal—Total moisture |
| 1038.2 | Part 2: Coke—Total moisture |
| 2418 | Coal and coke—Glossary of terms |
| 2706 | Numerical values—Rounding and interpretation of limiting values |
| 4264 | Coal and coke—Sampling |
| 4264.1 | Part 1: Higher rank coal—Sampling procedures |
| 4264.2 | Part 2: Coke—Sampling procedures |

ISO

- | | |
|-----|---|
| 567 | Coke—Determination of bulk density in a small container |
|-----|---|

3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 2418 and those below apply.

3.1 Bulk density of higher rank coal

The mass of a unit volume of higher rank coal, including the voids within and between the particles, measured under standard conditions.

3.2 Bulk density of coke

The mass per unit volume of dry coke, as determined in a standard container using a standardized procedure.

4 DETERMINATION OF BULK DENSITY OF HIGHER RANK COAL

4.1 General

Samples containing fines will show significant variations in bulk density with variations in moisture. Care should be taken to ensure that moisture in the test sample is representative of the gross sample.