

Australian Standard™

Alumina

Part 8: Determination of bulk density

This Australian Standard was prepared by Committee MN/9, Alumina and Materials used in Aluminium Production. It was approved on behalf of the Council of Standards Australia on 15 February 2000 and published on 8 June 2000.

The following interests are represented on Committee MN/9:

Australasian Institute of Mining and Metallurgy
Australian Aluminium Council
CSIRO Minerals
Minerals Council of Australia
The Royal Australian Chemical Institute

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.com.au, or write to the Chief Executive, Standards Australia International Ltd, PO Box 1055, Strathfield, NSW 2135.

Australian Standard™

Alumina

Part 8: Determination of bulk density

First published as AS 2879.8—2000.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd
PO Box 1055, Strathfield, NSW 2135, Australia

ISBN 0 7337 3315 8

PREFACE

This Standard was prepared by the Standards Australia Committee MN/9, on Alumina and Materials used in Aluminium Production as Part 8 of the AS 2879 series of methods for testing alumina.

CONTENTS

	<i>Page</i>
1 SCOPE.....	3
2 REFERENCED DOCUMENTS.....	3
3 PRINCIPLE.....	3
4 SAFETY.....	3
5 APPARATUS.....	3
6 SAMPLE HANDLING AND PREPARATION.....	4
7 PROCEDURE.....	4
8 CALCULATION AND REPORTING OF RESULTS.....	5
9 PRECISION.....	5
10 TEST REPORT.....	6

STANDARDS AUSTRALIA

Australian Standard

Alumina

Part 8: Determination of bulk density

1 SCOPE

This Standard sets out a method for the determination of unpacked and packed bulk density of smelter-grade aluminium oxide primarily used for the production of aluminium.

Methods using the fall of sample into a receptacle have been found to be sensitive to flow rate variations, which are caused by physical properties of the aluminium oxide.

This method minimizes rate variations.

2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

2243 Safety in laboratories (series)

2850 Chemical analysis—Interlaboratory test programs—For determining precision of analytical method(s)—Guide to the planning and conduct

2879 Alumina

2879.1 Part 1: Determination of loss of mass at 300°C and 1000°C

3 PRINCIPLE

A test portion of sample is allowed to fall in a narrow stream from a container onto a small metal impact plate from which the stream spreads and falls into a receiving vessel of known volume. The mass of sample filling the vessel is determined and unpacked bulk density is calculated on a moisture free (300°C) basis. The material in the receiver is then compacted while further sample is added so that packed bulk density can be determined again on a moisture free basis.

4 SAFETY

For information on laboratory safety, reference should be made to the relevant parts of AS 2243.

5 APPARATUS

5.1 Sample delivery apparatus

As shown in Figure 1, constructed entirely of metal. The orifice plate moves a 5 mm orifice beneath the delivery vessel to begin or terminate sample flow into the delivery tube.

5.2 Receiver

A cylindrical container of volume 200 ± 10 mL, having internal length-to-diameter ratio of approximately 6:1. The exact volume V shall be determined accurately by temperature corrected water mass.

NOTE: An error of 0.5 mL in the volume determination will cause an error of 3.0 kg/m^3 in the bulk density.