

Australian Standard™

**Metal finishing—Preparation and  
pretreatment of surfaces**

**Part 1: Removal of oil, grease and  
related contamination**

This Australian Standard was prepared by Committee MT-009, Metal Finishing. It was approved on behalf of the Council of Standards Australia on 11 April 2003 and published on 2 June 2003.

---

The following are represented on Committee MT-009:

Australasian Institute of Metal Finishing  
Australian Chamber of Commerce and Industry  
Australian Industry Group  
Australian Paint Manufacturers Federation  
Department of Defence  
Galvanizers Association of Australia  
Institute of Materials Engineering Australia  
Powder Coaters Association  
The Royal Australian Chemical Institute  
Society of Automotive Engineers—Australasia  
Telstra Corporation

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

STANDARDS AUSTRALIA

---

**RECONFIRMATION**

**OF**

**AS 1627.1—2003**

**Metal finishing—Preparation and pretreatment of surfaces  
Part 1: Removal of oil, grease and related contamination**

---

**RECONFIRMATION NOTICE**

Technical Committee MT-009 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 20 March 2017.

The following are represented on Technical Committee MT-009:

Australasian Institute of Surface Finishing  
Australian Chamber of Commerce and Industry  
Australian Industry Group  
Australian Steel Institute  
Bureau of Steel Manufacturers of Australia  
Galvanizers Association of Australia  
Galvanizing Association of New Zealand  
New Zealand Metal Roofing Manufacturers

## NOTES

Australian Standard™

**Metal finishing—Preparation and  
pretreatment of surfaces**

**Part 1: Removal of oil, grease and  
related contamination**

Originated as AS CK9.1—1965.  
Previous edition AS 1627.1—1989.  
Third edition 2003.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5257 8

## PREFACE

This Standard has been prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-009, Metal Finishing, to supersede AS 1627.1—1989. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

This Standard was revised by Standards Australia Subcommittee MT-009-05 which decided to change the title from *Metal finishing, Part 1: Cleaning using liquid solvents or alkaline solution* to *Metal finishing, Part 1: Removal of oil, grease and related contamination* as the latter better reflects the content of the Standard.

The objective of this Standard is to specify the procedures for the removal of surface contaminants on metallic surfaces.

This Standard forms Part 1 of a series of Standards that deal with the preparation and pre-treatment of metal surfaces in readiness for finishing processes.

The series comprises the following Parts:

### AS

- 1627 Metal finishing—Preparation and pretreatment of surfaces
- 1627.0 Part 0: Method selection guide
- 1627.1 Part 1: Removal of oil, grease and related contamination
- 1627.2 Part 2: Power tool cleaning
- 1627.4 Part 4: Abrasive blast cleaning
- 1627.5 Part 5: Pickling
- 1627.6 Part 6: Chemical conversion treatment of metals
- 1627.9 Part 9: Pictorial surface preparation standards for painting steel surfaces

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE.....	5
1.2 REFERENCED DOCUMENTS.....	5
1.3 DESIGNATION .....	5
1.4 DEFINITIONS.....	6
1.5 SURFACE CLEANLINESS .....	6
SECTION 2 SURFACE CLEANING PROCESSES	
2.1 GENERAL.....	8
2.2 NEUTRAL/ALKALINE PROCESSES.....	8
2.3 SOLVENT PROCESSES.....	9
2.4 EMULSION PROCESSES .....	10
2.5 HIGH PRESSURE CLEANING PROCESSES .....	10
2.6 CORROSION PROTECTION .....	11
2.7 SAFETY PRECAUTIONS .....	11
APPENDICES	
A PURCHASING GUIDELINES .....	12
B GUIDE TO THE SELECTION OF CLEANING PROCESS .....	13

## FOREWORD

This Standard describes methods and materials used to remove contaminants such as oil, grease and related contaminants from metal and previously coated surfaces prior to further surface preparation or coating.

Such methods are used prior to mechanical methods such as power tool cleaning or abrasive blasting. Methods included in the procedures are simple solvent wiping, immersion in solvent, solvent spray, vapour degreasing, emulsion cleaning and alkaline cleaning.

Solvent cleaning is not a suitable method for the removal of corrosive salts. These require treatment, according to the degree of contamination, by washing with suitable aqueous solutions, possibly utilizing high pressure water.

Liquid solvent cleaning seldom completely removes all oil and grease. Supplementary cleaning processes may be required to produce suitably clean surfaces for some coating systems. Solvent vapour degreasing is capable of removing all oil and grease deposits.

Successful coating of a metal component or structural items, whether with a paint system or another metal (such as zinc), lies in rendering its surface completely free of any foreign matter, notably dirt or greasy substances, that will interfere either with the coating operation itself or with the ultimate performance of the coating in service. The presence of unremoved contamination is likely to result in an unsatisfactory coating finish, such as blistering and bare areas, or in disbonding of an apparently satisfactory coating from the substrate with the passage of time.

A wide range of alkaline cleaning products and methods is available, and the nature of the final coating must be taken into account as the final performance may be affected by the cleaning method selected. It is also essential that residues of alkaline cleaning compounds and detergents be removed, as these can be detrimental to performance. Alkaline cleaning is suitable for removal of dirt, perspiration, light deposits of oil and some water wettable or soluble contaminants.

STANDARDS AUSTRALIA  
**Australian Standard**  
**Metal finishing—Preparation and pretreatment of surfaces**

Part 1: Removal of oil, grease and related contamination

SECTION 1 SCOPE AND GENERAL

### 1.1 SCOPE

This Standard sets out a variety of methods for eliminating dirt and organic residues, such as oil, grease and related contaminants from metal surfaces, so as to facilitate the satisfactory application of finished coatings. Methods described for decontaminating surfaces include simple solvent wiping, immersion in solvent, solvent spray, vapour degreasing, emulsion cleaning, and alkaline cleaning. The process will usually remove loose adherent dirt from affected surfaces.

Depending on the nature of the finish coating to be applied, cleaning by any of the procedures described in this Standard may be followed by a more rigorous intermediate treatment, such as pickling or abrasive blast cleaning.

NOTE: Appendix A contains advice and recommendations on information which should be supplied by the purchaser at the time of inquiry or order.

### 1.2 REFERENCED DOCUMENTS

The documents below are referred to in this Standard.

AS

2661 Vapour decreasing plant—Design, installation and operation—Safety requirements

3894 Site testing of protective coatings

3894.6 Method 6: Determination of residual contaminants

4108 Metal finishing—Glossary of terms used in electroplating and related processes

AS/NZS

1337 Eye protectors for industrial applications

1715 Selection, use and maintenance of respiratory protective devices

1716 Respiratory protective devices

### 1.3 DESIGNATION

The designations adopted for the various types of cleaning processes given in Table 2.1 are listed below:

(a) *Neutral/Alkaline degreasing process (A)*

AS..... Neutral/Alkaline spray process

AD ..... Neutral/Alkaline dip or soak process

ADM.... AD process with mechanical and/or ultrasonic agitation

AE..... Alkaline electrolytic