

Australian/New Zealand Standard™

Paints for steel structures

Part 21: Undercoat—Solvent-borne



AS/NZS 3750.21:2008

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee CH-003, Paints and Related Materials. It was approved on behalf of the Council of Standards Australia on 19 March 2007 and on behalf of the Council of Standards New Zealand on 3 March 2007.

This Standard was published on 19 May 2008.

The following are represented on Committee CH-003:

AUSTROADS

Australasian Corrosion Association
Australian Paint Approval Scheme
Australian Paint Manufacturers' Federation
Australian Pipeline Industry Association
Business New Zealand
Engineers Australia
Institution of Professional Engineers New Zealand
Master Painters Australia
Master Painters New Zealand Association
National Association of Testing Authorities Australia
Water Corporation Western Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.standards.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

Alternatively, both organizations publish an annual printed Catalogue with full details of all current Standards. For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR 04193.

Australian/New Zealand Standard™

Paints for steel structures

Part 21: Undercoat—Solvent-borne

Originated as SAA Int 226—1953.
Revised and redesignated AS K127—1961.
Revised and redesignated AS 4025.2—1993.
Revised and redesignated AS/NZS 3750.21:2008.

COPYRIGHT

© Standards Australia/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Jointly published by Standards Australia, GPO Box 476, Sydney, NSW 2001 and Standards New Zealand, Private Bag 2439, Wellington 6020

ISBN 0 7337 8696 0

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee CH-003, Paints and Related Materials, to supersede AS 4025.2—1993, *Paints for equipment including ships, Part 2: Solvent-borne—Interior and exterior—Undercoat*.

See AS 3730.0 for other published Standards in this series.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	4
3 DEFINITIONS.....	4
4 MATERIALS REQUIREMENTS.....	4
5 PACKAGING	9
6 LABELLING	9
APPENDICES	
A LIST OF REFERENCED DOCUMENTS	10
B PREPARATION OF TEST PANELS FOR RESISTANCE TO WEATHERING TESTS	12

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Australian/New Zealand Standard
Paints for steel structures

Part 21: Undercoat—Solvent-borne

1 SCOPE

This Standard sets out requirements for solvent-borne undercoat paints as part of a system for the protection of iron and steel against atmospheric corrosion. Typically available in white or grey colour, they are intended to be applied, as supplied, using brush, roller or by spray.

This Standard applies to paints intended for the undercoating of metal surfaces primed in accordance with AS/NZS 3750.19 or AS/NZS 3750.20 that are to be topcoated with a semi-gloss or full gloss film in accordance with AS/NZS 3750.22 or AS/NZS 3750.23 that will provide resistance to weathering, washing and intermittent contact with petrol or mineral oils. Typical applications include machinery and the superstructures of ships.

NOTE: Undercoats as part of a system for the protection of steel are not considered necessary according to AS/NZS 2312. However, for reasons such as additional filling properties, opacity, ease of sanding to obtain a finer finish, they may be incorporated in an alkyd system.

2 REFERENCED DOCUMENTS

A list of documents referred to in this Standard is given in Appendix A.

3 DEFINITIONS

The definitions of AS/NZS 2310 apply.

4 MATERIALS REQUIREMENTS

NOTE: The properties and requirements for paint to this Standard are summarized in Table 1.

4.1 Composition

The paint shall consist essentially of pigments, extenders, drying oils, modified resins such as alkyds or urethanes, and volatile hydrocarbon solvents such as mineral turpentine. The product shall not be a First, Second or Third Schedule paint as defined in the Standard for the Uniform Scheduling of Drugs and Poisons (SUSDP) issued by the Department of Health and Ageing.

4.2 Conditions of test

Unless otherwise indicated, the requirements specified in this Standard apply to products that are tested under the following conditions:

- (a) The test panel material is tinplate as specified in AS/NZS 1580.104.1 or as indicated in Table 1. Where reference panels are required, they shall be composed of the same material as the test panel and be prepared by methods identical to those used for the test panel.
- (b) The size of test panels is as specified in Table 1 for the appropriate test method.
- (c) The method of test paint application is by brush.