

DR 87036

AS 1038, Part 20—1981
UDC [662.66 + 662.74]:620.163.4

1992 ED.

Australian Standard 1038, Part 20—1981

See also
SAA TR 2.11-
1989

METHODS FOR THE ANALYSIS AND TESTING OF COAL AND COKE

Part 20—HARDGROVE GRINDABILITY INDEX OF HARD COAL

1038.20—1992 Higher rank coal—Hardgrove
grindability index
(In Professional Package 32) 6pp CC
Sets out the method for determining the grindability index
of higher rank coal, using the Hardgrove machine. Calibration
using ASCRM-011 is included.
Committee MN/1: Supersedes AS 1038.20—1981: Draft for comment
DR 87036: Publication date 1992-06-15: ISBN 0 7262 7369 4



STANDARDS ASSOCIATION OF AUSTRALIA

Incorporated by Royal Charter

THE FOLLOWING INDUSTRIAL, SCIENTIFIC AND GOVERNMENTAL organizations and departments were officially represented on the committee entrusted with the preparation of this standard:

Australian Coal Association

Australian Institute of Engineering and Metallurgy

Australian Institute of Mining and Metallurgy

Board of Trade, Queensland

Coal Preparation Societies of N.S.W. and Queensland

Confederation of Australian Industry Victoria

Department of Minerals and Energy, Victoria

Department of Mineral Resources, N.S.W.

Department of National Development, Australia

Electricity Supply Association of Australia

Institution of Engineers, Australia

Queensland Coal Board

Queensland Coal Board

Royal Australian Chemical Institute

Universities

This standard, prepared under the direction of Committee MN/1, Coal and Coke, was approved on behalf of the Council of the Standards Association of Australia on 24 December 1980, and was published on 1 May 1981.

To keep abreast of progress in industry, Australian Standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users be aware of the current status of standards. Details of all standards publications and amendments are available in the Australian Standards Journal, the Association's quarterly journal. The Australian Standards Handbook, a list of suggestions on the work, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

This standard was issued in draft form for public review as DR 79117.

This standard was issued in draft form for public review as DR 79117.

AUSTRALIAN STANDARD

**METHODS FOR THE
ANALYSIS AND TESTING
OF COAL AND COKE**

**Part 20
HARDGROVE
GRINDABILITY INDEX
OF HARD COAL**

AS 1038, Part 20—1981

First published (as AS K164)..... 1967
Revised and issued as AS 1038, Part 20 .. 1981

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 2159 7

PREFACE

This standard was prepared by the Association's Committee on Coal and Coke under the direction of the Minerals Standards Committee as a revision of AS K164—1967, which it accordingly supersedes. It is based on ISO 5074—Hard Coal—Determination of Hardgrove Grindability Index.

Grindability is a measure of the ease with which coal can be ground fine enough for use as a pulverized fuel, and is dependent upon the physical properties of the coal and the mechanical characteristics of the test machine.

Hardgrove grindability is determined by grinding a coal sample in a laboratory batch machine, and serves as a means of estimating the capacity of commercial pulverizers to grind different coals.

The standard requires reference to the following standards:

- AS 1038 Methods for the Analysis and Testing of Coal and Coke
 Part 16—Reporting of Results
- AS 1152 Test Sieves
- AS 1676 Methods for the Sampling of Hard Coal

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1981

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

CONTENTS

METHOD	<i>Page</i>
1 Scope	4
2 Principle	4
3 Apparatus....	4
4 Sampling	5
5 Sample Preparation	5
6 Procedure	6
7 Expression of Results	7
8 Precision	7
9 Test Report	7
APPENDICES	
A Calibration Charts	11
B Preparation of National Standard Reference Coal Samples	12
C Calibration of National Hardgrove Machines	13

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

METHODS FOR THE ANALYSIS AND TESTING OF COAL AND COKE

PART 20—HARDGROVE GRINDABILITY INDEX OF HARD COAL

1 SCOPE. This standard sets out the method for determining the grindability index of hard coal using the Hardgrove machine. It also prescribes the procedure for calibration of the test machines and the preparation of standard reference coal samples.

2 PRINCIPLE. A prepared sample of coal of limited size range is ground under defined conditions in a laboratory mill of standardized design. The grindability index is derived from a sieve analysis of the ground product and by reference to a calibration chart prepared from standard reference materials.

3 APPARATUS.

3.1 Balance. A balance capable of weighing up to 100 g to an accuracy of 0.01 g.

3.2 Balance. A balance capable of weighing up to 1500 g to an accuracy of 1 g.

3.3 Sample Divider. A sample divider as specified in Appendix A of AS 1676.

3.4 Crusher. A laboratory plate mill capable of reducing 4.75 mm coal particles to 1.18 mm with the production of a minimum of material finer than 600 μm . The plates shall be serrated and about 100 mm in diameter. The distance between the plates shall be adjustable and the relative frequency of rotation of the plates shall not exceed 200 r/min. Roll or impact crushers shall not be used because the former produces platy particles and the latter produces excessive fines.

3.5 Sieves.

3.5.1 Wire cloth test sieves. Wire cloth test sieves complying with AS 1152, of aperture sizes 1.18 mm, 600 μm and 75 μm respectively, and having a cover and receiver of diameter about 200 mm.

3.5.2 Protective sieve. A protective sieve capable of nesting in the test sieves, with round or square hole apertures in the range 16 mm to 19 mm.