

Australian Standard™

**Paints and related materials—Pavement
marking materials**

**Part 1: Solvent-borne paint—For use
with surface applied glass beads**

This Australian Standard was prepared by Committee CH-003, Paints and Related Materials. It was approved on behalf of the Council of Standards Australia on 13 October 2004.
This Standard was published on 21 January 2005.

The following are represented on Committee CH-003:

AUSTROADS

Australian Industry Group
Australian Motorcycle Council
Australian Paint Approval Scheme
Australian Paint Manufacturers' Federation
Main Roads Department, Queensland
Master Painters Australia
National Association of Testing Authorities Australia
Roadmarking Industry Association of Australia
Surface Coatings Association of Australia
Telstra Corporation
Water Corporation Western Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 02399.

Australian Standard™

**Paints and related materials—Pavement
marking materials**

**Part 1: Solvent-borne paint—For use
with surface applied glass beads**

Originated as K146—1967.
Revised and redesignated AS 4049.1—1992.
Second edition 2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 5420, Sydney, NSW 2001, Australia
ISBN 0 7337 6432 0

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee CH-003, Paints and Related Materials. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian, rather than an Australian/New Zealand Standard.

This Standard supersedes AS 4049.1—1992, *Paints and related materials—Road marking materials—Solvent-borne paint—For use with drop-on beads*.

This Standard is the first of three parts dealing with pavement marking materials. Other Standards in the AS 4049 series are:

AS

4049 Paints and related materials—Pavement marking materials

4049.2 Part 2: Thermoplastic pavement marking materials—For use with surface applied glass beads

4049.3 Part 3: Water-borne paints—For use with surface applied glass beads

This Standard mainly provides performance requirements for pavement marking materials but includes some material requirements.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
FOREWORD.....	4
1 SCOPE.....	5
2 OBJECTIVE	5
3 REFERENCED DOCUMENTS.....	5
4 DEFINITIONS.....	5
5 CLASSIFICATION	5
6 COMPOSITION	6
7 TESTING AND PERFORMANCE REQUIREMENTS.....	6
8 PACKAGING	8
9 LABELLING	8
APPENDICES	
A METHODS FOR DEMONSTRATING COMPLIANCE WITH THIS STANDARD	10
B LIST OF REFERENCED DOCUMENTS	12
C SAMPLING GUIDELINES.....	14
D DETERMINATION OF FINENESS OF PAINT	17
E ASSESSMENT OF RESISTANCE TO BLEEDING OF PAVEMENT MARKING PAINT	19
F PREPARATION OF TEST PANELS	21
G DETERMINATION OF LUMINANCE FACTOR.....	22
H FIELD TESTS FOR PAVEMENT MARKING PAINT.....	25
I DETERMINATION OF RETROREFLECTIVITY	28
J DETERMINATION OF DEGREE OF WEAR.....	30
K PICTORIAL STANDARDS FOR DEPICTING VARIOUS DEGREES OF WEAR	32

FOREWORD

Pavement marking paints are expected to perform under a wide variety of application, curing and exposure conditions, and therefore need to be assessed in both the laboratory and in the field. This Standard provides test procedures and performance criteria aimed at identifying paints which will provide satisfactory performance as a beaded and unbeaded pavement marking, in the majority of applications.

Skid resistance requirements have not been specified in this Standard. The skid resistance of a pavement marking paint is not a fixed property for any given formulation. For a new marking it may vary considerably according to the road surface and texture and it will also vary throughout its life according to conditions such as traffic wear and weather. Whilst the drop-on addition of glass beads may increase the frictional characteristics over that of unbeaded paint, the resultant skid resistance levels may not satisfy the requirements of all road users.

It is strongly recommended that users of this Standard consult materials suppliers where skid resistance is a requirement for the applied marking.

STANDARDS AUSTRALIA

Australian Standard

Paints and related materials—Pavement marking materials

Part 1: Solvent-borne paint—For use with surface applied glass beads

1 SCOPE

This Standard sets out requirements for solvent-borne paints as used for markings on pavement surfaces. The Standard is applicable to paints intended for use by spray application. It is also applicable to slower drying paints which may be applied by brush or roller. All paints are suitable for use with glass beads complying with AS/NZS 2009.

NOTES:

- 1 Alternative means for determining compliance with this Standard are given in Appendix A.
- 2 Spraying may be by air-atomizing or airless application processes.

2 OBJECTIVE

The objective of this Standard is to provide requirements and recommendations which may be used when specifying solvent-borne paints.

3 REFERENCED DOCUMENTS

A list of documents referred to in this Standard is contained in Appendix B.

4 DEFINITIONS

For the purpose of this Standard the definitions in AS/NZS 2310 and those below apply.

4.1 Retroreflectivity

The property of some materials such as solid glass beads, to reflect incident light in directions close to the direction from which it came.

4.2 Test pavement

Dense grade asphalt and/or sprayed bituminous surfacing constructed using an aggregate with a nominal size of 10 mm, in accordance with Table 1 of AS/NZS 2758.2. The pavement shall be free from the impact of turning vehicles, at least 6 months old and free from cracking, rutting or any other defects which may impact on the testing outcome.

5 CLASSIFICATION

For the purpose of this Standard, solvent-borne pavement marking paint shall be classified as follows:

- (a) *Rapid drying* A pavement marking paint which has a maximum no-pick-up time of 5 min, when tested in accordance with AS/NZS 1580.401.8.
- (b) *Slow drying* A pavement marking paint which has a no-pick-up time greater than 5 min but no more than 15 min, when tested in accordance with AS/NZS 1580.401.8.

NOTE: Where a paint supplied to this Standard is intended for application at elevated temperature then testing for the purposes of classification according to this Clause should be in accordance with AS/NZS 1580.401.8, except that the temperature of the paint when applied should be the manufacturer's recommended maximum spraying temperature.