

Under Revision See DR 95162

SUPERSEDED BY AS/NZS 2576:1996

AS 2576—1982  
UDC 621.791.04

# Australian Standard 2576—1982

---

## WELDING CONSUMABLES FOR BUILD-UP AND WEAR RESISTANCE— CLASSIFICATION SYSTEM



**STANDARDS ASSOCIATION OF AUSTRALIA**  
*Incorporated by Royal Charter*



This Australian standard was prepared by Committee WD/2, Electrodes and Filler Rods. It was approved on behalf of the Council of the Standards Association of Australia on 21 September 1982 and published on 6 December 1982.

---

The following interests were represented on the committee responsible for the preparation of this standard:

- Australian Gas Association
- Australian Institute of Petroleum Limited
- Australian Welding Institute
- Australian Welding Research Association
- Bureau of Steel Manufacturers of Australia
- Confederation of Australian Industry
- Department of Defence
- Department of Industrial Relations, N.S.W.
- Department of Industry and Commerce
- Department of Labour and Industry, Vic.
- Lloyds Register of Shipping
- Metal Trades Industry Association of Australia
- Metropolitan Water Sewerage and Drainage Board, N.S.W.
- Railways of Australia Committee

---

To keep abreast of progress in industry, Australian standards are subject to continuous review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that their standards are up-to-date. Full details of all SAA publications will be found in the Annual List of Australian Standards; these details are supplemented by listings in the SAA monthly journal 'The Australian Standard'. Information on the Annual List and 'The Australian Standard' may be obtained from any sales office of the Association, where details are also available of the current status of individual standards. Suggestions for improvements to published standards, addressed to the head office of the Association, are welcomed.

---

*This standard was issued in draft form for comment as DR 80264.* ✓

**AUSTRALIAN STANDARD**

**WELDING CONSUMABLES  
FOR BUILD-UP AND  
WEAR RESISTANCE—  
CLASSIFICATION SYSTEM**

**AS 2576—1982**

First published .....1982

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA  
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**



ISBN 0 7262 2735 8

## PREFACE

This standard was prepared by the Association's Committee on Electrodes and Filler Rods. It is one of a series of standards being developed to suit Australian conditions. The standard is largely based on Australian Welding Research Association Technical Note 4 and acknowledgement is made to that Association for its assistance in the preparation of this standard. Acknowledgement is also made to Commonwealth Industrial Gases Limited for the photomicrographs reproduced as Appendix B.

Australian standards dealing with electrodes are as follows:

- AS 1167 Alloy Filler Rods for Brazing
- AS 1552 Classification of Covered Electrodes
- AS 1553 Low Carbon Steel Covered Electrodes for Manual Metal-arc Welding
- AS 1586 Low Alloy Steel Covered Electrodes for Manual Metal-arc Welding
- AS 1588 Filler Rods for Welding
- AS 2203 Carbon Steel Electrodes, Cored (For Arc Welding)
- AS . . . . Electrodes for Gas Metal-arc Welding\*

The classification of the consumables is by alloy type (chemical analysis and microstructure) and hardness of the weld deposit. Surfacing consumables may be deposited by many different processes and may take the form of continuous wire (solid or tubular), covered electrodes or spray metal (wires or spray metal powders).

In those tables in the standard where particle size is specified, the sizes comply with AS-1152, Test Sieves, and are in line with ISO standards, following an R 40/3 preferred number series.

Guidance in the selection of a suitable consumable for a particular application is given in Appendix C. Additional information on this aspect is given in Australian Welding Research Association Technical Note 4.

---

\*In course of preparation.

©Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1982

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

## CONTENTS

	<i>Page</i>
<b>SECTION 1. SCOPE AND GENERAL</b>	
1.1 Scope .....	4
1.2 Application .....	4
1.3 Referenced Documents .....	4
1.4 Definitions .....	4
1.5 Classification .....	4
<b>SECTION 2. CONSUMABLES</b>	
2.1 Manufacture .....	6
2.2 Qualification Tests .....	6
2.3 Conformance Tests .....	6
2.4 Tests and Test Pieces Required .....	6
2.5 Retests .....	6
<b>SECTION 3. PROPERTIES AND REQUIREMENTS</b>	
3.1 Chemical Composition Requirements .....	7
3.2 Microstructure Requirements .....	7
3.3 Hardness Requirements .....	7
3.4 Packaging .....	7
3.5 Marking .....	7
3.6 Storage .....	7
<b>APPENDICES</b>	
A Methods of Test .....	13
B Atlas of Typical Photomicrographs .....	14
C Selection of Material .....	32

## STANDARDS ASSOCIATION OF AUSTRALIA

## Australian Standard

for

WELDING CONSUMABLES FOR BUILD-UP AND WEAR RESISTANCE—  
CLASSIFICATION SYSTEM

## SECTION 1. SCOPE AND GENERAL

**1.1 SCOPE.** This standard describes a classification system for welding consumables for build-up and wear resistance related to the properties of the weld deposit (chemical composition, microstructure and hardness) and to the method of deposition of, and the form of, the welding consumables.

Criteria relating to the selection of the welding consumable most appropriate for the particular surfacing requirement and additional information likely to be of use to the user in the choice of a consumable are provided in appendices.

**1.2 APPLICATION.** The classification system shall be in accordance with Section 1. The properties and requirements of the consumables shall be in accordance with Sections 2 and 3, as appropriate.

Appendix A describes the methods of test. Appendix B contains micrographs of the various alloy types and Appendix C gives additional information for users of the consumables.

**1.3 REFERENCED DOCUMENTS.** The following documents are referred to in this standard:

AS 1050	Methods for the Analysis of Iron and Steel
AS 1204	Structural Steels—Ordinary Weldable Grades
AS 1674	Fire Precautions in Cutting, Heating and Welding Operations
AS 1815	Method for Rockwell Hardness Test Part 1—Testing of Metals
AS K1	Methods for the Sampling and Analysis of Iron and Steel
AS Z5	Glossary of Metal Welding Terms and Definitions
ANSI/AWS	A5.4-78 Corrosion-resisting Chromium and Chromium-Nickel Steel Covered Electrodes
AWRA/AWI	Technical Note No 7 Health and Safety in Welding

**1.4 DEFINITIONS.** For the purpose of this standard, the terms given in AS Z5 and the following definitions apply:

**1.4.1 Impact**—the degree of severity of the impact expressed as follows:

- High impact—impact causing fracture or plastic deformation.
- Low impact—impact causing no perceptible deformation.

**1.4.2 Loading condition**—the degree of severity of the loading condition expressed as follows:

- High loading—gross local deformation of the surface.
- Medium loading—some local deformation.
- Low loading—no visible deformation.

**1.4.3 Lot (or batch) number**—a number from which the manufacturer is able to identify the constituents of the consumable and the date of manufacture.

**1.4.4 Shall and should**—the word 'shall' is to be understood as mandatory, and the word 'should' as non-mandatory, advisory or recommended.

**1.4.5 Self-shielded arc**—an arc where the shielding medium protecting the arc and metal in transfer is obtained from the electrode.

**1.4.6 Surfacing**—the application of a wear-resistant material to the surface of a component by welding, braze welding or spraying.

**1.4.7 Temperature**—the temperature due to the component's environment, e.g. in a furnace, or to heat generated during working, expressed as follows:

- High temperature—greater than 500°C (red heat and above).
- Medium temperature—over 200°C to 500°C.
- Low temperature—from ambient temperature to 200°C.

**1.4.8 Welding consumables**—electrodes (in the form of rod or continuous wire, either tubular or solid), filler rods, spray metal powders, spray metal wires and wire/flux combinations.

**1.5 CLASSIFICATION.**

**1.5.1 Basis of Classification.** Welding consumables for build-up and wear resistance shall be classified according to the following characteristics:

- Alloy group.
- Hardness of an undiluted deposit.
- Method of deposition.
- Form of the consumable.

**1.5.2 Designation of Classification.** The classification shall be designated by four digits followed by an alphanumeric suffix (see Fig. 1.1 for example). The elements of the designation shall have the following meanings:

- The *first digit* shall indicate the alloy group as listed below: