

Australian Standard™

**Insulators—Ceramic or glass—Hollow
pressurized and unpressurized—
Voltages greater than 1000 V a.c.**

This Australian Standard was prepared by Committee EL-010, Overhead Lines. It was approved on behalf of the Council of Standards Australia on 21 April 2005. This Standard was published on 20 May 2005.

The following are represented on Committee EL-010:

Australasian Railway Association
Australian Chamber of Commerce and Industry
Australian Electrical and Electronic Manufacturers Association
Australian Porcelain Insulators Association
Electricity Engineers Association (New Zealand)
Energy Networks Association

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 05018.

Australian Standard™

**Insulators—Ceramic or glass—Hollow
pressurized and unpressurized—
Voltages greater than 1000 V a.c.**

First published as AS IEC 62155—2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 6705 2

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee EL-010, Overhead Lines. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian, rather than an Australian/New Zealand Standard.

The objective of this Standard is to provide users and manufacturers of hollow ceramic and glass insulators with definitions and terms, test methods and acceptance criteria to facilitate their specification.

This Standard is identical with, and has been reproduced from IEC 62155, Ed. 1.0 (2003), *Hollow pressurized and unpressurized ceramic and glass insulators for use in electrical equipment with rated voltages greater than 1000 V*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number does not appear on each page of text and its identity is shown only on the cover and title page.
- (b) In the source text 'this international standard' should read 'this Australian Standard'.
- (c) A full point should be substituted for a comma when referring to a decimal marker.
- (d) Any French text on figures should be ignored.

The term 'informative' is used to define the application of the annex to which it applies. An informative annex is only for information and guidance.

CONTENTS

| | <i>Page</i> |
|--------|---|
| 1 | Scope and object 1 |
| 1.1 | General..... 1 |
| 1.2 | Hollow insulators or hollow insulator bodies intended for general use 1 |
| 1.3 | Ceramic hollow insulators intended for use with permanent gas pressure 2 |
| 2 | Normative references 2 |
| 3 | Terms and definitions 3 |
| 4 | Insulating materials 5 |
| 5 | General recommendations for design 6 |
| 5.1 | General recommendations for design of hollow insulators and hollow insulator bodies intended for general use..... 6 |
| 5.2 | Design rules for hollow insulators and hollow insulator bodies for use with permanent gas pressure 6 |
| 5.2.1 | Purpose 6 |
| 5.2.2 | Rules for design 6 |
| 5.2.3 | Determination of the design pressure 6 |
| 5.2.4 | Determination of the design temperature 7 |
| 5.2.5 | Determination of the type-test withstand bending moment 7 |
| 6 | Classification of the tests, sampling rules and procedures..... 8 |
| 6.1 | Classification of the tests 8 |
| 6.1.1 | Type tests 8 |
| 6.1.2 | Sample tests 9 |
| 6.1.3 | Routine tests 9 |
| 6.2 | Relevant tests for type, sample and routine tests 9 |
| 6.3 | Hollow insulator or hollow insulator body selection..... 11 |
| 6.3.1 | Hollow insulator or hollow insulator body selection for type tests 11 |
| 6.3.2 | Hollow insulator or hollow insulator body selection for sample tests 11 |
| 6.4 | Retest procedure for sample tests..... 12 |
| 6.5 | Quality assurance 12 |
| 7 | General test procedures and requirements..... 12 |
| 7.1 | Verification of the dimensions and roughness of ground surfaces 12 |
| 7.1.1 | General dimensional tolerances 13 |
| 7.1.2 | Creepage distance tolerance 13 |
| 7.1.3 | Tolerance of wall thickness 14 |
| 7.1.4 | Deviation from roundness of inner or outer core diameter 15 |
| 7.1.5 | Camber 15 |
| 7.1.6 | Position of end shed 16 |
| 7.1.7 | Tolerance on height of sanding and porcelain chamfered end flange 17 |
| 7.1.8 | Shed angle 18 |
| 7.1.9 | Tolerances on parallelism of end faces, coaxiality, eccentricity and angular deviation of fixing holes 18 |
| 7.1.10 | Control of the roughness of ground surfaces 18 |
| 7.1.11 | Acceptance criteria 18 |
| 7.2 | Mechanical failing load tests 18 |
| 7.2.1 | General requirements for pressure tests 19 |

| | | |
|--------|--|----|
| 7.2.2 | General requirements for bending tests..... | 19 |
| 7.2.3 | Torsion test..... | 20 |
| 7.2.4 | Tensile test..... | 20 |
| 7.2.5 | Compression test..... | 20 |
| 7.2.6 | Acceptance criteria for torsion, tensile and compression tests..... | 20 |
| 7.3 | Temperature cycle test..... | 21 |
| 7.3.1 | General requirements..... | 21 |
| 7.3.2 | Test procedure for insulators of ceramic material and toughened glass..... | 21 |
| 7.3.3 | Alternative test procedure for large insulators of ceramic material..... | 22 |
| 7.3.4 | Test procedure for insulators of annealed glass..... | 23 |
| 7.3.5 | Acceptance criteria..... | 23 |
| 7.4 | Porosity test..... | 23 |
| 7.4.1 | Test procedure..... | 23 |
| 7.4.2 | Acceptance criteria..... | 23 |
| 7.5 | Galvanizing test..... | 23 |
| 7.5.1 | Test procedure..... | 24 |
| 7.5.2 | Acceptance criteria..... | 24 |
| 8 | Type tests..... | 25 |
| 8.1 | Tests..... | 25 |
| 8.2 | Pressure test..... | 25 |
| 8.2.1 | Pressure test for hollow insulators or hollow insulator bodies intended for general use..... | 26 |
| 8.2.2 | Pressure test for ceramic hollow insulators or hollow insulator bodies intended for use with permanent gas pressure..... | 26 |
| 8.3 | Bending test..... | 26 |
| 8.3.1 | Bending test for hollow insulators or hollow insulator bodies intended for general use..... | 26 |
| 8.3.2 | Bending test for ceramic hollow insulators or hollow insulator bodies intended for use with permanent gas pressure..... | 26 |
| 9 | Sample tests..... | 26 |
| 9.1 | Tests for hollow insulators or hollow insulator bodies intended for general use..... | 26 |
| 9.2 | Tests for ceramic hollow insulators or hollow insulator bodies intended for use with permanent gas pressure..... | 27 |
| 10 | Routine tests..... | 27 |
| 10.1 | Tests for hollow insulators or hollow insulator bodies intended for general use..... | 27 |
| 10.2 | Tests for ceramic hollow insulators or hollow insulator bodies intended for use with permanent gas pressure..... | 27 |
| 10.3 | Routine visual inspection..... | 28 |
| 10.3.1 | Hollow insulators or hollow insulator bodies of ceramic material..... | 28 |
| 10.3.2 | Hollow insulators or hollow insulator bodies of glass material..... | 29 |
| 10.4 | Electrical routine test..... | 29 |
| 10.4.1 | Test procedure..... | 29 |
| 10.4.2 | Acceptance criteria..... | 30 |
| 10.5 | Routine mechanical tests for hollow insulators or hollow insulator bodies intended for general use..... | 30 |
| 10.5.1 | Routine pressure test..... | 30 |
| 10.5.2 | Routine bending test..... | 30 |
| 10.5.3 | Routine mechanical test determined by service applications..... | 30 |

| | |
|---|--------|
| 10.5.4 Acceptance criteria | 30 |
| 10.6 Routine mechanical tests for ceramic hollow insulators or hollow insulator bodies intended for use with permanent gas pressure..... | 31 |
| 10.6.1 Routine pressure test..... | 31 |
| 10.6.2 Routine bending test..... | 31 |
| 10.6.3 Routine mechanical test determined by service applications | 31 |
| 10.6.4 Acceptance criteria | 31 |
| 10.7 Routine thermal shock test..... | 31 |
| 11 Documentation..... | 32 |
| 11.1 Marking..... | 32 |
| 11.2 Records..... | 32 |
| Annex A (informative) Methods of testing for tolerances of parallelism, coaxiality, eccentricity, angular deviation, camber and shed angle of hollow insulators or hollow insulator bodies..... | 33 |
| Annex B (informative) Methods for bending tests of hollow insulator bodies | 39 |
| Annex C (informative) Alternative test method for the temperature-cycle test | 42 |
| Annex D (informative) Bending moment equivalent to the design pressure | 43 |
| Bibliography | 45 |
| Figure 1 – Bending moments..... | 8 |
| Figure 2 – Tolerance of wall thickness..... | 14 |
| Figure 3 – Deviation from roundness of inner or outer core diameter..... | 15 |
| Figure 4 – Effect of camber of the hollow insulator body..... | 16 |
| Figure 5 – Tolerance on height of sanding and porcelain chamfered end flange | 17 |
| Figure 6 – Definition of thickness ϕ mm for temperature-cycle test..... | 21 |
| Figure A.1 – Measuring of tolerances of form and position | 34 |
| Figure A.2 – Measuring of angular deviation of fixing holes | 35 |
| Figure A.3 – Method for measuring camber | 36 |
| Figure A.4 – Measuring shed angle | 36 |
| Figure A.5 – Centring with conical shank screws | 37 |
| Figure A.6 – Axial run-out..... | 37 |
| Figure A.7 – Parallelism and perpendicularity..... | 38 |
| Figure A.8 – Coaxiality and concentricity, evenness, alignment of fixing holes and proper sealing..... | 38 |
| Figure B.1 – Test ram for uniform distributed bending moment..... | 39 |
| Figure B.2 – Test ram for non-uniform distributed bending moment | 40 |
| Figure B.3 – Test method with bending load applied..... | 41 |
| Figure C.1 – Alternative test arrangement for the temperature-cycle test..... | 42 |
| Figure D.1 – Diameters for determining the equivalent bending moment to the design pressure..... | 44 |
| Table 1 – Typical examples of load combinations and weighting factors | 7 |
| Table 2 – Hollow insulators or hollow insulator bodies intended for general use – Relevant tests for type, sample and routine tests | 10 |

| | |
|---|----|
| Table 3 – Ceramic hollow insulators or hollow insulator bodies intended for use with permanent gas pressure – Relevant tests for type, sample and routine tests | 11 |
| Table 4 – Number of samples for sample tests | 12 |
| Table 5 – Selection of temperature difference for temperature cycle test | 22 |
| Table 6 – Selection of temperature difference for the alternative temperature-cycle test..... | 22 |
| Table 7 – Selection of temperature difference for insulators of annealed glass | 23 |

STANDARDS AUSTRALIA

Australian Standard**Insulators—Ceramic or glass—Hollow pressurized and unpressurized—
Voltages greater than 1000 V a.c.**

1 Scope and object**1.1 General**

This standard is applicable to

- ceramic and glass hollow insulators intended for general use in electrical equipment;
- ceramic hollow insulators intended for use with a permanent gas pressure in switchgear and controlgear.

These insulators are intended for indoor and outdoor use in electrical equipment, operating on alternating current with a rated voltage greater than 1 000 V and a frequency not greater than 100 Hz or for use in direct-current equipment with a rated voltage of greater than 1 500 V.

The hollow insulators are intended for use in electrical equipment, for example:

- circuit-breakers,
- switch-disconnectors,
- disconnectors,
- earthing switches,
- instrument transformers,
- surge arresters,
- bushings,
- cable sealing ends,
- capacitors.

It is not the object of this standard to prescribe dielectric type tests because the withstand voltages are not characteristics of the hollow insulator itself but of the apparatus of which it ultimately forms a part.

1.2 Hollow insulators or hollow insulator bodies intended for general use

Hollow insulators or insulator bodies of ceramic material or glass, intended for use

- without pressure;
- with permanent pressure ≤ 50 kPa gauge;
- with permanent gas pressure > 50 kPa gauge in combination with an internal volume < 1 l (1 000 cm³);
- with permanent hydraulic pressure.

The object of this standard is to define

- the terms used;
- the mechanical and dimensional characteristics of hollow insulators and hollow insulator bodies;