

Australian Standard™

**Coal preparation**

**Part 6: Determination of dust/moisture  
relationship for coal**

This Australian Standard was prepared by Committee MN/1, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 31 May 2000 and published on 22 August 2000.

---

The following interests are represented on Committee MN/1:

Australasian Institute of Mining and Metallurgy  
Australian Coal Association  
Australian Coal Preparation Society  
Australian Institute of Energy  
Bureau of Steel Manufacturers of Australia  
Coalfield Geology Council of N.S.W.  
CSIRO, Energy Technology  
Department of Mines and Energy, Qld  
Electricity Supply Association of Australia  
Institution of Engineers Australia  
Minerals Council of Australia  
University of Newcastle  
University of New South Wales  
University of Queensland

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

Australian Standard™

## Coal preparation

### Part 6: Determination of dust/moisture relationship for coal

First published as AS 4156.6—2000.

#### **COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 3461 8

## PREFACE

This Standard was prepared by the Standards Australia Committee MN/1, Coal and Coke and is based on the Rio Tinto Research and Technology Development\* Tumbler Dust Test as an alternative to ASTM D 441.

The objective of this Standard is to provide a comprehensive procedure that will allow determination of the dustiness of coal with respect to moisture and determine a dust extinction moisture (DEM), and evaluation of chemical for dust suppression.

The procedures shown in this Standard are based on a standard air flow. However, it is also possible to determine dust extinction moisture (DEM) values at other flow rates using the equipment described provided the actual air flow rates are recorded with the results.

The term 'informative' has been used in this Standard to define the application of the Appendix to which it applies. An informative appendix is for guidance and information only.

---

\* Rio Tinto Research and Technology Development is a unit of Rio Tinto Technology Group Legal Entity Technological Resources Pty Ltd ACN 002 183 557.

## CONTENTS

	<i>Page</i>
FOREWORD .....	4
1 SCOPE .....	5
2 REFERENCED DOCUMENTS .....	5
3 DEFINITIONS .....	5
4 SAFETY .....	5
5 EQUIPMENT .....	6
6 REAGENT .....	6
7 SAMPLE PREPARATION—INITIAL .....	6
8 SAMPLE PREPARATION—TOTAL MOISTURE ADJUSTMENT .....	6
9 SAMPLE PREPARATION—REAGENT TESTING .....	8
10 DUST DETERMINATION .....	9
11 CALCULATION .....	10
12 REPORT .....	10
13 PRECISION .....	10
APPENDICES	
A WORKED EXAMPLE .....	11
B WORKSHEET EXAMPLE .....	14

## FOREWORD

The development of the dust/moisture curve provides an indication of the likely response of different coal types to drying or water addition during mining and handling processes. The dust/moisture curve provides a good basis for comparing the response of different coal types. Understanding the dust/moisture characteristics of a coal will allow minimized water addition to the product for dust suppression. This will in turn assist in water conservation at mines and other handling facilities, as well as minimizing the total moisture of the product.

This Standard describes a reliable measurement of dustiness of coal and extends to cover the relationship between dust and total moisture utilizing the Rio Tinto Dust Tumbler Test. This test provides a quantitative measure of the dustiness of a coal that can be used to predict operational dust problems, and is suitable also, for the assessment of dust suppression chemicals. The Rio Tinto Dust Tumbler Test follows earlier work by Farrugia et al\*.

The Rio Tinto Dust Tumbler Test was developed using rotating equipment in a controlled temperature and humidity environment, and uses a stream of air to remove particles which become airborne during the tumbling process. It is a batch test in which dust particles ( $-150\ \mu\text{m}$  particles) are collected into a pre-weighed filter bag and weighed. From this weight a dust number, calculated as the mass yield of dust multiplied by 100 000, is determined for the test total moisture. Only one kilogram of sample is required for each dust test, but eight sample lots are required to develop the dust/moisture curve for a particular coal, i.e. approximately 10 kg is required for each coal type.

This dust test can be repeated with sub-samples at different coal total moisture levels to develop a dust/moisture curve. The slope of the curve provides information on how sensitive the dustiness is to changes in total moisture and a dust number of 10 has been used to provide a comparison between coals.

The test has been successfully used for several years on many coals and other bulk materials. The results have been correlated with operating practice. The method has been applied to the evaluation of dust control products, and the determination of dust elimination total moisture requirements for coal handling systems.

---

\* FARRUGIA, T.R., AHMED, N. and JAMESON, G.J., A new technique for measuring dustiness of coal, *Journal of Coal Quality*, Vol. 8, No. 2, pp. 51-55, April-June 1989.

# STANDARDS AUSTRALIA

## Australian Standard Coal preparation

### Part 6: Determination of dust/moisture relationship for coal

#### 1 SCOPE

This Standard sets out a laboratory procedure for the dust testing of higher rank coals. The procedure defines a means of evaluating the dust/moisture relationship characteristic of a coal and a dust extinction moisture (DEM).

NOTE: In this Standard an experimental dust number of 10 has been used in the example given in Appendix A.

#### 2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- 1038 Coal and coke — Analysis and testing
- 1038.1 Part 1: Higher rank coal — Total moisture
- 2706 Numerical values — Rounding and interpretation of limiting values
- 3881 Higher rank coal — Size analysis

#### 3 DEFINITIONS

For the purpose of this Standard, the definitions below apply.

##### 3.1 Dust

Particles of 150 µm or less diameter entrained in an air stream.

##### 3.2 Dust extinction moisture (DEM)

The total moisture at which a dust number of 10 is attained on the dust/moisture curve. DEM is a useful point for comparing different coals and the effectiveness of reagents.

#### 4 SAFETY

The following safety precautions shall be observed:

- (a) To prevent nitrogen build up within the laboratory, the exhaust tube of the minimum free space oven shall remain clear of obstruction.
- (b) Safety glasses shall be worn at all times.
- (c) The minimum head space oven's exhaust tube shall remain free of obstruction to prevent nitrogen build up within the laboratory.
- (d) A dust mask shall be worn when handling coal. Coal with less than 5% quartz has been assigned a time weighted average exposure standard of 3 mg/m<sup>3</sup> (respirable) by the National Occupational Health and Safety Commission.
- (e) Cloth or leather gloves shall be worn when using ovens.
- (f) The hazards associated with a reagent shall be determined prior to use. Instructions on all relevant Material Safety Data Sheets (MSDS) shall be followed.