

Australian Standard™

**Electroplated coatings of rhodium for  
general engineering applications**

This Australian Standard was prepared by Committee MT-009, Metal Finishing. It was approved on behalf of the Council of Standards Australia on 3 February 2004 and published on 22 March 2004.

---

The following are represented on Committee MT-009:

Australian Aluminium Council  
Australian Industry Group  
Australian Institute of Metal Finishing  
Australian Paint Manufacturer's Federation  
Department of Defence  
Galvanizers Association of Australia  
Powder Coaters Association  
The Royal Australian Chemical Institute  
Society of Automotive Engineers—Australasia  
Telstra Corporation

---

### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.org.au](mailto:mail@standards.org.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

STANDARDS AUSTRALIA

---

**RECONFIRMATION**

**OF**

**AS 2429—2004**

**Electroplated coatings of rhodium for general engineering applications**

---

**RECONFIRMATION NOTICE**

Technical Committee MT-009 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 20 March 2017.

The following are represented on Technical Committee MT-009:

Australasian Institute of Surface Finishing  
Australian Chamber of Commerce and Industry  
Australian Industry Group  
Australian Steel Institute  
Bureau of Steel Manufacturers of Australia  
Galvanizers Association of Australia  
Galvanizing Association of New Zealand  
New Zealand Metal Roofing Manufacturers

## NOTES

Australian Standard™

**Electroplated coatings of rhodium for  
general engineering applications**

Originated as AS K170—1967.  
Previous edition AS 2429—1981.  
Second edition 2004.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 5778 2

## PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-009, Metal Finishing, at the request of industry to supersede AS 2429—1981, *Electroplated coatings of rhodium for general engineering applications*.

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than Australian/New Zealand Standard.

The objective of this Standard is to specify the requirements for electroplating rhodium on metallic substrates.

The objective of this revision is to include new plating classifications, applications and hydrogen embrittlement treatments.

In the preparation of this Standard cognizance was taken of ASTM B634-88:1999, *Electrodeposited coatings of rhodium for engineering use*.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a standard, whereas an 'informative' appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
FOREWORD.....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE .....	5
1.2 REFERENCED DOCUMENTS .....	5
1.3 DEFINITIONS .....	6
SECTION 2 CONDITION OF THE METALLIC SUBSTRATE SURFACE	
2.1 PROCESS REQUIREMENTS.....	7
2.2 PREPLATING.....	7
2.3 POST-PLATING .....	7
SECTION 3 COATING REQUIREMENTS	
3.1 GENERAL .....	8
3.2 PARTIALLY COATED SURFACES.....	8
3.3 THICKNESS CLASSIFICATIONS.....	8
3.4 SIGNIFICANT SURFACES.....	8
3.5 APPEARANCE .....	9
SECTION 4 SAMPLING.....	10
SECTION 5 SEPARATE TEST SPECIMENS	
5.1 GENERAL .....	11
5.2 SEPARATE TEST SPECIMENS .....	11
5.3 COATING THICKNESS.....	11
5.4 SEPARATE SPECIMENS FOR EMBRITTLEMENT RELIEF .....	12
5.5 REFLECTIVITY .....	12
APPENDICES	
A PURCHASING GUIDELINES.....	13
B MEANS OF DEMONSTRATING COMPLIANCE WITH THIS STANDARD.....	14
C GUIDANCE ON THE USE OF STRIKES AND UNDERCOATS PRIOR TO RHODIUM PLATING .....	16
D PRETREATMENT OF IRON OR STEEL TO REDUCE THE RISK OF HYDROGEN EMBRITTLEMENT.....	17
E POST-COATING TREATMENTS OF IRON OR STEEL TO REDUCE THE RISK OF HYDROGEN EMBRITTLEMENT .....	20
F APPLICATIONS FOR ELECTRODEPOSITED RHODIUM .....	24

## FOREWORD

Electroplated coatings of rhodium are hard (approximately HV 800) and do not tarnish readily which makes such coatings important in the general engineering field but more particularly in the fields of electronics and electrical engineering.

High reflectivity of rhodium in the infrared and visible sections of the spectrum, in association with its resistance to tarnishing, make it suitable for use as a reflector coating.

Rhodium is chemically inert and very resistant to acids and other corrosive materials at ordinary temperatures but is subject to oxidation at temperatures above 400°C.

Since electroplated coatings of rhodium are usually thin, arcing or sparking may lead to the coating being penetrated, and hence rhodium-plated contacts should only be used in radio-frequency and audio-frequency circuits where current and voltage are low. Arcing and sparking problems do not arise with sliding contacts, hence it is in this field that rhodium electrodeposits are particularly useful. Sliding contacts of rhodium working against each other tend to wear rapidly, and it is usual for one of the contact members to be an alternative noble metal (e.g. gold), or for contact member that is subject to the greater wear to have a thicker rhodium coating and for the contact pressure to be reduced to the minimum. Typical thickness of coatings for applications are given in this Standard.

Rhodium may be deposited directly onto silver, copper, brass, phosphor-bronze (copper-tin-phosphorous), nickel, nickel-brass, and beryllium-copper alloys. Phosphor-bronze and beryllium-copper alloys require special treatment to ensure adequate adhesion of rhodium coatings.

Owing to the acidic nature of rhodium plating baths and the position of rhodium in the electrochemical series, rhodium cannot be plated directly onto iron, steel, zinc, aluminum, lead or tin. Accordingly the use of an underplate or a strike on these metals is necessary.

## STANDARDS AUSTRALIA

### Australian Standard

## Electroplated coatings of rhodium for general engineering applications

### SECTION 1 SCOPE AND GENERAL

#### 1.1 SCOPE

This Standard specifies requirements for electroplated coatings of rhodium on metallic substrates for general engineering applications.

Purchasing guidelines on requirements to be specified and/or agreed at the time of enquiry or order are shown in Appendix A.

In addition, the Standard provides for the optional application of pretreatment of iron or steel to reduce the risk of hydrogen embrittlement as shown in Appendix D and post-coating treatment of iron or steel as shown in Appendix E.

#### NOTES:

- 1 The means of complying to the Standard are shown in Appendix B.
- 2 Guidance on the use of strikes and undercoats are shown in Appendix C.
- 3 Typical applications for electroplated rhodium are shown in Appendix F.

#### 1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard.

#### AS

- |          |  |
|----------|--|
| 1199     | Sampling procedures for inspection by attributes   |
| 1199.0   | Part 0: Introduction to the ISO 2859 attribute sampling system   |
| 1199.1   | Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection                                 |
| 1391     | Methods for tensile testing of metals (ISO 6892)   |
| 1627     | Metal finishing—Preparation and pretreatment of surfaces   |
| 1627.1   | Part 1: Removal of oil, grease and related contamination   |
| 1627.2   | Part 2: Power tool cleaning (ISO 8504-3)   |
| 1627.4   | Part 4: Abrasive blast cleaning (ISO 8504-2)   |
| 1627.5   | Part 5: Pickling   |
| 1627.6   | Part 6: Chemical conversion treatment of metals  |
| 2331     | Methods of tests for metallic and related coatings   |
| 2331.1.1 | Method 1.1: Local thickness tests—Micrographic examination of cross-sections   |
| 2331.1.5 | Method 1.5: Local thickness test—Beta-backscatter method   |
| 2331.2.1 | Method 2.1: Tests for average coating mass per unit area or for thickness—Dissolution methods—Strip and weigh and analytical |
| 2331.4.1 | Physical tests—Qualitative adhesion tests  |
| 2483     | Metal finishing—Recommended sampling plans for the inspection and testing of coatings (ISO 4519:1980, MOD)                   |
| 4291     | Mechanical properties of fasteners made of carbon steel and alloy steel  |
| 4291.1   | Part 1: Bolts, screws and studs  |