

Amendment 1 - Oct 1990 Dup

AS 3577-1989

~~LOAN COPY~~
~~INFORMATION CENTRE~~
~~STANDARDS AUSTRALIA~~

SUPERSEDED BY:
AS 3577-1999

Revision see DR 98446

Australian Standard®

**Steel cylinders for compressed
gases—Welded—150 kg to 500 kg**

STANDARDS AUSTRALIA



D

This Australian Standard was prepared by Committee ME/2, Gas Cylinders. It was approved on behalf of the Council of Standards Australia on 14 September 1988 and published on 13 February 1989.

The following interests are represented on Committee ME/2:

Aluminium Development Council
Australasian Steamship Owners Federation
Australian Chamber of Commerce
Australian Liquefied Petroleum Gas
Australian Underwater Federation
Australian Welding Institute
Board of Fire Commissioners, N.S.W.
Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Department of Defence
Department of Employment and Industrial Affairs, Qld
Department of Employment and Industrial Affairs, Vic.
Department of Industrial Relations and Employment, N.S.W.
Department of Labour, S.A.
Department of Labour and Industry, Tas.
Department of Mines, Qld
Department of Mines and Energy, N.T.
Department of Occupational Health, Safety and Welfare, W.A.
Department of Territories
Insurance Council of Australia
Fire Protection Industry Association of Australia
Railways of Australia Committee

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 86056.

Australian Standard®

**Steel cylinders for compressed
gases—Welded—150 kg to 500 kg**

First published as part of AS B15—1950.
Revised and redesignated AS B115—1958.
Second edition 1966.
In part revised and redesignated AS 3577—1989.

PREFACE

This Standard was prepared by the Standards Australia Committee on Gas Cylinders, to supersede (in part) B115—1966, *Welded or brazed steel cylinders for compressed gases*. It is one of a suite of four Standards for welded and brazed cylinders for compressed gases, the other Standards being as follows:

AS 2468, *Steel cylinders for compressed gases—Brazed—0.1 kg to 11 kg*

AS 2469, *Steel cylinders for compressed gases—Brazed—0.1 kg to 11 kg*

AS 2470, *Steel cylinders for compressed gases—Welded—11 kg to 150 kg*

AS B115—1966, has not been withdrawn, but has been declared 'obsolescent' and is being retained for reference purposes.

AS 3509, *LP gas fuel vessels for automotive use*, was used as a model for some requirements for larger welded gas cylinders, particularly for radiography requirements.

This Standard provides for gas cylinders produced in large quantities. Users of this Standard should note that the relevant Inspecting Authority will require either quality control procedures to be employed at the point of manufacture in Australia, or sampling and testing at the point of entry into Australia. It should also be noted that before a gas cylinder can be first filled in Australia it must be stamped with a Standards Australia Approved Gas Cylinder Test Station registered mark in accordance with the relevant Standard of the AS 2030 series.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the Head Office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
1 SCOPE	4
2 REFERENCED DOCUMENTS	4
3 DEFINITIONS	4
4 STEEL	4
5 DESIGN AND CONSTRUCTION	4
6 WELDING	8
7 INSPECTION AND TESTING	8
8 HEAT TREATMENT	9
9 MECHANICAL TESTS	10
10 PRESSURE TESTS	10
11 TYPE TESTS	11
12 SURFACE COATINGS	12
13 RECORD AND TEST CERTIFICATE(S)	12
14 STAMPING	12
15 PREPARATION FOR DESPATCH	12
 APPENDICES	
A SUGGESTED MINIMUM INFORMATION TO BE SUPPLIED BY THE PURCHASER	13
B LIST OF REFERENCED DOCUMENTS	14
C RESISTANCE SPOT WELDING FOR NON-PRESSURE-RETAINING ATTACHMENTS	16
D LOCATIONS OF TEST SPECIMENS....	17
E SUGGESTED FORM OF MANUFACTURER'S RECORD AND TEST CERTIFICATE	18

STANDARDS AUSTRALIA

Australian Standard

STEEL CYLINDERS FOR COMPRESSED GASES—WELDED—150 kg to 500 kg

1 SCOPE. This Standard specifies requirements for welded steel cylinders with one longitudinal joint, and not more than two circumferential joints of water capacity not less than 150 kg nor more than 500 kg, which have test pressures from 1750 kPa to 7000 kPa, and are intended for the storage and transport of compressed gases in accordance with AS 2030.1.

NOTES:

1. A gas cylinder manufactured by welding but which includes any brazing of or on the pressure-retaining portions is for the purpose of this Standard considered to be a brazed gas cylinder.
2. Other Australian Standards for brazed and welded gas cylinders are AS 2468, AS 2469, and AS 2470.
3. Appendix A lists the suggested minimum information that should be supplied by the purchaser when ordering gas cylinders to this Standard.

2 REFERENCED DOCUMENTS. A list of documents referred to in this Standard is given in Appendix B.

3 DEFINITIONS. For the purpose of this Standard the definitions given in AS 2030.1 and those below apply.

Inspector—a person, acceptable to the Inspecting Authority, who ensures and certifies that all the inspections specified herein have been carried out and that the cylinders comply with all the requirements of this Standard.

Attachment—any fitting attached to the pressure-retaining sections of the cylinder by welding, including bosses, pads, valve protection rings, and footings.

4 STEEL.**4.1 Cylindrical sections and ends.**

4.1.1 Steelmaking process. The steel shall be made by the open hearth, basic oxygen, or an electric process. Rimmed steels shall not be used for arc welded components.

NOTE: Rimmed steels are considered not suitable for arc-welded components because of problems associated with welding of the slit edge due to the possibility of lamination and segregation problems.

4.1.2 Cast analysis. The cast analysis shall conform to Table 1, except that where resistance-welded attachments are to be added to the cylinder the maximum carbon content of the pressure-retaining portion of the joint shall be 0.15%.

TABLE 1
CAST ANALYSIS

Elements (other than iron)	Cast analysis (max.), percent
Carbon	0.25
Manganese	1.70
Silicon	0.40
Micro-alloying elements (total)	0.15
Sulphur	0.040
Phosphorus	0.040

NOTES:

1. Grain-refining elements, i.e. titanium (up to 0.040%) and aluminium (up to 0.1%), may be added.

2. Examples of micro-alloying elements are titanium (where greater than 0.040%), niobium, and vanadium.
3. AS 1594 and equivalent overseas Standards specify some acceptable grade of steel with conforming cast analyses.
4. Residual elements up to the following individual amounts or a sum of 0.7% of all listed elements are considered to be incidental:

Chromium	0.30%
Copper	0.35%
Molybdenum	0.10%
Nickel	0.35%

4.1.3 Residual elements. Elements not shown in Table 1 shall not be intentionally added to the steel, other than for the purpose of finishing the heat.

All reasonable precautions shall be taken to prevent the addition of such elements during manufacture, and the quantities present shall not be detrimental to the application of steel for a welded gas cylinder.

4.1.4 Weldability. The steel for components to be welded shall be of a weldable quality.

4.1.5 Mechanical properties. When a completed gas cylinder is tested in accordance with Clause 9.3, the yield and tensile strength values obtained shall be not less than the values used in the equations in Clause 5.1.1.

When determined in accordance with Clause 9.3, the elongation shall be not less than 20% minus 1 percentage unit for each increment of 50 MPa by which the measured tensile strength exceeds 350 MPa, but in any case not less than 16%.

4.2 Attachments. Attachments shall be of steel complying with the requirements of Clause 4.1, except that for resistance-welded attachments the steel of both components of the joint shall be weldable and be subject to a maximum carbon content of 0.15%.

5 DESIGN AND CONSTRUCTION.**5.1 Minimum thickness.**

5.1.1 Cylindrical portions of shell (not including any part of the ends). The thickness of the cylindrical portion shall be not less than 1.75 mm, nor less than the greater of those calculated from the following equations:

$$t = 2.5 \left(\frac{D_i}{R_m} \right)^{1/2} \dots (1) \text{ and } t = \frac{p_h D_o}{2f_n + P_h} \dots 5.1.1(2)$$

where

t = minimum finished thickness of the cylinder, in millimetres

D_i = nominal internal diameter, in millimetres

D_o = outside diameter of cylindrical section, in millimetres

p_h = test pressure (the design test pressure specified in AS 2030.1), in megapascals