

Australian Standard®

**PERFORATED PLASTICS
DRAINAGE AND EFFLUENT PIPE
AND FITTINGS**

**Part 2—PERFORATED EFFLUENT
PIPE AND ASSOCIATED
FITTINGS FOR SEWERAGE
APPLICATIONS**

This Australian standard was prepared by Committee PL/26, Perforated Plastics Pipe. It was approved on behalf of the Council of the Standards Association of Australia on 8 September 1982 and published on 10 January 1983.

The following interests were represented on the committee responsible for the preparation of this standard:

CSIRO, Division of Horticultural Research

Department of Agriculture, Victoria

Health Commission of New South Wales

Health Commission of Victoria

Health Surveyors' Institute

National Association of Australian State Road Authorities

Plastics Institute of Australia Incorporated

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 80214.

Australian Standard®

**PERFORATED PLASTICS
DRAINAGE AND EFFLUENT PIPE
AND FITTINGS**

**Part 2—PERFORATED EFFLUENT
PIPE AND ASSOCIATED
FITTINGS FOR SEWERAGE
APPLICATIONS**

First published 1983

PREFACE

This standard was prepared by the Association's Committee on Perforated Plastics Pipe under the direction of the Plastics Standards Board.

This is a performance standard and therefore all requirements and tests are related to end use. It is not the intention of this standard to establish how strong the product is, but rather to determine if the product is strong enough to fulfil the desired function.

The requirements and tests contained in this standard relate to field conditions as follows:

Bending—pipe is often bent at temperatures close to 0°C.

Straightening—coils are often unwound in cold conditions.

High temperature impact resistance—pipe laid out in the hot sun must not be so soft that it is damaged during backfilling.

Low temperature impact resistance—to determine that pipe will not fail due to handling, fill material or degradation in service.

Pipe stiffness—pipe must be stiff enough to withstand the design loads after back-filling and settlement.

Elongation—pipe must not excessively elongate during installation.

Joint separation—joints must not separate when subjected to tensile forces induced when laying.

In the preparation of this standard the committee gave consideration to ASTM D 2729, Poly(vinyl chloride) (PVC) Sewer Pipe and Fittings, and a specification prepared by the Department of Health, Victoria.

The standard is presented in two parts. Part 1 (AS 2439, Part 1) covers plastics drainage pipe and fittings for both corrugated pipe (Type 1) and smooth wall pipe (Type 2). This Part 2 specifies requirements for corrugated effluent pipe (Type 3) and smooth wall effluent pipe (Type 4). Information on the installation of perforated plastics effluent pipe is available from the relevant State Health Authority.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
SPECIFICATION	
1 Scope	4
2 Referenced Documents	4
3 Types and Classification	4
4 Material	4
5 Freedom from Defects	4
6 Dimensions	4
7 Perforations	5
8 Fittings	5
9 Packaging	5
10 Conditioning of Test Specimens	5
11 Performance Requirements	5
12 Marking	6
APPENDICES	
A Determination of Compliance of a Lot	7
B Methods for Measurement of Dimensions	8
C Bending Test (Type 3 Only)	10
D Straightening Test at 0°C (Type 3 Only)	11
E Method of Test for High Temperature Impact Resistance	12
F Method of Test for Low Temperature Impact Resistance	13
G Method for Determining Elongation and Perforation Deformation (Type 3 Only)	14
H Method for Determining Pipe Stiffness and Perforation Deformation . .	15
J. Method of Test for Joint Separation (Type 3 Only)	16

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
for
PERFORATED PLASTICS DRAINAGE AND EFFLUENT PIPE AND FITTINGS

**PART 2—PERFORATED EFFLUENT PIPE AND ASSOCIATED FITTINGS FOR
SEWERAGE APPLICATIONS**

1 SCOPE. This standard specifies requirements for perforated plastics effluent pipe and associated fittings intended for effluent disposal from septic sewerage systems.

NOTE: Advisory information on the determination of compliance of a 'lot' with this standard is given in Appendix A.

2 REFERENCED DOCUMENTS. The following standards are referred to in this standard:

AS 1199 Sampling Procedures and Tables for Inspection by Attributes

AS 1327 Standard Environments for Conditioning and Testing Plastics Materials

AS 1399 Guide to AS 1199, Sampling Procedures and Tables for Inspection by Attributes

AS 1821 to

AS 1823 Suppliers Quality Control Systems—Levels 1 to 3

AS 2000 Guide to AS 1821—1823, Suppliers Quality Control Systems

3 TYPES AND CLASSIFICATION.

3.1 Types. Plastics effluent pipe shall be classified into types as follows:

(a) *Type 3*—corrugated pipe.

(b) *Type 4*—smooth wall pipe.

3.2 Classification. Each type of plastics effluent pipe shall be classified into classes as follows:

(a) *Class 100*—at 5 percent deflection a minimum force of 100 kN and at 10 percent deflection a minimum force of 80 kN per metre deflection per metre length of pipe.

(b) *Class 200*—at 5 percent deflection a minimum force of 200 kN and at 10 percent deflection a minimum force of 160 kN per metre deflection per metre length of pipe.

(c) *Class 400*—at 5 percent deflection a minimum force of 400 kN and at 10 percent deflection a minimum force of 300 kN per metre deflection per metre length of pipe.

NOTE: Class 100 pipe is intended for use in effluent disposal trenches; Class 200 pipe where above normal loading is expected; and Class 400 pipe for the under-draining of sub-surface sand filters.

4 MATERIAL. Any suitable plastics materials may be used to manufacture the pipe or fitting, provided that the pipe or fitting so formed is capable of complying with the performance requirements of

this standard at the time of manufacture and after a period of up to 6 months of outdoor exposure.

Any plastics material unable to comply with the requirements of this standard after six months outdoor exposure shall be protected at the time of manufacture by suitable means in order to provide a satisfactory storage life of at least 6 months in outdoor conditions.

Re-work material may be used.

5 FREEDOM FROM DEFECTS. Pipe and fittings shall not contain any pores, bubbles, cracks or foreign matter or other faults that may affect the performance of the pipe or fitting.

6 DIMENSIONS.

6.1 Diameter. When measured in accordance with Paragraph B4(a) of Appendix B, the outside diameter of Type 3 pipe shall conform to the dimensions of Table 1 and the outside diameter of Type 4 pipe shall conform to the dimensions of Table 2.

TABLE 1
DIMENSIONS OF TYPE 3 PIPE

millimetres		
Nominal outside diameter	Outside diameter	
	Minimum	Maximum
80	79.0	82.0
100	99.0	102.0
160	158.0	163.0

TABLE 2
DIMENSIONS OF TYPE 4 PIPE

millimetres		
Nominal diameter	Outside diameter	
	Minimum	Maximum
90	90.0	90.3
100	110.0	110.4
160	160.0	160.5

NOTE: The nominal diameters given in Table 2 are not necessarily the same as the actual outside diameters, as Type 4 pipes before slotting may conform to other standards.