

DR 97340

1999 ed FWD 981218

1999 ED.



Standards
 Association of
 Australia



Australian Standard[®] 1085.4—1988

RAILWAY PERMANENT WAY MATERIAL Part 4—FISHBOLTS AND NUTS



This Australian Standard was prepared by Committee CE/2, Railway Permanent Way Materials. It was approved on behalf of the Council of the Standards Association of Australia on 4 March 1988 and published on 9 May 1988.

The following interests are represented on Committee CE/2:

Bureau of Steel Manufacturers of Australia
Confederation of Australian Industry
Railways of Australia Committee

Review of Australian Standards. To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 85338.

AUSTRALIAN STANDARD

**RAILWAY PERMANENT WAY
MATERIAL**

**Part 4
FISHBOLTS AND NUTS**

AS 1085.4—1988

First published in part as AS E25—1928.
AS E26 first published—1928.
Second edition AS E25—1937.
Second edition AS E26—1937.
Third edition AS E25—1949.
Third edition AS E26—1949.
Fourth edition AS E25—1964.
Fourth edition AS E26—1964.
AS E25—1964 revised and redesignated in part
AS 1085.4—1978 and as part of AS 1085.6—1978.
AS E26—1964 revised and redesignated in part
AS 1085.5—1978 and as part of AS 1085.6—1978.
Second edition AS 1085.4—1979.
Second edition AS 1085.5—1979.
Second edition AS 1085.6—1979.
AS 1085.4—1979, AS 1085.5—1979 and
AS 1085.6—1979 revised, amalgamated and
redesignated AS 1085.4—1988.

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 4957 2

PREFACE

This Standard was prepared by the Association's Committee on Railway Permanent Way Materials. It is a revision and amalgamation of AS 1085.4—1979*, AS 1085.5—1979† and AS 1085.6—1979‡ in consequence of which—

- (a) it is designated AS 1085.4—1988;
- (b) it supersedes AS 1085.4—1979; and
- (c) both AS 1085.5—1979 and AS 1085.6—1979 are now withdrawn.

* AS 1085, *Railway permanent way material, Part 4—1979, Non-heat-treated fishbolts (interference fit)*

† AS 1085, *Railway permanent way material, Part 5—1979, Heat-treated fishbolts (medium thread class)*

‡ AS 1085, *Railway permanent way material, Part 6—1979, Nuts for fishbolts*

CONTENTS

	<i>Page</i>
1 SCOPE	3
2 REFERENCED DOCUMENTS	3
3 CHEMICAL COMPOSITION	3
4 FISHBOLTS	3
5 NUTS	6
6 MARKING	8
7 ROUNDING OF NUMBERS	8
APPENDIX A. PURCHASING REQUIREMENTS	9

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1988

Users of Standards are reminded that copyright subsists in all SAA publications. Except where the Copyright Act otherwise allows, no part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia. Requests for permission should be directed to the Head Office of the Association. Where such requests relate to the reproduction of the whole or a substantial part of any Standard, permission may be conditional on an appropriate royalty payment.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

RAILWAY PERMANENT WAY MATERIAL

PART 4: FISHBOLTS AND NUTS

1 SCOPE. This Standard specifies requirements for steel non-heat-treated or heat-treated fishbolts and nuts for use in conjunction with steel rails and fishplates rolled in accordance with AS 1085.1 and AS 1085.2.

NOTE: Nuts to be used for interference fit fishbolts require to be batched with near to zero variation in thread size. It is essential that the purchaser supply the manufacturer with certain information when enquiring about or ordering nuts to this Standard. Purchasing guidelines are given in Appendix A.

2 REFERENCED DOCUMENTS. The documents below are referred to in this Standard.

AS

- 1050 Methods for the analysis of iron and steel
 1085 Railway permanent way material
 Part 1: Steel rails (AS 1085.1)
 Part 2: Fishplates (AS 1085.2)
 1213 Iron and steel—Methods of sampling
 1252 High-strength steel bolts with associated nuts and washers for structural engineering
 1275 Metric screw threads for fasteners
 1391 Methods for tensile testing of metals
 1442 Carbon steels and carbon-manganese steels—Hot-rolled bars and semi-finished products
 1654 Limits and fits for engineering
 1721 General purpose metric screw threads
 1815 Method for Rockwell hardness test
 Part 1: Testing of metals (AS 1815.1)
 1816 Method for Brinell hardness test
 Part 1: Testing of metals (AS 1816.1)
 1817 Method for Vickers hardness test
 Part 1: Testing of metals (AS 1817.1)
 2706 Numerical values—Rounding and interpretation of limiting values
 K1 Methods for the sampling and analysis of iron and steel

3 CHEMICAL COMPOSITION.

3.1 General. The steel used for the manufacture of fishbolts and nuts shall comply with the requirements of AS 1442.

3.2 Material specification. The steel grades used shall be selected from appropriate grades in the tables of AS 1442, and comply with the chemical composition limits (cast analysis) as set out in Table 1 below.

TABLE 1
CHEMICAL COMPOSITION
CAST ANALYSIS

Product	percent			
	Carbon	Manganese	Phosphorus	Sulphur
Fishbolt	0.55 max.	—	0.05 max.	0.05 max.
Nut	0.58 max.	0.25 min.	0.06 max.	0.15 max.

4 FISHBOLTS.

4.1 Manufacture. Fishbolts may be produced by hot or cold forging with or without secondary machining. Screw threads shall be formed by thread rolling or thread cutting.

NOTE: When the threads are produced by rolling, small laps are commonly present at the crests and are generally of a magnitude which is not detrimental to the performance of the bolt. A lap formed at the crest of the thread, perpendicular to the axis of the thread of the fishbolt, is not considered cause for rejection if the lap does not exceed 33 percent of the depth of thread.

4.2 Shape, dimensions and finish. The shape and dimensions of fishbolts shall be in accordance with Figure 1 and the following requirements:

- (a) Bolts shall be cleanly finished, sound and free from defects detrimental to their end use.
 (b) Ends of fishbolts shall be either reasonably square with the centreline of the shank or rounded (see Figure 1). Where the ends of the fishbolts are finished square, a nominal 45° chamfer is to be provided to a depth slightly exceeding the depth of the thread.

4.3 Mechanical properties. The mechanical properties of non-heat-treated fishbolts shall comply with Table 2 and of heat-treated fishbolts with Table 3.

Heat-treated fishbolts shall be hardened and then tempered by being uniformly reheated to a minimum temperature of 450°C.

TABLE 2

MECHANICAL PROPERTIES OF
NON-HEAT-TREATED FISHBOLTS

Property	Requirement
Minimum tensile strength	540 MPa
Minimum yield stress	270 MPa
Minimum elongation on $5.65 \sqrt{S_0}$ *	16%

TABLE 3

MECHANICAL PROPERTIES OF
HEAT-TREATED FISHBOLTS

Property	Requirement
Minimum tensile strength	800 MPa
Stress at permanent set limit, $R_r 0.2$	640 MPa
Minimum elongation on $5.65 \sqrt{S_0}$ *	12%

* See Figure 2.

4.4 Screw threads. Profile and basic dimensions of the fishbolt screw threads shall be in accordance with the ISO coarse series 6g for external screw threads as given in AS 1275 and AS 1721. For non-heat-treated fishbolts requiring an interference fit, deviation and manufacturing tolerances shall be such that the torque requirements of Clause 4.5.3 are satisfied.