

Australian Standard™

**Methods of testing materials for
resistance to fungal growth**

**Part 11: Resistance of rubbers
and plastics to surface fungal
growth**

This Australian Standard was prepared by Committee CH/20, Resistance to Fungal Growth. It was approved on behalf of the Council of Standards Australia on 30 November 1998 and published on 5 February 1999.

The following interests are represented on Committee CH/20:

Australian Paint Manufacturers Federation
Australian Wool Research and Promotion Organization
CSIRO Forestry & Forest Products
Department of Defence (Australia)
Federated Tanners Association
Plastics and Chemicals Industry Association Incorporated
Surface Coatings Association Australia
The Textile Institute (Southern Australia Section)

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 98443.

Australian Standard™

**Methods of testing materials for
resistance to fungal growth**

**Part 11: Resistance of rubbers
and plastics to surface fungal
growth**

Originated as AS 1157.11—1978.
Second edition 1999.

PREFACE

This Standard was prepared by the Standards Australia Committee CH/20, Resistance to Fungal Growth to supersede AS 1157.11—1978.

This is Part 11 of a series of methods for assessing the resistance to fungal growth of a range of commonly used materials. The other Standards in the series are as follows:

AS

1157	Methods of testing materials for resistance to fungal growth
1157.1	Part 1: General principles of testing
1157.2	Part 2: Resistance of textiles to fungal growth
1157.3	Part 3: Resistance of cordage and yarns to fungal growth
1157.4	Part 4: Resistance of coated fabrics and electronic boards to fungal growth
1157.5	Part 5: Resistance of timber to surface fungal growth
1157.6	Part 6: Resistance of leather and wet 'blue' hides to fungal growth
1157.7	Part 7: Resistance of paper and paper products to surface fungal growth
1157.10	Part 10: Resistance of dried or cured adhesives and glues to fungal growth

© Copyright – STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
FOREWORD	4
SECTION 1 RESISTANCE OF RUBBERS AND PLASTICS TO SURFACE- GROWING FUNGI	
1.1 SCOPE	5
1.2 REFERENCED DOCUMENT.....	5
1.3 PRINCIPLE.....	5
1.4 APPARATUS, TEST MEDIUM AND TEST ORGANISMS	5
1.5 TEST SPECIMENS	6
1.6 PROCEDURE	7
1.7 REPORT.....	8
SECTION 2 DETERMINATION OF THE FUNGITOXIC PROPERTIES OF RUBBERS AND PLASTICS	
2.1 SCOPE	9
2.2 REFERENCED DOCUMENT.....	9
2.3 PRINCIPLE.....	9
2.4 DEFINITION	9
2.5 APPARATUS, TEST MEDIUM AND TEST ORGANISMS	9
2.6 TEST SPECIMENS	10
2.7 PROCEDURE	10
2.8 REPORT.....	12

FOREWORD

The growth of fungi on rubbers and plastics may be objectionable for aesthetic reasons, because of adverse effects on physical properties or because of obnoxious odours.

Two methods of testing the resistance to surface fungal growth of rubbers and plastics and articles manufactured therefrom are described. In neither method is the effect of the fungal growth on the mechanical (physical) properties of the test specimens assessed, though this may be significant. If required by the material specification, specimens suitable for subsequent testing may be exposed to fungal attack using the method described.

STANDARDS AUSTRALIA

Australian Standard

Methods of testing materials for resistance to fungal growth

Part 11: Resistance of rubbers and plastics to surface fungal growth

SECTION 1 RESISTANCE OF RUBBERS AND
PLASTICS TO SURFACE-GROWING FUNGI

1.1 SCOPE

This Section describes procedures for determining the resistance of rubbers and plastics to surface-growing fungi. The basic material may not be attacked by the fungi used, but other substances, such as plasticizers, included in the formulation to modify the properties of the rubbers and plastics, may be attacked.

This method is suitable for testing the resistance to fungal growth of most rubbers and plastics.

This Standard provides a laboratory test which is intended to provide severe, standardized assessment of fungal resistance under laboratory conditions. It does not include the testing of rubbers and plastics in the field which, although possibly more severe, is much longer in duration and also more subjective.

1.2 REFERENCED DOCUMENT

The following document is referred to in this Standard:

AS

1157 Methods of testing materials for resistance to fungal growth

1157.1 Part 1: General principles of testing

1.3 PRINCIPLE

The test specimens are sterilized, inoculated with a spore suspension and then incubated for 14 days. At the end of the incubation period the fungal growth on all specimens is assessed.

1.4 APPARATUS, TEST MEDIUM AND TEST ORGANISMS

1.4.1 Apparatus

The following apparatus is required:

- (a) As specified in the following appendices of AS 1157.1:
- (i) Leaching of test specimens Appendix A.
 - (ii) Preparing the test medium Appendix B.
 - (iii) Sterilizing the equipment..... Appendix C.
 - (iv) Sterilizing the test specimens..... Appendix D.
 - (v) Preparing the spore suspension Appendix E.