

Australian Standard[®]

**SAA PACKAGING CODE—
Part 6—PAPER AND
PAPERBOARD**

This Australian standard was prepared by Committee PK/25, Packaging Code. It was approved on behalf of the Council of the Standards Association of Australia on 25 March 1986 and published on 2 June 1986.

The following interests are represented on Committee PK/25:

- Agricultural and Veterinary Chemicals Association of Australia
 - Adhesives and Sealants Manufacturers Association
 - Australian Airline Company
 - Australian Institute of Packaging
 - Australian and New Zealand Pulp and Paper Industry Technical Association (Appita)
 - Australian Timber Producers Council
 - Bureau of Steel Manufacturers of Australia
 - Canmakers Institute of Australia
 - Confederation of Australian Industry
 - Cordage Institute of Australia
 - Department of Defence
 - Department of Primary Industry
 - Department of Industry Technology and Commerce
 - Glass Packaging Institute of Australia
 - Packaging Council of Australia
 - Plastics Institute of Australia Incorporated
 - Printing and Allied Trades Employers Federation of Australia
 - Railways of Australia Committee
-

Review of Australian Standards. *To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This standard was issued in draft form for comment as DR 85029.

First published 1986

PREFACE

This standard was prepared by the Association's Packaging Code Committee under the direction of the Packaging Standards Board, as a proposed further part of AS 2400, SAA Packaging Code.

The purpose of this standard is to provide information on the choice and use of paper and paperboard products.

The SAA Packaging Code has been divided into parts dealing with specific subjects, as follows:

Part	Title
1	Glossary of Packaging Terms*
2	Basic Principles of Packaging Practice*
3	Mechanical Aids in Package Handling*
4	Protection Against Spoilage of Packages and their Contents by Micro-organisms, Insects, Mites and Rodents*
5	Metal Protection
6	Paper and Paperboard
7	Timber Containers
8	Textile Bags, Sacks and Wrappings
9	Metal Containers
	9.1 Metal Cans and Tubes*
10	Cushioning Materials
11	Cordage
12	Adhesive Closing and Sealing Tapes*
13	Tensional Strapping*
14	Adhesives for Packaging*
15	Glass Containers*
16	Flexible Packaging*
17	Packaging in Plastics Containers*
18	Use of Desiccants in Packaging*
19	Packaging for Airfreight*
20	Handling of Goods in Freight Containers*
21	Packaging of Dangerous Goods
22	Closures*
23	Shrink and Stretch Wrapping*

During the preparation of the SAA Packaging Code, account is being taken of material included in BS 1133, Packaging Code, and the assistance obtained from this source is acknowledged.

* Published

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

CONTENTS

	<i>Page</i>
FOREWORD	6
SECTION 1. SCOPE AND GENERAL	
1.1 SCOPE	8
1.2 APPLICATION	8
1.3 REFERENCED DOCUMENTS	8
1.4 DEFINITIONS	8
SECTION 2. WRAPPING PAPERS	
2.1 GENERAL	9
2.2 TYPES OF WRAPPING PAPER	9
2.3 SELECTION OF A WRAPPING PAPER ¹⁰	
2.4 PARCELLING	11
SECTION 3. PAPER BAGS	
3.1 GENERAL	12
3.2 BAG TYPES	12
3.3 HOW BAGS ARE MADE	12
3.4 TYPICAL PROPERTIES OF BAGS	13
3.5 MATERIALS USED FOR PAPER BAGS	13
SECTION 4. MULTIWALL PAPER SACKS	
4.1 GENERAL	14
4.2 DEFINITIONS	14
4.3 SACK DESIGNS	15
4.4 TYPES OF MATERIAL USED	17
4.5 ASSEMBLY AND CLOSURE MATERIALS	18
4.6 SELECTION OF SACK CONSTRUCTION	19
4.7 DIMENSIONS OF MULTIWALL PAPER SACKS	19
4.8 FILLING OF SACKS	19
4.9 STORAGE OF EMPTY SACKS	21
4.10 HANDLING OF SACKS	22
4.11 SECURING OF UNIT LOADS OF FILLED SACKS	22
4.12 EMPTYING OF FILLED SACKS	22
SECTION 5. PAPERBOARD BOXES(CARTONS)	
5.1 GENERAL	23
5.2 TYPES OF PAPERBOARD	23
5.3 CARTON STYLES	23
5.4 DIMENSIONS	27
5.5 MATERIALS	28
5.6 PRINTING	28
5.7 CREASE QUALITY	29
5.8 ADHESIVE APPLICATION	29
5.9 PACKING AND STORAGE	29
SECTION 6. FIBREBOARD BOXES	
6.1 BOX DESIGN CRITERIA	30
6.2 BOX CONSTRUCTION	30
6.3 TYPES OF BOX	32
6.4 BOX JOINTS	32
6.5 BOX DIMENSIONS	32
6.6 SPECIAL FEATURES	32
6.7 PRINTING	32

	<i>Page</i>
6.8 STORAGE OF UNFILLED BOXES	33
6.9 CLOSURE OF BOX	33
 SECTION 7. MOULDED PULP	
7.1 MANUFACTURE	35
7.2 PROPERTIES OF MOULDED PULP	35
 SECTION 8. COMPOSITE CANS AND DRUMS	
8.1 GENERAL	36
8.2 MATERIALS	36
8.3 TECHNOLOGY OF COMPOSITE CONTAINERS	36
8.4 LABELLING	36
8.5 TYPES OF COMPOSITE CANS	36
8.6 TYPES OF FIBREBOARD DRUMS	36
8.7 DRUM CLOSURES	36

FOREWORD

In AS 2400, Part 1, paper is defined as 'a continuous felted web of vegetable fibres deposited from a water suspension onto a fine wire screen'. Paperboard is 'a fairly rigid paper with a grammage usually greater than 225 g/m²'. In most cases, the vegetable fibres are wood fibres which may be derived either from hardwoods or softwoods. These are mechanically treated (refined) to increase their plasticity in the wet state.

The mechanical properties of paper are largely determined by the properties of its constituent fibres, in particular their length and their ability to bond to one another. A wide variety of non-fibrous materials may be incorporated into the paper sheet during the papermaking operation or applied subsequently as coatings. These may impart special properties which are needed for a particular end use (e.g. water resistance) or may provide a balance of properties which cannot be achieved by refining alone (e.g. improved strength at high bulk). However, when paper or paperboard is used as a packaging material, it must always be remembered that the base sheet is made from natural fibres with certain inherent properties which must affect the behaviour of the paper made from them.

THE PAPERMAKING FIBRE.

Although a wide variety of vegetable fibres are used for specialty papers, most packaging papers and paperboards are made from wood fibres. A typical wood fibre is a long, thin tube, tapering towards the ends. If derived from coniferous woods (softwoods), they are 3 mm to 4 mm long and 30 µm to 40 µm in diameter; if obtained from deciduous woods (hardwoods), they are typically 1 mm to 1.5 mm long and 15 µm to 25 µm in diameter. The wall of each fibre is made up from smaller elements (known as microfibrils) which are arranged in a spiral pattern at a small angle to the fibre axis. It is this construction, together with the chemical nature of the cell wall substance, which gives the fibre its unique properties. These fibres are quite strong, even when wet, but wetting markedly reduces their elastic modulus and also the strength of the bonds between the fibres. Water resistance of the bonds can be improved by appropriate treatment with a wet-strength resin, but no effective method of maintaining elastic modulus has yet been introduced. Thus, a sheet of paper may retain a significant proportion of its tensile strength when wetted, but its wet stiffness will always be much less than the stiffness in the dry state. Wood fibres also swell when wet. There is little change in fibre length, but a considerable increase in fibre diameter. Thus, changes in moisture content of a paper sheet result in dimensional changes, greatest in the thickness of the sheet.

The properties of individual fibres depend both on the type of wood from which they are obtained (which controls fibre dimensions), and on the pulping process used to convert the wood to individual fibres. Methods used for reducing wood to pulp range from those in which the lignin which holds the fibres together in the tree is removed by a suitable chemical treatment to those in which the fibres are separated from one another by purely mechanical means. A variety of combinations of chemical and mechanical treatments are also used to produce pulps with properties suitable for a particular end use. In general, the so-called chemical pulps give paper which is relatively strong and dense. This is the preferred raw material for products such as sacks, bags and strong wrapping papers. Mechanical pulp fibres are stiffer and give papers which are somewhat weaker, but less dense. The lower density is used to advantage in paperboards, where the additional thickness per unit mass of fibre provides the stiffness required for applications such as box boards.

Waste paper is also a significant source of raw material. The quality can range from mixed household waste to high quality cuttings from converting operations. Mixed waste contains a considerable amount of mechanical pulp (from newsprint) and is largely used in multi-ply liners and boxboards. Higher grade wastes may be used, either alone or in admixture with virgin pulp, in better quality papers and paperboards. When paper is recycled, characteristics will change.

PREPARING THE FIBRE.

Once the original raw material (wood chips, waste paper etc.) has been separated into its component fibres, two further steps are needed before it can be fed to the paper machine. Firstly, the fibres, in the presence of water, are subjected to severe mechanical stresses. This process, known as beating or refining (but not to be confused with chip refining) makes the fibres more plastic and better able to adhere to one another when pressed and dried. Other side effects occur at the same time, especially fibre cutting and the formation of fine debris. These effects may be desirable or otherwise, depending on the type of paper being made. Careful control of the operation is needed to ensure that the balance of properties obtained is appropriate to the intended end use.

The second step is the incorporation of non-fibrous additives into the fibre suspension. A judicious addition of appropriate materials can provide a paper sheet with properties which cannot be obtained otherwise. For example, the addition of a resin size can reduce rate of penetration of liquids into the body of the paper, while a wet-strength resin can reduce the amount of strength lost when the paper is wetted. Dyestuffs can be added at this point to produce coloured papers, or pigments (fillers) may be used to provide increased opacity. Availability of these non-fibrous additives provides the papermaker with the means of producing a wide range of paper types, each with a different combination of properties.

THE PAPER SHEET.

A paper machine is made up of three basic units: the forming section, the press and the dryers. The forming section converts a suspension of 1 percent or less of fibre in water into a web of fibres containing about 20 percent solids. This wet web is consolidated in the press section and more water is removed. The wet web, now at about 40 percent solids, passes to the dryers, where the remaining water is evaporated on steam-heated drums.

In the forming section, the dilute suspension of fibre in water is drained through a wire mesh. Most of the water passes through, leaving the web of fibres on the wire. Several different designs of former are available, some of which can produce paperboards made up of a number of plies, each having different composition. Whatever the type of former, the fibres in the web are preferentially oriented in the machine direction, to a degree which depends on the hydrodynamics of the former in question. This preferential orientation means that the mechanical properties of any machine-made paper in the direction of travel of the wire (machine direction or MD) are not the same as in the direction at right angles to this (cross direction or CD). This effect is increased during the drying stage. Here, the wet web is able to shrink in the cross direction but is under tension in the machine direction; this adds to the degree of variation between MD and CD properties (anisotropy). The end result is that tensile and compression strength are higher in the machine direction, while stretch and tearing resistance are higher in the cross direction. Dimensional changes caused by a change in moisture content are also more pronounced in the cross direction.

The surface finish of a sheet of paper or paperboard may be modified once the base sheet has been formed. Papers with a smooth surface on one side are produced by replacing the normal series of drying cylinders by a single, highly polished cylinder (the MG cylinder). The surface of the paper in contact with the cylinder dries with a very smooth finish. Calendering or supercalendering involves passing the paper web through the nips of a series of heavy rolls set one above another. In this case, paper surfaces are subjected to combined pressing and polishing at high speed. Alternatively, the paper surface may be coated with a pigment suspended in an appropriate binder solution—an operation analogous to applying a coat of paint. The coated surface may be smoothed as part of the coating operation or may be subsequently calendered to produce an extremely smooth and glossy finish.

Despite the limitations imposed by the characteristics of the constituent fibres and by the mechanics of the papermaking process, paper and paperboard can be tailored to fit a wide range of end-use requirements. Even in the packaging field, one can produce products as diverse as soft wrapping tissues and rigid fibreboard drums, transparent glassine bags and multiwall paper sacks. Furthermore, for some applications, several alternative papers having similar properties, but differing in composition, may be available. It should also be realized that the composition of papers used for packaging a particular product may vary from country to country, usually because the wood resource available for pulp production in any area is unique to that area. This can create confusion when a packer wishes to purchase paper made according to an overseas specification. Often, paper specifications are written with the intention of describing a product which has been found to be satisfactory in practice. A change in the raw material from which the paper is made can result either in a product which complies with the specification but does not perform well or a product which will produce a satisfactory package but does not comply with the specification. This type of problem arises because of the lack of standard test methods which correlate well with use requirements. Specialist advice should be sought and appropriate trials conducted to ensure that a new or changed packaging system will be effective.

Performance requirements of paper products depend on moisture content which under equilibrium is a function of relative humidity. It may vary markedly due to condensation or exposure to weather. User should establish that the type of paper or paperboard used in any form of packaging provides adequate protection for the contents under the anticipated conditions of abuse.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard
SAA PACKAGING CODE

PART 6—PAPER AND PAPERBOARD

SECTION 1. SCOPE AND GENERAL

- 1.1 SCOPE.** This standard provides guidance on the use of paper and paperboard products.
- 1.2 APPLICATION.** Detailed guidance on specific products made of pulp is given in the following sections:
- Section 2 Wrapping papers
 Section 3 Paper bags
 Section 4 Multiwall paper sacks
 Section 5 Paperboard boxes
 Section 6 Fibreboard boxes
 Section 7 Moulded pulp
 Section 8 Composite cans and drums
- 1.3 REFERENCED DOCUMENTS.** The following standards are referred to in this standard:
- | | | | |
|------------------|---|---------|--|
| AS 1048 | International Fibreboard Box Code | AS 2222 | Adhesives for Unit Loads (Palletizing Adhesives) |
| AS 1301 | Methods of Test for Pulp and Paper | AS 2322 | Corrugated Fibreboard Boxes for the Export of Rindless Cheese |
| | P403rp — Bursting Strength of Paper | AS 2348 | Guide to the Determination of Optimum Dimensions of Packages for Unit Load Handling |
| | P405s — Grammage of Non-creped Paper and Board | AS 2400 | SAA Packaging Code |
| | P414m — Conditioning of Paper for Testing | | Part 1 — Glossary of Packaging Terms |
| | P415m — Standard Atmosphere for Paper Testing | | Part 2 — Basic Principles of Packaging Practice |
| | P421m — Determination of the pH Value of Aqueous Extracts of Paper—Cold Extraction Method | | Part 3 — Mechanical Aids in Package Handling |
| | P440ts — Bendtsen Porosity of Paper | | Part 11 — Cordage* |
| AS 1764 | Vegetable Parchment for Wrapping Dairy Products | | Part 12 — Adhesive Closing and Sealing Tapes |
| AS 1814 | High Wet-strength Greaseproof Paper for Wrapping Dairy Products | | Part 13 — Tensional Strapping |
| AS 1990 | Corrugated Fibreboard Containers for Export of Dried Vine Fruit | AS 2516 | Corrugated Fibreboard Boxes for Export of Apples in Containerized Shipments |
| AS 1991 | Fibreboard Containers and Container Blanks for Export of Non-refrigerated Canned Goods | AS 2517 | Corrugated Fibreboard Boxes for Export of Pears |
| AS 1992 | Solid Fibreboard Containers and Container Blanks for Export of Frozen Boneless Meat | AS 2582 | Complete, Filled Transport Packages—Methods of Test |
| AS 1993 | Corrugated Fibreboard Containers and Container Blanks for Export of Frozen Boneless Meat | AS 2583 | Complete, Filled Transport Packages—Distribution Trials—Information to be Recorded |
| AS 2001.4.2-1982 | Part 4— Colourfastness Tests—Determination of Colourfastness to Daylight | AS 2584 | Complete, Filled Transport Packages—General Rules for the Compilation of Performance Schedules |
| AS 2173 | Corrugated Fibreboard Containers and Container Blanks for Export of Butter | AS 2609 | Materials Used for the Packaging of Food and Beverages—Methods for the Assessment of Odour and Taint |
| | | AS 2838 | Classification System for Corrugated and Solid Fibreboard. |
| | | AS 2852 | Packaging-Pictorial Markings for the Handling of Packages |
| | | BS 3110 | Methods for Measuring the Rub Resistance of Print. |
- 1.4 DEFINITIONS.** For the purpose of this standard the definitions of AS 2400, Part 1 apply.

* In course of preparation.