

Australian Standard™

**Methods for the analysis and testing of  
lower rank coal and its chars**

**Part 2: Lower rank coal—Determination  
of volatile matter**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 16 September 2002 and published on 1 October 2002.

---

The following are represented on Committee MN-001:

Australasian Institute of Mining and Metallurgy  
Australian Coal Association  
Australian Coal Preparation Society  
Australian Institute of Energy  
Coal field Geology Council of N.S.W.  
CSIRO Energy Technology  
Department of Mines and Energy (Qld)  
Electricity Supply Association of Australia  
Institution of Engineers Australia  
Minerals Council of Australia  
University of New South Wales  
University of Newcastle  
University of Queensland

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

Australian Standard™

**Methods for the analysis and testing of  
lower rank coal and its chars**

**Part 2: Lower rank coal—Determination  
of volatile matter**

Originated as AS 2434.2—1983.  
Second edition 2002.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4851 1

## PREFACE

This Standard was prepared by the Standards Australia Committee MN-001, Coal and Coke to supersede AS 2434.2—1985, *Methods for the analysis and testing of brown coal and brown coal char, Part 2: Determination of the volatile matter in low rank coal*.

The method differs from that given for higher rank coal (AS 1038.3, *Coal and coke—Analysis and testing, Part 3: Proximate analysis of higher rank coal*) in that there are two stages of heating to accommodate the large release of volatiles from low rank coal without loss of solids.

The volatile matter in low rank coal is determined as the loss in mass, less that due to moisture, when low rank coal is heated out of contact with air under standardized conditions. It is intended as a determination of the volatile organic fraction of the coal and it must be noted that, because of their large internal surface area, some low rank coals may contain significant amounts of inorganic matter which may be lost, or which may lose mass, during the test. An example is sodium chloride, which can be removed by prior washing of the sample with water.

The test is empirical, and in order to ensure reproducible results it is essential that the rate of heating, the final temperature, and the overall duration of the test are carefully controlled. Where the determination is performed on moist samples, the moisture content of the sample must be determined at the same time as the volatile matter, so that appropriate correction can be made.

The method of specifying the apparatus and procedure permits one or more determinations to be carried out simultaneously in the muffle furnace.

Heating in air of the residue from this volatile matter determination results in a slightly lower ash than by the direct determination used in AS 1038.3. Thus a fixed carbon measurement calculated from the volatile matter determination residue described in this Standard and its ash will give a result slightly higher than that using AS 1038.3.

## CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS .....	4
3 DEFINITIONS .....	4
4 PRINCIPLE .....	4
5 SAFETY .....	4
6 REAGENTS.....	4
7 APPARATUS .....	5
8 SAMPLE.....	6
9 PROCEDURE.....	6
10 CALCULATION .....	7
11 REPORTING OF RESULTS.....	8
12 PRECISION .....	8
13 TEST REPORT .....	8

# STANDARDS AUSTRALIA

## Australian Standard

### Methods for the analysis and testing of lower rank coal and its chars

#### Part 2: Lower rank coal—Determination of volatile matter

## 1 SCOPE

This Standard sets out a method for the determination of the volatile matter of air-dried low rank coal, either directly or with an initial oven drying.

## 2 REFERENCED DOCUMENTS

The following Standards are referred to in this Standard:

### AS

1038	Coal and coke—Analysis and testing
1038.3	Part 3: Proximate analysis of higher rank coal
1038.16	Part 16: Assessment and reporting of results
2243	Safety in laboratories (series)
2418	Coal and coke—Glossary of terms
2508	Safe storage and handling information card (series)
2706	Numerical values—Rounding and interpretation of limiting values
4264	Coal and coke—Sampling
4264.3	Part 3: Lower rank coal—Sampling procedures

## 3 DEFINITIONS

For the purpose of this Standard, the definitions given in AS 2418 apply.

## 4 PRINCIPLE

The coal is heated out of contact with air for 7 min at 400°C and then at 900°C for a further 7 min.

The percentage of volatile matter is calculated from the loss in mass of the sample. In the direct method the loss in mass due to moisture which is determined on a separate test portion taken from the same analysis sample at the same time, is deducted.

## 5 SAFETY

For information on laboratory safety, reference should be made to the relevant parts of AS 2243 and AS 2508.

## 6 REAGENTS

### 6.1 General

Unless otherwise specified, all reagents shall be of analytical reagent grade, and only distilled water, or water of equivalent purity, shall be used.