

Australian Standard<sup>®</sup>

**Copper, lead, zinc and nickel  
concentrates—Sampling**

**Part 2: Experimental methods for  
checking the precision of sampling**



This Australian Standard® was prepared by Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates. It was approved on behalf of the Council of Standards Australia on 24 January 2008.  
This Standard was published on 19 March 2008.

---

The following are represented on Committee MN-005:

- CSIRO Minerals
- Minerals Council of Australia

Additional Interests:

- Minerals Industry Analytical Laboratories
- 

This Standard was issued in draft form for comment as DR 07038.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through the public comment period.

---

### **Keeping Standards up-to-date**

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting **[www.standards.org.au](http://www.standards.org.au)**

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at **[mail@standards.org.au](mailto:mail@standards.org.au)**, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

---

Australian Standard<sup>®</sup>

**Copper, lead, zinc and nickel  
concentrates—Sampling**

**Part 2: Experimental methods for  
checking the precision of sampling**

Originated as AS 2862.2—1999.  
Second edition 2008.

**COPYRIGHT**

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia  
ISBN 0 7337 8598 0

## PREFACE

This Standard was prepared by the Standards Australia Committee MN-005, Copper, Lead, Zinc and Nickel Ores and Concentrates, to supersede AS 2862.2—1999, *Copper, lead and zinc sulfide concentrates—Sampling, Part 2: Experimental methods for checking the precision of sampling*.

The objective of this Standard is to provide those involved in the sampling of sulfide concentrates with standardized methods for checking the precision of sampling.

The objective of this revision is to adopt the latest edition of the corresponding International Standard.

This Standard is identical with, and has been reproduced from ISO 12744:2006, *Copper, lead, zinc and nickel concentrates— Experimental methods for checking the precision of sampling*.

As this Standard is reproduced from an International Standard, the following applies:

- (a) Its number appears on the cover and title page while the International Standard number appears only on the cover.
- (b) In the source text ‘this International Standard’ should read ‘this Australian Standard’.
- (c) A full point substitutes for a comma when referring to a decimal marker.

References to International Standards should be replaced by references to Australian Standards, as follows:

<i>Reference to International Standard</i>	<i>Australian Standard</i>
ISO	AS
12743 Copper, lead, zinc and nickel concentrates—Sampling procedures for determination of metal and moisture content	2862 Copper, lead, zinc and nickel concentrates—Sampling 2862.1 Part 1: Sampling procedures for determination of metal and moisture content

The term ‘informative’ has been used in this Standard to define the application of the annex to which it applies. An ‘informative’ annex is only for information and guidance.

## CONTENTS

	<i>Page</i>
<b>1</b>	<b>Scope ..... 1</b>
<b>2</b>	<b>Normative references ..... 1</b>
<b>3</b>	<b>General conditions ..... 1</b>
<b>3.1</b>	<b>General..... 1</b>
<b>3.2</b>	<b>Number of lots..... 1</b>
<b>3.3</b>	<b>Number of increments and number of samples ..... 1</b>
<b>3.4</b>	<b>Sample processing and analysis ..... 2</b>
<b>3.5</b>	<b>Frequency of precision checks ..... 2</b>
<b>4</b>	<b>Symbols ..... 2</b>
<b>5</b>	<b>Method of experiment..... 3</b>
<b>5.1</b>	<b>Interleaved samples..... 3</b>
<b>5.2</b>	<b>Sample processing and analysis ..... 3</b>
<b>5.2.1</b>	<b>Sample processing method 1 (see Figure 2) ..... 3</b>
<b>5.2.2</b>	<b>Sample processing method 2 (see Figure 3) ..... 3</b>
<b>5.2.3</b>	<b>Sample processing method 3 (see Figure 4) ..... 3</b>
<b>6</b>	<b>Evaluation of experimental data..... 6</b>
<b>6.1</b>	<b>General..... 6</b>
<b>6.2</b>	<b>Sample processing method 1 ..... 6</b>
<b>6.3</b>	<b>Sample processing method 2 ..... 8</b>
<b>6.4</b>	<b>Sample processing method 3 ..... 9</b>
<b>7</b>	<b>Assessment of results and action ..... 11</b>
<b>7.1</b>	<b>Primary sampling..... 11</b>
<b>7.2</b>	<b>Sample processing ..... 11</b>
<b>7.3</b>	<b>Analysis ..... 11</b>
<b>8</b>	<b>Recording of data ..... 11</b>
<b>Annex A (informative)</b>	<b>Recording of sampling data..... 12</b>
<b>Bibliography</b>	<b>..... 15</b>

AUSTRALIAN STANDARD

## Copper, lead, zinc and nickel concentrates—Sampling

Part 2:

Experimental methods for checking the precision of sampling

**WARNING — This International Standard may involve hazardous materials, operations and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.**

### 1 Scope

This International Standard specifies methods for checking the precision of primary sampling, sample processing, chemical analysis, physical testing and determination of moisture content of copper, lead, zinc and nickel concentrates being carried out in accordance with the methods specified in ISO 12743, expressed in terms of standard deviations.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 12743, *Copper, lead, zinc and nickel concentrates — Sampling procedures for determination of metal and moisture content*

### 3 General conditions

#### 3.1 General

The determination of precision of primary sampling is based on collecting pairs of interleaved samples from each lot. If sample processing and measurement are also carried out in duplicate, it is possible to determine the precision of sample processing and analysis.

#### 3.2 Number of lots

It is recommended that pairs of interleaved samples be collected from more than 20 lots of the same type of concentrate, in order to reach a reliable conclusion. The lot size shall be chosen to ensure that this requirement is met.

#### 3.3 Number of increments and number of samples

The minimum number of increments for checking precision should preferably be twice the number determined in accordance with ISO 12743. Hence, if the number of increments required for routine sampling is  $n$  and one lot sample is constituted, the minimum number of increments should be  $2n$ , and two interleaved samples shall be constituted.

Alternatively, if the precision is being checked as part of routine sampling,  $n$  increments may be taken and two interleaved samples constituted, each comprising  $n/2$  increments. The sampling precision thus obtained must be divided by  $\sqrt{2}$  to obtain the sampling precision for lot samples comprising  $n$  increments.