

Australian Standard™

**Calibration blocks and their methods of
use in ultrasonic testing**

This Australian Standard was prepared by Committee Current, Non-Destructive Testing of Metals and Materials. It was approved on behalf of the Council of Standards Australia on 8 June 2005. This Standard was published on 8 July 2005.

The following are represented on Committee Current:

Australasian Railway Association
Australasian Aerospace Non-Destructive Testing Committee
Australian Industry Group
Australian Institute for Non-Destructive Testing
ANSTO
Australian Pipeline Association
Bureau of Steel Manufacturers of Australia
Institute of Engineers
NATA
TestSafe Australia
Victoria Workcover
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 05037.

STANDARDS AUSTRALIA

RECONFIRMATION

OF

AS 2083—2005

Calibration blocks and their methods of use in ultrasonic testing

RECONFIRMATION NOTICE

Technical Committee MT-007 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 2 March 2017.

The following are represented on Technical Committee MT-007:

Australasian Thermographers Association
Australian Aerospace Non-Destructive Testing Committee
Australian Institute for Non-Destructive Testing
Australian Nuclear Science & Technology Organisation
AUSTROADS
Bureau of Steel Manufacturers of Australia
Engineers Australia
Institute of Electrical Inspectors
National Association of Testing Authorities Australia
New Zealand Non-Destructive Testing Association
TestSafe Australia
Welding Technology Institute of Australia
WorkSafe Victoria

NOTES

Australian Standard™

**Calibration blocks and their methods of
use in ultrasonic testing**

Originated as AS B258—1968.
Previous edition AS 2083—1981.
Third edition AS 2083—2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 6789 3

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/Standards New Zealand Committee MT-007, Non-Destructive Testing of Metals and Materials to supersede AS 2083—1981, *Calibration blocks and their methods of use in ultrasonic testing*. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this Standard is to specify the requirements for a range of ultrasonic calibration blocks and testing methods for non-destructive testing.

The objective of this revision is to revise the range of calibration blocks used in ultrasonic testing.

In the preparing of this edition of the Standard, the Committee decided to include requirements for reference blocks and blocks for use in the measurement of thickness of metal by acoustic energy.

Methods included for the calibration of ultrasonic testing equipment are considered by the Committee to be those based on accepted good practice and in widespread use, although the Committee is aware that other methods are used.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	5
1.2 APPLICATION	5
1.3 REFERENCED DOCUMENTS	5
1.4 DEFINITIONS	5
1.5 CONSTRUCTION OF BLOCKS	5
SECTION 2 REQUIREMENTS FOR CALIBRATION BLOCK NO.1 AND METHODS OF USE	
2.1 GENERAL	7
2.2 PROBES.....	7
2.3 DIMENSIONS.....	7
2.4 METHODS OF USE—NORMAL PROBES	8
2.5 METHODS OF USE—ANGLE PROBES.....	17
SECTION 3 REQUIREMENTS FOR CALIBRATION BLOCK No.2 AND METHODS OF USE	
3.1 GENERAL	22
3.2 PROBES.....	22
3.3 DIMENSIONS AND SURFACE IDENTIFICATION.....	22
3.4 METHODS OF USE—NORMAL PROBES	23
3.5 METHODS OF USE—ANGLE PROBES.....	23
SECTION 4 REQUIREMENTS FOR CALIBRATION BLOCK No.3 AND METHODS OF USE	
4.1 GENERAL	27
4.2 DIMENSIONS.....	27
4.3 METHODS OF USE—ANGLE PROBES.....	27
SECTION 5 REQUIREMENTS FOR CALIBRATION BLOCK No.4 AND METHOD OF USE	
5.1 GENERAL	29
5.2 DIMENSIONS.....	29
5.3 METHOD OF USE.....	29
SECTION 6 REQUIREMENTS FOR CALIBRATION BLOCK No.5 AND METHODS OF USE	
6.1 GENERAL	30
6.2 PROBES.....	30
6.3 DIMENSIONS.....	30
6.4 METHOD OF USE—NORMAL PROBES	30
6.5 METHODS OF USE—ANGLE PROBES.....	30
SECTION 7 REQUIREMENTS FOR CALIBRATION BLOCK No.6 AND METHOD OF USE	
7.1 GENERAL	33
7.2 DIMENSIONS.....	33
7.3 ASSESSMENT OF RESOLUTION	33

SECTION 8	CALIBRATION PROCEDURES NOT REQUIRING SPECIFIC BLOCKS	
8.1	GENERAL	36
8.2	MEASUREMENT OF DEAD ZONE LENGTH USING NORMAL PROBES	36
8.3	MEASUREMENT OF DEAD ZONE LENGTH USING ANGLE PROBES	36
SECTION 9	CALIBRATION AND REFERENCE BLOCKS CONTAINING FLAT-BOTTOMED HOLES	
9.1	GENERAL	38
9.2	DIMENSIONS.....	38
9.3	CONSTRUCTION OF BLOCKS	38
9.4	ULTRASONIC RESPONSE.....	38
9.5	REFERENCE BLOCKS—IDENTIFICATION	41
9.6	METHODS OF USE OF BLOCKS	42
SECTION 10	REQUIREMENTS FOR CALIBRATION BLOCK No.7 AND METHOD OF USE IN ULTRASONIC THICKNESS MEASUREMENTS	
10.1	GENERAL	44
10.2	DIMENSIONS.....	44
10.3	METHOD OF USE.....	44
SECTION 11	THE USE OF ULTRASONIC TESTING EQUIPMENT	
11.1	GENERAL	45
11.2	EQUIPMENT PERFORMANCE	45

STANDARDS AUSTRALIA

Australian Standard

Calibration blocks and their methods of use in ultrasonic testing

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard specifies requirements for a range of calibration blocks and their methods of use in ultrasonic testing.

NOTE: Calibration blocks of different designs within this Standard may be used for equipment calibrations.

1.2 APPLICATION

Calibration blocks shall comply with the relevant requirements of Section 1 and with the specific requirements of the following Sections, as appropriate to the type of block:

Block No.1 (IIW).....	Section 2
Block No.2 (IOW)	Section 3
Block No.3	Section 4
Block No.4	Section 5
Block No.5 (Miniature Block).....	Section 6
Block No.6 (Resolution Block)	Section 7
Reference Blocks.....	Section 9
Block No.7 (Thickness Measurement)	Section 10

The methods of use shall be as specified in the relevant Section.

1.3 REFERENCED DOCUMENTS

The following documents are referred to in this Standard.

AS	
1733	Methods for the determination of grain size in metals
1929	Non-destructive testing—Glossary of terms

1.4 DEFINITIONS

For the purpose of this Standard, the terms and definitions given in AS 1929 apply.

1.5 CONSTRUCTION OF BLOCKS

1.5.1 Material

Calibration blocks shall be manufactured from a normalized plain carbon steel of grain size No.5 or finer (refer to AS 1733).