

Australian/New Zealand Standard™

Structural steel welding

**Part 7: Welding of sheet steel
structures**



AS/NZS 1554.7:2014

This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee WD-003, Welding of Structures. It was approved on behalf of the Council of Standards Australia on 24 September 2014 and on behalf of the Council of Standards New Zealand on 12 September 2014.
This Standard was published on 25 November 2014.

The following are represented on Committee WD-003:

Australasian Corrosion Association
Australian Chamber of Commerce and Industry
Australian Industry Group
Australian Steel Institute
Austroads
Bureau of Steel Manufacturers of Australia
Energy Networks Association
Engineers Australia
New Zealand Heavy Engineering Research Association
New Zealand Non-Destructive Testing Association
Steel Reinforcement Institute of Australia
University of Sydney
Welding Technology Institute of Australia

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at www.saiglobal.com.au or Standards New Zealand web site at www.standards.co.nz and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

This Standard was issued in draft form for comment as DR AS/NZS 1554.7.

Australian/New Zealand Standard™

Structural steel welding

Part 7: Welding of sheet steel structures

Originated as AS/NZS 1554.7:2006.
Second edition 2014.

COPYRIGHT

© Standards Australia Limited/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, Private Bag 2439, Wellington 6140.

PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee WD-003, Welding of Structures, to supersede AS/NZS 1554.7:2006.

The objective of this Standard is to provide rules for the welding of a wide range of light gauge steel constructions designed in accordance with the requirements of AS/NZS 4600. Although this Standard has been specifically prepared for steel structures, it may be usefully applied to machine frames and other types of steel constructions.

Given the historical links between the requirements of AS/NZS 4600, *Cold-formed steel structures* and the American Welding Society's AWS D1.3, *Structural Welding Code—Sheet Steel*, this Standard takes cognizance of the requirements and practices associated with AWS D1.3, and the similar requirements contained within AS/NZS 1554.1, *Structural steel welding Part 1: Welding of steel structures*, for category GP quality welds.

This edition incorporates the following major changes to the 2006 edition:

(a) *Changes to the following Clauses:*

1.1, 1.7 (new title and text), 2.3.1, 2.3.3, 3.3.3, 4.1.2 [new Items (d), (f)-(j)], 4.2(b), 4.2(d) (correction), 4.3(e), 4.5.5.1, 4.5.5.3, 4.6.1.1, 4.6.1.2 (new Note), 4.7.1, 4.7.7, 4.8, 4.12.1, 4.12.2, 5.1, 5.2.4, 5.3.4, 6.1.2, 6.4 (Note 2), 6.5 (new Note), 7.2, 7.4, Appendix H (new), Bibliography (new).

(b) *Changes to the following Tables:*

4.6.1(A), 4.6.1(B), 4.6.1(C), 4.11(A), 4.11(B), 4.11(C) (new), 4.12.2(A), 4.12.2(B), 5.3.4(A), E1, E2.

(c) *Changes to the following Figures:*

3.2.5, 4.5.5.1 (Note 2 and title), 4.5.5.4 (title).

The Standard requires that weld preparations, welding consumables and welding procedures be qualified before commencement of welding. Prequalified joint preparations, welding consumables and welding procedures are also given in the Standard.

The Standard caters specifically for statically loaded structures and, similarly to AS/NZS 4600, does not consider brittle fracture requirements. Under circumstances where brittle fracture is considered likely, the user is instead referred to AS/NZS 1554.1. Whilst AS/NZS 4600 now caters for dynamic loading conditions, both AS/NZS 4600 and this Standard also refer the user to the more appropriate requirements of AS/NZS 1554.1 Category SP, or for high levels of dynamic loading (fatigue), to AS/NZS 1554.5, *Structural steel welding, Part 5: Welding of steel structures subject to high levels of fatigue loading*. This will ensure that appropriate levels of supervision and inspection will be applied to the relevant parts of the structure.

Statements expressed in mandatory terms in notes to tables and figures are deemed to be requirements of this Standard.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE.....	5
1.2 EXCLUSIONS.....	6
1.3 INNOVATION	6
1.4 NORMATIVE REFERENCES	6
1.5 DEFINITIONS.....	6
1.6 SYMBOLS	7
1.7 MANAGEMENT OF QUALITY.....	7
1.8 SAFETY	7
SECTION 2 MATERIALS OF CONSTRUCTION	
2.1 PARENT MATERIAL.....	8
2.2 BACKING MATERIAL	8
2.3 WELDING CONSUMABLES.....	8
SECTION 3 DETAILS OF WELDED CONNECTIONS	
3.1 GENERAL.....	10
3.2 BUTT WELDS	10
3.3 FILLET WELDS	13
3.4 COMPOUND WELDS	14
3.5 SEAL WELDS.....	15
3.6 FLARE WELDS	15
3.7 ARC SPOT (PUDDLE) WELDS	16
3.8 ARC SEAM WELDS.....	18
3.9 ARC PLUG WELDS	19
SECTION 4 QUALIFICATION OF PROCEDURES AND PERSONNEL	
4.1 QUALIFICATION OF WELDING PROCEDURE.....	20
4.2 METHODS FOR QUALIFYING A WELDING PROCEDURE.....	22
4.3 PREQUALIFIED WELDING PROCEDURES.....	23
4.4 PORTABILITY OF QUALIFIED WELDING PROCEDURES	23
4.5 PREQUALIFIED JOINT PREPARATIONS	23
4.6 QUALIFICATION OF WELDING CONSUMABLES.....	31
4.7 QUALIFICATION OF WELDING PROCEDURE BY TESTING	38
4.8 EXTENSION OF QUALIFICATION	40
4.9 COMBINATION OF PROCESSES	41
4.10 RECORDS OF TESTS	41
4.11 REQUALIFICATION OF WELDING PROCEDURES	43
4.12 QUALIFICATION OF WELDING PERSONNEL	45

SECTION 5 WORKMANSHIP

5.1	PREPARATION OF EDGES FOR WELDING	51
5.2	ASSEMBLY	51
5.3	PREHEATING AND INTER-RUN CONTROL	53
5.4	WELDING UNDER ADVERSE WEATHER CONDITIONS	59
5.5	TACK WELDS	59
5.6	WELD DEPTH TO WIDTH RATIO	59
5.7	CONTROL OF DISTORTION AND RESIDUAL STRESS	60
5.8	BACKGOUGING AND REPAIR OF DEFECTS IN WELDS	60
5.9	TEMPORARY ATTACHMENTS	61
5.10	ARC STRIKES	61
5.11	CLEANING OF FINISHED WELDS	62
5.12	DRESSING OF BUTT WELDS	62

SECTION 6 QUALITY OF WELDS

6.1	METHODS OF INSPECTION AND PERMISSIBLE LEVELS OF IMPERFECTIONS	63
6.2	MAGNETIC PARTICLE EXAMINATION	67
6.3	LIQUID PENETRANT EXAMINATION	67
6.4	WELD DEFECTS	67
6.5	REPORTING	67

SECTION 7 INSPECTION

7.1	GENERAL	68
7.2	QUALIFICATIONS OF INSPECTORS	68
7.3	VISUAL INSPECTION OF WORK	68
7.4	NON-DESTRUCTIVE EXAMINATION OTHER THAN VISUAL	68

APPENDICES

A	NORMATIVE REFERENCED DOCUMENTS	70
B	BRITTLE FRACTURE	73
C	TYPICAL FORMS FOR WELDING PROCEDURES	76
D	MATTERS FOR RESOLUTION	79
E	WELDED JOINT AND PROCESS IDENTIFICATION	80
F	MIG BRAZING	86
G	BEND AND TORSION TESTS FOR SHEET STEELS	88
H	WELD PROCEDURE REQUIREMENTS ASSOCIATED WITH CHANGES TO THE WELDING CONSUMABLE CLASSIFICATION SYSTEM	94

BIBLIOGRAPHY	98
--------------------	----

STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

Australian/New Zealand Standard
Structural steel welding

Part 7: Welding of sheet steel structures

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard specifies requirements for the arc welding of steel structures made up of combinations of steel plate, sheet or sections, including pipe, hollow sections and built up sections (collectively referred to herein as sheet steels) up to 4.8 mm in thickness by the following processes:

- (a) Manual metal arc welding (MMAW).
- (b) Gas metal arc welding (GMAW or MIG), including pulsed mode.
- (c) Gas tungsten-arc welding (GTAW or TIG).
- (d) Flux-cored arc welding (FCAW).

The Standard is limited to the welding of steel parent material with a specified minimum yield strength not exceeding 550 MPa.

The Standard applies to the welding of steelwork in structures complying with AS/NZS 4600. The following limitations apply:

- (i) For other than fatigue conditions, where welded joints are governed by dynamic loading conditions, AS/NZS 1554.1 category SP applies.
- (ii) For welded joints subject to fatigue conditions (i.e. weld categories higher than detail category 118 of AS/NZS 4600), AS/NZS 1554.5 category FP.

Consistent with AS/NZS 4600, brittle fracture provisions have not been included in this Standard. For service temperatures colder than -10°C , the brittle fracture provisions of AS/NZS 1554.1 for materials and welding consumables apply (see Appendix B).

In addition to the abovementioned structures, the Standard applies to the welding of steelwork in applications other than structural.

The Standard specifies requirements equivalent to AS/NZS 1554.1 category GP arc welding. For the welding of sheet steels thicker than 4.8 mm, the requirements of AS/NZS 1554.1 apply.

For stud welding through the flat portion of decking or roofing onto supporting structural members, AS/NZS 1554.2 applies.

NOTES:

- 1 Further information on this Standard is given in WTIA Technical Note 11.
- 2 GMAW includes waveform controlled welding such as 'synergic', 'programmable', and 'microprocessor controlled' processes' e.g. pulsed spray transfer, controlled short circuit transfer.