

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 12.3: Higher rank coal—Caking and  
coking properties—Dilatation**

This Australian Standard was prepared by Committee MN-001, Coal and Coke. It was approved on behalf of the Council of Standards Australia on 15 February 2002 and published on 11 March 2002.

---

The following interests are represented on Committee MN-001:

Australasian Institute of Mining and Metallurgy  
Australian Coal Association  
Australian Coal Preparation Society  
Australian Institute of Energy  
Bureau of Steel Manufacturers of Australia  
Coalfield Geology Council of N.S.W.  
CSIRO, Energy Technology  
Department of Mines and Energy, Qld  
Electricity Supply Association of Australia  
Institution of Engineers Australia  
Minerals Council of Australia  
University of Newcastle  
University of New South Wales  
University of Queensland

---

#### **Keeping Standards up-to-date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Australia web site at [www.standards.com.au](http://www.standards.com.au) and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Australian Standard*, has a full listing of revisions and amendments published each month.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at [mail@standards.com.au](mailto:mail@standards.com.au), or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

---

Australian Standard™

**Coal and coke—Analysis and testing**

**Part 12.3: Higher rank coal—Caking and  
coking properties—Dilatation**

Originated as AS 1038.12.3—1984.  
Second edition 1993.  
Third edition 2002.

**COPYRIGHT**

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd  
GPO Box 5420, Sydney, NSW 2001, Australia

ISBN 0 7337 4367 6

## PREFACE

This Standard was prepared by the Standards Australia Committee MN-001, Coal and Coke, to supersede AS 1038.12.3—1993, *Coal and coke—Analysis and testing*, Part 12.3: *Higher rank coal—Caking and coking properties—Dilatation*. This revision confirms the procedures for determining the dilatometer characteristics of higher rank coal using a metal-core furnace and has been editorially updated to the latest format. It is based on ISO 8264:1989, *Hard coal—Determination of the swelling properties using a dilatometer* and BS 1016.107.3:1990, *Methods for analysis and testing of coal and coke*, Section 107.3, *Determination of swelling properties using a dilatometer*, both of which are Ruhr dilatometer methods. Solid core furnaces are specified in all these standard methods.

This Standard is one of a series of Standards for assessing physical properties of coal. The other parts of this series are as follows:

## AS

1038	Coal and coke—Analysis and testing
1038.12.1	Part 12.1: Higher rank coal—Caking and coking properties—Crucible swelling number
1038.12.2	Part 12.2: Higher rank coal—Caking and coking properties—Determination of Gray-King coke type
1038.12.4.1	Part 12.4.1: Higher rank coal—Caking and coking properties—Plasticity—Continuous-torque Gieseler method
1038.12.4.2	Part 12.4.2: Higher rank coal—Caking and coking properties—Plasticity—Discontinuous-torque Gieseler method

The precision data reported in Clause 10 have been taken directly from ISO 8264:1989.

The term ‘normative’ has been used in this Standard to define the application of the appendix to which it applies. A ‘normative’ appendix is an integral part of a Standard.

## CONTENTS

	<i>Page</i>
1 SCOPE.....	4
2 REFERENCED DOCUMENTS.....	4
3 DEFINITIONS.....	4
4 PRINCIPLE.....	5
5 SAFETY.....	5
6 APPARATUS.....	5
7 PREPARATION OF COAL PENCIL.....	8
8 DILATATION TEST PROCEDURE.....	9
9 REPORTING OF RESULTS.....	10
10 PRECISION.....	10
11 TEST REPORT.....	11
APPENDIX A INSPECTION OF DILATOMETER RETORTS.....	17

## STANDARDS AUSTRALIA

## Australian Standard

## Coal and coke—Analysis and testing

## Part 12.3: Higher rank coal—Caking and coking properties—Dilatation

**1 SCOPE**

This Standard sets out a method for the determination of the dilatation in higher rank coal by using a metal-core furnace.

**2 REFERENCED DOCUMENTS**

The following documents are referred to in this Standard:

## AS

1038	Coal and coke—Analysis and testing
1038.16	Part 16: Assessment and reporting of results
1152	Specification for test sieves
2243	Safety in laboratories (series)
2418	Coal and coke—Glossary of terms
2508	Safe storage and handling information card
4264	Coal and coke—Sampling
4264.1	Part 1: Higher rank coal—Sampling procedures

**3 DEFINITIONS**

For the purpose of this Standard, the definitions given in AS 2418 and those below apply.

**3.1 Duplicate dilatation tests**

Tests carried out at different times on two coal pencils prepared before each heating cycle from a single coal sample and treated in the same retort in the same furnace in independent heating cycles by the same operator.

**3.2 Maximum contraction**

The maximum downward movement of the dilatometer piston, measured from the zero point and expressed as a percentage of the initial pencil length (see Figure 1(c)). However, if the final trace of the curve is not truly horizontal but slopes downward, the maximum contraction is the value observed at 500°C (see Figure 1(d)).

**3.3 Maximum dilatation**

The maximum upward movement of the dilatometer piston after contraction, measured from the zero point and expressed as a percentage of the initial pencil length. The value can be either positive or negative (see Figure 1).

**3.4 Temperature of initial contraction**

The temperature at which the downward movement of the dilatometer piston is 0.5 mm (see  $T_1$  in Figure 1).