

Australian Standard™

Timber—Machine proof grading



This Australian Standard was prepared by Committee TM-003, Timber grading. It was approved on behalf of the Council of Standards Australia on 29 June 2005. This Standard was published on 25 August 2005.

The following are represented on Committee TM-003:

A3P
AFFS Forestry Research
Australian Timber Importers Federation
CSIRO Manufacturing, and Infrastructure Technology
Curtin University of Technology
Forest and Forest Products Employment Skills Company
Forests New South Wales
Housing Industry Association
Master Builders Australia
New Zealand Forest Research Institute
New Zealand Timber Industry Federation
New Zealand Timber Suppliers Group
Tasmanian Timber Promotion Board
Timber Promotion Council
Timber Queensland
University of Technology, Sydney

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards™ and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard™

Timber—Machine proof grading

Originated as AS 3519—1993.
Second edition 2005.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia, GPO Box 476, Sydney, NSW 2001, Australia

ISBN 0 7337 6827 X

PREFACE

This Standard was prepared by the Australian members of Joint Standards Australian/Standards New Zealand Committee TM-003, Timber Grading, to supersede AS 3519—1993. After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this Standard is to provide timber producers and graders with methods for machine proof grading of sorted sub-populations of timber to enable pieces of timber to be designated a stress grade for structural purposes.

This Standard is intended for use by sawmill and grading operators, quality assurance auditors, government authorities, timber inspectors and all personnel concerned with the proof-grading of timber.

Changes to the previous edition are as follows:

- (a) Now in limit states format (i.e., the ψ factor has been replaced with ψ_k).
- (b) The application clause has been moved to the Preface.
- (c) The requirements for pre-sorting of timber have been moved from the Appendix to Section 2.
- (d) References to personnel have been removed, as they are contractual in nature.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

CONTENTS

	<i>Page</i>
FOREWORD.....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE	5
1.2 REFERENCED DOCUMENTS	5
1.3 DEFINITIONS	5
1.4 NOTATION	7
SECTION 2 PROOF GRADING	
2.1 PROOF-GRADING SYSTEM.....	8
2.2 VERIFICATION	8
2.3 MACHINE PROOF-GRADER.....	8
2.4 PROOF-GRADING PROCEDURE.....	10
2.5 PRE-SORTING OF TIMBER.....	10
2.6 CALCULATION OF PROOF LOAD	11
2.7 GRADING REQUIREMENTS.....	11
2.8 MARKING	12
APPENDICES	
A PROOF-GRADING OPERATION FLOW CHART.....	13
B ESTIMATE OF PROOF STRESS	14
C CALCULATION OF NOMINAL BENDING STRESS AND DEFLECTION	21

FOREWORD

The process of grading timber for obtaining stress grades incorporates three essential operations—

- (a) specification of a parent population of timber;
- (b) sorting of this parent population into sub-populations that are then designated to specific stress grades; and
- (c) checking structural properties of each stress grade from the graded timber.

Proof grading is a method for obtaining stress-graded timber by the use of a machine proof-grader. It is supported by an initial evaluation of properties (that is, an in-grade evaluation using AS/NZS 4063) and continuous monitoring to check for variation of the properties of the population of timber.

The concept of proof grading is based on the principle that at some stage during the grading process a specified proportion of the timber (this Standard specifies all of the timber) is subjected to a proof stress, which it sustains without failure.

The proof stress is induced in a piece of timber by a machine that applies the stress continuously along all or most of the length of timber. This proof stress is directly related to the specific stress grade of the timber.

In this Standard it is assumed that a proof load is applied in a continuous manner along the loaded edge of a piece of timber to induce a predetermined level of bending stress, that is, a proof stress corresponding to the specific stress grade of that timber. Therefore, as a piece of timber passes through a machine proof-grader, the timber is continuously loaded on edge by a proof load, which induces an accompanying proof stress within the timber. If the timber sustains this proof stress without damage or excessive deformation, then it is deemed to belong to the specific stress grade. This Standard would require modification if the proof load is applied in some other manner.

It is expected that, when testing a population of timber, some proportion of the pieces tested will fail at the proof load. Tables are given for 5% and 1% expected failure rates. The remaining pieces that have not failed are assigned to the stress-grade.

It is intended the proof-grading machine be operated by a person who is properly trained (to the level necessary) in the technique of machine proof grading.

The term ‘stress grade’ refers to the structural properties of a population of graded timber. All pieces of timber within the population are assigned a common suite of design properties to be used for structural design purposes. The design properties are established from the measured strength properties of the stress-graded sub-population. That is to say, the term stress grade is more appropriately applied to a population of graded timber and not to a single piece of timber.

Design information on joint strength and compression (bearing) perpendicular to the grain are not covered by the allocation of timber to a stress grade.

Documentation should be kept of the process, its establishment (e.g., the initial evaluation) and any monitoring and quality control measures undertaken (including test results, calibration and ongoing records of production).

STANDARDS AUSTRALIA

Australian Standard
Timber—Machine proof grading

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard sets out procedures for obtaining stress-graded timber by machine proof grading.

1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

AS

- | | |
|--------|--|
| 1604 | Specification for preservative treatment |
| 1604.1 | Part 1: Sawn and round timber |
| 1613 | Timber—Colours for marking F-grades |
| 1720 | Timber structures |
| 1720.1 | Part 1: Design methods |
| 2082 | Timber—Hardwood—Visually stress-graded for structural purposes |
| 2858 | Timber—Softwood—Visually graded for structural purposes |

AS/NZS

- | | |
|------|---|
| 4063 | Timber—Stress-graded—In-grade strength and stiffness evaluation |
|------|---|

1.3 DEFINITIONS

For the purpose of this Standard, the definitions below apply.

1.3.1 Characteristic proof load factor

Factor applied to the characteristic stress in bending to derive a proof stress.

1.3.2 Characteristic stress in bending

Design property for assessing the bending strength of timber having a designated stress grade.

NOTE: The characteristic stresses in bending for stress-graded timber, assigned an F-grade, are given in AS 1720.1.

1.3.3 Double-pass grading

Proof-grading method in which each piece of timber is proof tested twice, each time with the opposite edge placed in tension.

1.3.4 F-grade

Stress-grade of timber for which the specific suite of design properties given in AS 1720.1 are applicable.