

AS 2792—1992

Reconfirmed 2017

Australian Standard<sup>®</sup>

---

**Fire hose—Delivery layflat**

---

This Australian Standard was prepared by Committee FP/9, Fire Hydrant Installations. It was approved on behalf of the Council of Standards Australia on 5 May 1992 and published on 13 July 1992.

---

The following interests are represented on Committee FP/9:

Australian Assembly of Fire Authorities  
Australian Fire Protection Association  
Australian Uniform Building Regulations Coordinating Council  
Australian Valve Manufacturers Association  
Board of Works, Melbourne  
Civil Aviation Authority  
Commonwealth Fire Board  
Confederation of Australian Industry  
Department of Bush Fire Services, New South Wales  
Department of Defence  
Fire Protection Industry Association of Australia  
Institute of Engineers of Australia  
Insurance Council of Australia  
Water Board, Sydney—Illawarra—Blue Mountains  
Western Australian Fire Brigades Board

---

**Review of Australian Standards.** To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

**STANDARDS AUSTRALIA**

---

**RECONFIRMATION**

**OF**

**AS 2792—1992**

**Fire hose—Delivery layflat**

---

**RECONFIRMATION NOTICE**

Technical Committee FP-009 has reviewed the content of this publication and in accordance with Standards Australia procedures for reconfirmation, it has been determined that the publication is still valid and does not require change.

Certain documents referenced in the publication may have been amended since the original date of publication. Users are advised to ensure that they are using the latest versions of such documents as appropriate, unless advised otherwise in this Reconfirmation Notice.

Approved for reconfirmation in accordance with Standards Australia procedures for reconfirmation on 20 January 2017.

The following are represented on Technical Committee FP-009:

Association of Accredited Certification Bodies  
Association of Hydraulic Services Consultants Australia  
Australasian Fire and Emergency Service Authorities Council  
Australian Building Codes Board  
Australian Fire Safety Practitioner's Accreditation Board  
Australian Industry Group  
Australian Steel Institute  
Engineers Australia  
Fire Protection Association Australia  
Insurance Council of Australia  
International Copper Association Australia  
Master Plumbers Australia  
Property Council of Australia

## NOTES

AS 2792—1992

Australian Standard<sup>®</sup>

---

**Fire hose—Delivery layflat**

---

First published as AS 2792—1985  
Second edition 1992.

PUBLISHED BY STANDARDS AUSTRALIA  
(STANDARDS ASSOCIATION OF AUSTRALIA)  
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 7517 4

## PREFACE

This Standard was prepared by the Standards Australia Committee on Fire Hydrant Installations. It covers percolating and non-percolating delivery fire hose in various grades according to their intended working pressures and supersedes AS 2792—1985, *Fire hose—Delivery layflat* edition.

For some time a variety of specifications for fire hose have been used by various organizations. The committee examined these and accepted their broad principles, but has adapted some requirements to suit Australian conditions.

In the preparation of this Standard, account has been taken of the following documents:

Central Fire Brigades Advisory Council (England and Wales), Scottish Central Fire Brigades Advisory Council—Joint Committee on Design and Development of Appliance and Equipment: Specification JCDD/1/1, *Requirement specification for non-percolating delivery hose for fire brigade use (with or without an outer coating or jacket)*.

Department of Defence: DEF(AUST) 5195, *Australian Defence standard for hose, synthetic fibre, rubber lined (fire fighting, delivery, 38 mm, 50 mm, 63 mm and 70 mm) specification*.

New South Wales Fire Brigades:

*Requirement specification for non-percolating delivery hose for fire brigade use.*

Department of Housing and Construction:

*Specification for fire hose.*

BS 6391: 1983, *Non-percolating layflat delivery hoses and hose assemblies for fire fighting purposes.*

Fire hose requires to be constructed to resist high pressures under working conditions. Consequently the assessment of the performance of hose under various test conditions specified is intended to be a measure of the reliability of the fire hose during its most arduous service.

Appendix R which gives a full length kink resistance test has been added to this revision of the Standard.

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

# CONTENTS

	<i>Page</i>
FOREWORD .....	4
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE .....	5
1.2 APPLICATION .....	5
1.3 REFERENCED AND RELATED DOCUMENTS .....	5
1.4 DEFINITIONS .....	5
1.5 CLASSIFICATION .....	5
SECTION 2 GENERAL REQUIREMENTS	
2.1 CONSTRUCTION .....	6
2.2 INSIDE DIAMETER .....	6
2.3 NOMINAL LENGTH .....	6
2.4 MASS .....	6
2.5 MARKING .....	6
SECTION 3 PERFORMANCE REQUIREMENTS	
3.1 ALL HOSE .....	7
3.2 PERCOLATING HOSE .....	7
3.3 NON-PERCOLATING HOSE .....	8
APPENDICES	
A PURCHASING GUIDELINES .....	9
B ADDITIONAL REQUIREMENTS .....	10
C LIST OF REFERENCED AND RELATED DOCUMENTS .....	10
D APPARATUS .....	11
E PROOF PRESSURE TEST .....	11
F BURST PRESSURE TEST .....	12
G DETERMINATION OF PRESSURE LOSS .....	13
H DIMENSIONAL STABILITY TEST .....	14
I KINK TEST .....	15
J PERCOLATION TEST .....	16
K ABRASION TEST .....	17
L LINING ADHESION TEST .....	19
M AGEING TEST .....	21
N COATING STABILITY TEST .....	21
O REPAIRABILITY TEST .....	22
P FIRE TEST .....	23
Q CHEMICAL RESISTANCE TEST .....	24
R FULL LENGTH KINK RESISTANCE TEST .....	25

## FOREWORD

In the absence of a fixed fire protection system, the most convenient method of delivering water to a fire is by means of a flexible hose.

The first fire hose was made of leather with longitudinal seams hand-sewn or joined by rivets. This presented a number of problems including mass, lack of flexibility and the difficulty of repairing seams part way along the length.

Consequently in Scotland around 1850, a more flexible, lighter and seamless hand-woven flax hose was produced. The major disadvantage lay in the slow production rate, but this was overcome by the development of weaving machines which are now used for the manufacture of hose jackets.

This Standard is concerned with two types of fire hose commonly known as layflat fire hose, viz percolating and non-percolating.

Percolating hose may be made from natural fibre, or synthetic fibre, or blends of both which may be unlined or lined with natural or synthetic material or vulcanized natural rubber lining. Percolating hose is generally lighter than non-percolating hose of the same size, and because water seeps through the jacket, the hose provides a degree of self-protection against embers and flame when in use. For this reason percolating hose is not subject to the heat test. Further, the abrasion test cannot be satisfactorily carried out on a wet jacket and is not applied to percolating hose. The rate of percolation in a natural fibre hose is controlled by the swelling of the fibres as they absorb water. Because synthetic fibres have a lower water absorption, the rate of percolation is controlled by a thin lining.

The prime reason for using non-percolating hose is to minimize water damage to property from seepage. It may be used for the application of foam. Because the lining is thicker than in a percolating hose, the inner surface is smoother, resulting in lower pressure losses due to friction. Where resistance to abrasion or chemical attack is a factor, coated non-percolating hose should be considered.

## STANDARDS AUSTRALIA

**Australian Standard**  
**Fire hose—Delivery layflat**

## SECTION 1 SCOPE AND GENERAL

**1.1 SCOPE** This Standard specifies the dimensional and performance requirements for layflat delivery fire hose of two types, viz percolating and non-percolating, intended for the delivery of water or foam.

NOTE: Guidelines for the purchasing of fire hose are given in Appendix A.

**1.2 APPLICATION** Layflat delivery fire hose shall comply with the general requirements of Section 2, and with the performance requirements of Section 3.

NOTE: Additional requirements, i.e. those properties for which requirements may be specified by the purchaser in addition to the requirements of Section 2 and Section 3, are set out in Appendix B.

**1.3 REFERENCED AND RELATED DOCUMENTS** A list of the documents referred to and related to in this Standard is given in Appendix C.

**1.4 DEFINITIONS** For the purpose of this Standard, the definitions below apply.

**1.4.1 Coating** An external surface application.

**1.4.2 Informative** An Appendix giving additional information, recommendations, guidelines or other non-mandatory statements.

**1.4.3 Jacket** The woven fabric construction of the hose.

**1.4.4 Natural fibre** Flax, hemp, cotton or a combination of these fibres.

**1.4.5 Normative** An Appendix which is essential to the understanding of the Standard.

**1.4.6 Synthetic fibre** Man-made fibre.

**1.4.7 Warp** The longitudinal threads of the jacket.

**1.4.8 Weft** The circumferential threads of the jacket.

**1.4.9 Lining** A vulcanized natural rubber or synthetic interior surface application.

**1.4.10 Percolating hose** Hose which is manufactured to allow water permeation through the jacket.

**1.4.11 Non-percolating hose** Hose which is manufactured to prevent water permeation through the jacket.

**1.4.12 Extruded hose** A non-percolating hose consisting of a jacket onto which the lining and coating are applied by an extrusion process.

**1.4.13 Layflat** A characteristic of softwall hose which assumes a flattened shape when empty.

**1.5 CLASSIFICATION** Fire hose shall be classified according to working pressure in accordance with Table 1.1.

**TABLE 1.1**  
**CLASSIFICATION OF FIRE HOSE**

Class	Working pressure kPa	Proof test pressure kPa	Burst pressure (minimum), kPa
L (Low)	1 000	1 500	2 500
M (Medium)	1 400	2 100	3 500
H (High)	2 100	3 150	5 250