

Australian Standard[®]

**TEXTILE FABRICS—
DETERMINATION OF BURNING
BEHAVIOUR—
DETERMINATION OF SURFACE
BURNING TIME**

This Australian Standard was prepared by Committee TX/13, Burning Behaviour of Textiles and Textile Products. It was approved on behalf of the Council of the Standards Association of Australia on 2 May 1988 and published on 8 August 1988.

The following interests are represented on Committee TX/13:

Attorney-General's Department
Australian Assembly of Fire Authorities
Australian Confederation of Apparel Manufacturers
Australian Consumers Association
Australian Council of Furniture Manufacturers
Australian Federation of Consumer Organizations
Australian Knitting Industries Council
Australian Retailers' Association
Australian Wholesale Softgoods Federation
Australian Wool Corporation
Australian Wool Testing Authority, Textile Testing
Carpet Institute of Australia
Consumer Affairs Bureau, Queensland
CSIRO, Division of Wool Technology
Department of Consumer Affairs, New South Wales
Department of Health
Department of Industrial Relations, New South Wales
Department of Labour and Industry, Tasmania
Ministry of Consumer Affairs, Victoria
Plastics Institute of Australia
Royal Children's Hospital, Melbourne
Textile Clothing and Footwear Council of Australia
Textile Council of Australia
The Textile Institute
Trade Practices Commission
University of New South Wales
Wool Textile Manufacturers of Australia

***Review of Australian Standards.** To keep abreast of progress in industry, Australian Standards are subject to periodic review and are kept up to date by the issue of amendments or new editions as necessary. It is important therefore that Standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

Full details of all Australian Standards and related publications will be found in the Standards Australia Catalogue of Publications; this information is supplemented each month by the magazine 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn Standards.

Suggestions for improvements to Australian Standards, addressed to the head office of Standards Australia, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian Standard should be made without delay in order that the matter may be investigated and appropriate action taken.

This Standard was issued in draft form for comment as DR 86086.

AS 2755.3—1988

Australian Standard®

**TEXTILE FABRICS—
DETERMINATION OF BURNING
BEHAVIOUR—
DETERMINATION OF SURFACE
BURNING TIME**

First published as AS 2755.3—1988.

PUBLISHED BY STANDARDS AUSTRALIA
(STANDARDS ASSOCIATION OF AUSTRALIA)
1 THE CRESCENT, HOMEBUSH, NSW 2140

ISBN 0 7262 5139 9

PREFACE

This Standard was prepared by the Association's Committee on Burning Behaviour of Textiles and Textile Products under the direction of the Textile Standards Board. It describes the method for determining the surface burning time of textile fabrics.

This Standard was taken from the ISO document ISO/TC 38/SC 19/WG2 N 132 together with amendments from documents ISO/TC 38/SC 19/WG2 N 148 and ISO/TC 38/SC 19/WG2 N156.

The format of the Standard has been changed slightly to comply with AS 2744, *Preparation, application and format of fire tests*.

CONTENTS

	<i>Page</i>
1 SCOPE AND APPLICATION	3
2 REFERENCED DOCUMENTS	3
3 PRINCIPLE	3
4 APPLICATION TO FIRE HAZARD ASSESSMENT	3
5 DEFINITIONS	3
6 HEALTH AND SAFETY OF TEST OPERATORS	3
7 APPARATUS	3
8 TEST SPECIMENS	3
9 PROCEDURES	4
10 REPORT	5
11 CROSS-REFERENCE IN OTHER AUSTRALIAN STANDARDS	5
12 QUOTING OF RESULTS IN COMMERCIAL LITERATURE	5
 APPENDICES	
A BURNER FOR TESTING THE BURNING BEHAVIOUR OF TEXTILES AND TEXTILE PRODUCTS	6
B BRUSHING DEVICE FOR RAISING THE SURFACE FIBRES OF A FABRIC TEST SPECIMEN	8
C WASH PROCEDURE	9

© Copyright — STANDARDS AUSTRALIA

Users of Standards are reminded that copyright subsists in all Standards Australia publications and software. Except where the Copyright Act allows and except where provided for below no publications or software produced by Standards Australia may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing from Standards Australia. Permission may be conditional on an appropriate royalty payment. Requests for permission and information on commercial software royalties should be directed to the head office of Standards Australia.

Standards Australia will permit up to 10 percent of the technical content pages of a Standard to be copied for use exclusively in-house by purchasers of the Standard without payment of a royalty or advice to Standards Australia.

Standards Australia will also permit the inclusion of its copyright material in computer software programs for no royalty payment provided such programs are used exclusively in-house by the creators of the programs.

Care should be taken to ensure that material used is from the current edition of the Standard and that it is updated whenever the Standard is amended or revised. The number and date of the Standard should therefore be clearly identified.

The use of material in print form or in computer software programs to be used commercially, with or without payment, or in commercial contracts is subject to the payment of a royalty. This policy may be varied by Standards Australia at any time.

STANDARDS ASSOCIATION OF AUSTRALIA

Australian Standard

TEXTILE FABRICS—DETERMINATION OF BURNING BEHAVIOUR—
DETERMINATION OF SURFACE BURNING TYPE

1 SCOPE AND APPLICATION. This Standard specifies a method for the measurement of surface burning time of textile fabrics which have a raised fibre surface, i.e. napped, pile, tufted, flocked, or similar surface. This test simulates the surface burning properties of textiles from a small heat source or where the ignition source is likely to be of a fleeting nature.

NOTE: This Standard complies with AS 2744.

2 REFERENCED DOCUMENTS. The documents below are referred to in this Standard:

AS	
2744	Preparation, application and format of fire tests
ISO	
1101	Technical drawings—Geometrical tolerancing of form orientation, location and run-out—Generalities, definitions, symbols, indications on drawings
ASTM	
D 1230	Test method for flammability of clothing textiles

3 PRINCIPLE. A dry specimen of the fabric is supported on a vertical plate and its raised surface is ignited near the top in a standard manner. The spread of flame downwards on the surface of the fabric to a reference line is timed.

NOTE: The flame of a pile surface travels more reproducibly downwards or sideways than upwards. It is considered that the blanketing effect of the combustion products may not allow the surface pile above the flame front to burn whereas the surface pile below the flame front is not affected in this way.

4 APPLICATION TO FIRE HAZARD ASSESSMENT. These test results on their own do not indicate the fire hazard of the textile fabric under actual fire conditions and consequently, should not be applied to the assessment of fire hazard without taking into account additional supportive information.

5 DEFINITIONS. For the purpose of this Standard, the definitions below apply.

5.1 Surface burn—spread of flame over the surface of a material without ignition of its basic structure.

5.2 Surface burning—time the time required for the pile or nap of a fabric to burn a defined distance when tested by the method described in this Standard.

6 HEALTH AND SAFETY OF TEST OPERATORS. Burning of textiles may produce smoke and toxic gases which can affect the health of operators. The testing area should be cleared of smoke and fumes by suitable means of forced ventilation after each test, then restored to the required testing conditions (see Clauses 7.2 and 9(a)).

7 APPARATUS.

7.1 Construction of testing equipment. The equipment shall be constructed of material which will not be adversely affected by the gas fumes.

NOTE: Some products of combustion are corrosive and the equipment should be made of materials which will facilitate cleaning.

7.2 Location of test. A location is to be selected in which the air movement is less than 0.2 m/s at the commencement of the test and is not further influenced by mechanical devices during the test. The volume of air surrounding the test location shall be such that the test is not affected by any reduction of oxygen concentration.

7.3 Specimen holder. The specimen holder shall be a stainless steel plate approximately 150 mm long, 75 mm wide and 3 mm thick (see Figure 1). The specimen shall be framed by stainless steel 3 mm thick so that an area of 125 mm × 50 mm of fabric surface is exposed for testing. The frame shall have a reference mark which shall be 75 mm below the ignition point of the test specimen.

7.4 Gas burner. A gas burner as described in Appendix A or any other burner may be used provided it gives the same test results as the burner described in Appendix A.

NOTE: It may be convenient to control the gas to the burner through a solenoid valve. In such circumstances, it is permissible to leave a small pilot light 5 mm long on the burner.

7.5 Gas. Commercial grade propane or butane gas, or a mixture thereof is suitable.

7.6 Timing device for burner (optional). A timing device to control and measure the application time of the flame for a period of 1.0 ± 0.1 s. This should be used for specimens which burn down 75 mm in less than one second.

7.7 Brushing device. A brushing device as described in Appendix B should be used.

7.8 Washing and drying apparatus. Washing and drying apparatus as described in Appendix C should be used.

7.9 Circulating air oven. A circulating air oven capable of drying the test specimens at $105 \pm 2^\circ\text{C}$ should be used.

7.10 Dry airtight container. A dry airtight container capable of holding dried test specimens should be used.

7.11 Stopwatch. A stopwatch or other timing device readable to 0.2 s should be used.

8 TEST SPECIMENS.

8.1 Size. The size of each specimen shall be 150 mm × 75 mm, except fabrics narrower than 75 mm shall be cut and tested at their full width.