

DR 95297

1996 ed  
Fwd 19960221

AS 1049—1986


UDC 621.315.616:621.315.221.8:678.742.2

# Australian Standard<sup>®</sup> 1049—1986

1996 ED.

---

## TELECOMMUNICATION CABLES— INSULATION AND SHEATH— POLYETHYLENE



STANDARDS ASSOCIATION OF AUSTRALIA  
*Incorporated by Royal Charter*

This Australian standard was prepared by Committee TE/9, Polyethylene Insulation for Telecommunication Cables. It was approved on behalf of the Council of the Standards Association of Australia on 18 July 1986 and published on 5 September 1986.

---

The following interests are represented on Committee TE/9:

Confederation of Australian Industry  
Department of Defence  
Plastics Institute of Australia Inc.  
Railways of Australia Committee  
Telecom Australia

---

***Review of Australian Standards.** To keep abreast of progress in industry, Australian standards are subject to periodic review and are kept up-to-date by the issue of amendments or new editions as necessary. It is important therefore that standards users ensure that they are in possession of the latest edition, and any amendments thereto.*

*Full details of all SAA publications will be found in the Catalogue of SAA Publications; this information is supplemented each month by SAA's journal 'The Australian Standard', which subscribing members receive, and which gives details of new publications, new editions and amendments, and of withdrawn standards.*

*Suggestions for improvements to Australian standards, addressed to the head office of the Association, are welcomed. Notification of any inaccuracy or ambiguity found in an Australian standard should be made without delay in order that the matter may be investigated and appropriate action taken.*

---

*This standard was issued in draft form for comment as DR 84011.*

AUSTRALIAN STANDARD

**TELECOMMUNICATION  
CABLES—  
INSULATION/SHEATH—  
POLYETHYLENE**

AND  
Brian Barron  
+  
Kor. Prof. H.  
Nashville, TN  
06/09/26

Rae  
For Info  
The AND  
is missing  
Cable

AS 1049—1986

First published ..... 1971  
Second edition ..... 1986

PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA  
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.

ISBN 0 7262 4324 8



17 SEP 1986

**AUSTRALIAN STANDARD**

**TELECOMMUNICATION  
CABLES—  
INSULATION<sup>AND</sup> SHEATH—  
POLYETHYLENE**

**AS 1049—1986**

First published .....	1971
Second edition.....	1986

**PUBLISHED BY THE STANDARDS ASSOCIATION OF AUSTRALIA  
STANDARDS HOUSE, 80 ARTHUR ST, NORTH SYDNEY, N.S.W.**

ISBN 0 7262 4324 8

## PREFACE

This edition of this standard was prepared by the Association's Committee on Polyethylene Insulation for Telecommunication Cables to supersede AS 1049—1971, Polyethylene Insulation and Sheath for Telecommunication Cables. The standard has been organized in sections with the test methods given as appendices. In this edition a considerable number of test methods were added which are based on ASTM standard methods or tests from BS 2782, Methods of Testing Plastics. Grateful acknowledgment is made of the assistance received from these sources.

The purpose of the standard is to provide specifications of the materials used for insulating and sheathing telecommunication cables, in terms of the physical and electrical characteristics of the cables. Test methods to evaluate the properties of the various polyethylene insulation systems are specified. The requirements and tests apply to either solid or cellular insulation of metallic conductors of cables of both filled and air core construction. They also apply to solid sheath with and without a screen or moisture barrier, where it is used on cables.

© Copyright — STANDARDS ASSOCIATION OF AUSTRALIA 1986

Users of standards are reminded that copyright subsists in all SAA publications. No part of this publication may be reproduced, stored in a retrieval system in any form or transmitted by any means without prior permission in writing of the Standards Association of Australia.

## CONTENTS

	<i>Page</i>
<b>SECTION 1. GENERAL</b>	
1.1 SCOPE .....	4
1.2 APPLICATION .....	4
1.3 REFERENCED DOCUMENTS .....	4
1.4 DEFINITIONS .....	4
<b>SECTION 2. POLYETHYLENE INSULATING AND SHEATHING COMPOUNDS</b>	
2.1 GENERAL .....	5
2.2 MATERIAL CHARACTERISTICS .....	5
2.3 CLASSIFICATION .....	5
2.4 MELT FLOW INDEX .....	5
2.5 DENSITY .....	5
2.6 TENSILE STRESS AT YIELD AND ELONGATION AT BREAK .....	5
2.7 STABILIZATION .....	5
2.8 ENVIRONMENTAL STRESS-CRACKING RESISTANCE .....	5
2.9 BUTYL RUBBER .....	6
2.10 CARBON BLACK .....	6
2.11 DIELECTRIC DISSIPATION FACTOR AND RELATIVE PERMITTIVITY .....	6
<b>SECTION 3. POLYETHYLENE INSULATION AND SHEATH</b>	
3.1 GENERAL .....	10
3.2 POLYETHYLENE COMPOUND .....	10
3.3 CABLE .....	10
3.4 COLOUR .....	10
3.5 STABILIZATION .....	10
3.6 COMPATIBILITY .....	10
3.7 SHRINKBACK .....	10
<b>APPENDICES</b>	
A DETERMINATION OF MELT FLOW INDEX .....	14
B DETERMINATION OF DENSITY .....	17
C DETERMINATION OF TENSILE STRESS AT YIELD, AND ELONGATION AT BREAK .....	20
D DETERMINATION OF STABILIZER TYPE .....	23
E DETERMINATION OF STABILIZER CONCENTRATION .....	28
F DETERMINATION OF ENVIRONMENTAL STRESS-CRACKING .....	34
G DETERMINATION OF BUTYL RUBBER CONTENT .....	41
H DETERMINATION OF CARBON BLACK CONTENT .....	43
J DETERMINATION OF CARBON BLACK DISPERSION .....	44
K DETERMINATION OF DIELECTRIC DISSIPATION FACTOR AND RELATIVE PERMITTIVITY .....	48
L DETERMINATION OF COLOUR .....	51
M DETERMINATION OF BLOOMING AND MIGRATION OF COLOURS .....	52
N DETERMINATION OF COLOURFASTNESS TO DAYLIGHT .....	53
P DETERMINATION OF COLOURFASTNESS TO WATER .....	57
Q DETERMINATION OF COMPATIBILITY OF POLYETHYLENE INSULATION WITH FILLING COMPOUND .....	58
R DETERMINATION OF SHRINKBACK .....	63
S REMOVAL OF CELLULAR STRUCTURE IN CELLULAR INSULATION .....	64
T PREPARATION OF COMPRESSION MOULDED PLAQUE .....	65

## STANDARDS ASSOCIATION OF AUSTRALIA

## Australian Standard

for

## TELECOMMUNICATION CABLES—INSULATION AND SHEATH—POLYETHYLENE

## SECTION 1. GENERAL

**1.1 SCOPE.** This standard specifies the requirements for polyethylene used for insulation and sheathing of the telecommunications cables and provides test methods to evaluate the properties specified. The requirements and tests apply to both solid and cellular insulation of metallic conductors of both filled and air-cored cables and to solid sheath with or without a metallic screen or moisture barrier.

The standard specifies the composition, physical and electrical requirements of various types of polyethylene in three main parts as follows:

- (a) *Section 2.* Specifies the requirements of the polyethylene compounds as supplied to the cable manufacturers and forming the basis of the raw material quality control procedures for both the polymer manufacturer and the cable manufacturer.
- (b) *Section 3.* Specifies the requirements of various types of polyethylene taken from completed cable or, where specified, during manufacture, providing the basis of the cable manufacturer's quality control and end-user acceptance procedures for the completed cable.
- (c) *Appendices.* Provide a set of reference test methods for determination of compliance with the requirements of this standard.

**1.2 APPLICATION.** The standard applies to the testing of polyethylene materials for insulation and sheath prior to, during, and following manufacture of telecommunication cables.

This standard also applies to polyethylene used in telecommunication cables but it does not apply to compounds that are semiconductive, formulated for cross-linking or to be fire retardant.

It is recognized that whereas polyethylene is, however, used extensively in a much wider range of cables e.g. coaxial, electrical and control cables, it is not the intent of the standard to preclude the use of polyethylene in such applications.

The standard does not include dimensions or electrical and mechanical properties of completed cables.

**1.3 REFERENCED DOCUMENTS.** The following standards are referred to in this standard.

- AS 1152 Test Sieves
- AS 1886 Terms Relating to Plastics
- AS 2001 Methods of Test for Textiles  
Part 4.1—Colourfastness tests—Definitions and General Requirements
- AS 2164 One-mark Volumetric Flasks
- AS 2165 Burettes and Bulb Burettes
- AS 2166 One-mark Pipettes
- AS 2193 Methods of Calibration and Grading of Force-measuring Systems of Testing Machines
- BS 612 Nessler Cylinders
- ANSI/EIA RS359-A-84 Colours for Colour Identification and Coding
- ASTM D638-77 Tensile Properties of Plastics
- ASTM D1510-75 Test for Iodine Adsorption Number of Carbon Black
- ASTM E1 ASTM Thermometers

**1.4 DEFINITIONS.** For the purpose of this standard, terms defined in AS 1886 and the following definitions apply:

**1.4.1 Filled cable**—a term denoting the continuous filling of the interstices of the cable core to prevent water penetration into the cable.

NOTE: The filler should not be confused with the polyethylene additives or mineral filler. An unfilled cable is termed an aircore cable.

**1.4.2 Moisture-barriered cable**—cable with an aluminium foil bonded to the inner surface of the sheath to prevent moisture permeation into the cable core.

NOTE: The aluminium foil may also serve as an electrical screen.